

W0/ 96/23829

VERIFIED TRANSLATION OF PCT

44382/96

IN THE MATTER OF an Australian
Application corresponding to
PCT Application PCT/EP96/00195

I, Andrew Harvey David SUMPTER BSc,
c/o Europa House, Marsham Way, Gerrards Cross, Buckinghamshire,
England, do solemnly and sincerely declare that I am conversant
with the English and German languages and am a competent
translator thereof, and that to the best of my knowledge and
belief the following is a true and correct translation of the
PCT Application filed under No. PCT/EP96/00195.

Date: 23 July 1997


A. H. D. SUMPTER

For and on behalf of RWS Translations Ltd.

PCT WORLD ORGANISATION FOR INTELLECTUAL PROPERTY
International Office
INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International patent classification^a: C08G 61/00</p>	<p>A1</p>	<p>(11) International publication number: WO 96/23829</p> <p>(43) International publication date: 8 August 1996 (08.08.96)</p>
<p>(21) International application number: PCT/EP96/00195</p> <p>(22) International filing date: 18 January 1996 (18.01.96)</p> <p>(30) Data relating to the priority: 261/95 31 January 1995 (31.01.95)</p> <p>(71) Applicant (for all designated States except US): CIBA-GEIGY AG [CH/CH]: Klybeckstrasse 141, CH-4002 Basle (CH).</p> <p>(72) Inventors: and (75) Inventors/Applicants (US only): Andreas MÜHLEBACH [CH/CH]: Les Grands Esserts 7, CH-1782 Belfaux (CH). Andreas HAFNER [CH/CH]: Bendenweg 3, CH-3177 Laupen (CH). Paul Adriaan VAN DER SCHAAF [NL/CH]: Impasse du Castel 9, CH-1700 Fribourg (CH).</p> <p>(74) Joint Representative: CIBA-GEIGY AG: Patent Department, Klybeckstrasse 141, CH-4002 Basle (CH).</p>	<p>(81) Designated States: AL, AM, AU, BB, BG, BR, CA, CN, CZ, EE, FI, GE, HU, IS, JP, KR, LK, LR, LT, LV, MD, MG, MK, MN, MX, NO, NZ, PL, RO, SG, SI, SK, TR, TT, UA, US, UZ, VN, ARIPO Patent (KE, LS, MW, SD, SZ, UG), Eurasian Patent (AZ, BY, KG, KZ, RU, TJ, TM), European Patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI Patent (BF, BJ, CF, CG, CI, GA, GN, ML, MR, NE, SN, TD, TG).</p> <p>Published: With the International Search Report. Before expiry of the period provided for amending the claims. Further publication will be made if such amendments are received.</p>	

As printed

(54) Title: **POLYMERISABLE COMPOSITION, PROCESS FOR PRODUCING CROSS-LINKED POLYMERS, AND CROSS-LINKABLE POLYMERS**

(54) Bezeichnung: **POLYMERISIERBARE ZUSAMMENSETZUNG, VERFAHREN ZUR HERSTELLUNG VERNETZTER POLYMERE UND VERNETZBARE POLYMERE**

(57) Abstract

A composition containing (a) catalytic quantities of a single-component metathesis polymerisation catalyst and (b) at least one polymer with tensioned cycloalkenylene radicals bonded in the polymer skeleton alone or mixed with tensioned cyclo-olefines. The composition can be polymerised thermally or photochemically by metathesis polymerisation and is suitable for the production of castings, coatings and relief images.

(57) Zusammenfassung

Zusammensetzung, enthaltend (a) katalytische Mengen eines Einkomponenten-Katalysators für die Metathesepolymerisation und (b) mindestens ein Polymer mit im Polymerückgrat gebundenen gespannten Cycloalkenyleneinheiten alleine oder in Mischung mit gespannten Cycloolefinen. Die Zusammensetzung kann thermisch oder photochemisch durch Metathesepolymerisation polymerisiert werden und eignet sich zur Herstellung von Formkörpern, Beschichtungen und Reliefabbildungen.

Polymerizable composition, process for producing cross-linked polymers, and cross-linkable polymers

The present invention relates to a composition of unsaturated polymers, in the polymer backbone of which is bonded a strained cycloalkenylene, with a one-component catalyst for metathesis polymerization which is induced thermally or by actinic radiation; a process for the polymerization of the composition; materials coated with the composition or the polymerized composition, and shaped articles of the crosslinked polymers; and crosslinkable polymers.

Thermally induced ring-opening metathesis polymerization using catalytic amounts of metal catalysts has already been known for a relatively long time and described in many cases in the literature [see, for example, Ivin, K.J., Olefin Metathesis 1-12, Academic Press, London (1983)]. Polymers obtainable in this way are prepared industrially and are commercially obtainable, for example under the trade name Vestenamer®. The industrial preparation is carried out using highly reactive two-component catalysts, as a rule transition metal halides, for example WCl_6 and metal-alkylenes, for example zinc-, aluminium- or tin-alkylene. The polymerization or gelling starts immediately after a cycloolefin has been combined with the two catalyst components. The mixtures of cycloolefin and catalyst therefore have exceptionally short pot lives, and they are suitable in practice only in the reaction injection moulding process (RIM process). The severe heating of the reaction mixture due to the heat of reaction, which imposes very high technical requirements on a controlled reaction temperature, is also a disadvantage. It is therefore difficult to adhere to a polymer specification.

WO 93/13171 describes air- and water-stable one-component and two-component catalysts based on molybdenum and tungsten compounds containing carbonyl groups and ruthenium and osmium compounds having at least one polyene ligand

for thermal metathesis polymerization and a photoactivated metathesis polymerization of strained cycloolefins, in particular norbornene. No other polycyclic - above all non-fused polycyclic - cycloolefins are mentioned. The one-component catalysts of the ruthenium compounds used, that is to say $[\text{Ru}(\text{cumene})\text{Cl}_2]_2$ and $[(\text{C}_6\text{H}_5)_3\text{Ru}(\text{CH}_3\text{CN})_2\text{Cl}]^+\text{PF}_6^-$, can indeed be activated by UV irradiation; however, the storage stability of the compositions with norbornene are [sic] completely unsatisfactory. These catalysts can replace the known two-component catalysts only in adequately.

Demonceau et al. [Demonceau, A., Noels, A.F., Saive, E., Hubert, A.J., J. Mol. Catal. 76: 123-132 (1992)] describe $(p\text{-cumene})\text{RuCl}_2\text{P}(\text{C}_6\text{H}_{11})_3$, $(\text{C}_6\text{H}_5)_3\text{PRuCl}_2$ and $(\text{C}_6\text{H}_5)_3\text{PRuHCl}$ as thermal catalysts for the ring-opening metathesis polymerization of norbornene, a fused polycycloolefin. Because their activity is too low, these catalysts have not found acceptance in industrial preparation. It is therefore proposed to increase the activity by the addition of diazoesters. It is also mentioned that only $(p\text{-cumene})\text{RuCl}_2\text{P}(\text{C}_6\text{H}_{11})_3$ is capable of polymerizing norbornene in a relatively short time at 60°C. Cyclooctene is also mentioned as a further monomer. No other cycloolefins are mentioned for the metathesis [sic] polymerization.

Petasis and Fu [Petasis, N.A., Fu, D., J. Am. Chem. Soc. 115: 7208-7214 (1993)] describe the thermal ring-opening metathesis polymerization of norbornene using bis-cyclopentadienyl-bis(trimethylsilyl)methyl-titanium(IV) as a thermally active catalyst. No other cycloolefins are mentioned for the metathesis polymerization.

No other more reactive one-component catalysts have yet been disclosed. It is furthermore also not known to use polymers with a strained cycloalkenylene in the polymer backbone for the preparation of crosslinked polymers.

It has now been found that polymers with strained cycloalkenylene radicals bonded in the polymer backbone are outstandingly suitable for the preparation of crosslinked polymers under the action particularly of one-component catalysts. The compositions are storage-stable and are even insensitive to air and oxygen,

depending on the catalysts used, which allows processing without particular protective measures. Processing is easy and the processing possibilities are diverse, because no particular measures have to be taken owing to excessive reactivity. The polymers are suitable both for the production of solid shaped articles and for coatings with particularly high adhesive strength. The polymers can furthermore be used for the production of images by means of irradiation under a photomask and subsequent development of the non-exposed portions with a suitable solvent.

The invention first relates to a composition comprising (a) catalytic amounts of a one-component catalyst for metathesis polymerization and (b) at least one polymer with strained cycloalkenylene radicals bonded in the polymer backbone, alone or mixed with strained cycloolefins.

In a preferred embodiment, the polymers are those with recurring structural units of the formula (a) in the polymer backbone



in which

R_{01} and R_{02} independently of one another are H or C_1 - C_6 alkyl, or R_{01} and R_{02} together are a bond, and

A, together with the C-C group, forms an unsubstituted or substituted strained cycloolefin ring. The structural units of the formula (a) can be bonded directly or via bridge groups, preferably identical bridge groups.

Alkyl R_{01} and R_{02} preferably contain 1 to 4 C atoms; the alkyl is preferably methyl or ethyl. R_{01} and R_{02} are particularly preferably H.

The substituents for the cycloolefin ring can be, for example, C_1 - C_6 -, and

t-butyl, methoxy, ethoxy or propyloxy; C_1 - C_4 haloalkyl or -alkoxy, for example trifluoromethyl, trichloromethyl, perfluoroethyl, bis(trifluoromethyl)methyl, trifluoromethoxy or bis(trifluoromethyl)methoxy; halogen, for example F, Cl or Br; -CN; -NH₂; secondary amino having 2 to 18 C atoms; tertiary amino having 3 to 18 C atoms; -C(O)-OR₀₃ or -C(O)-NR₀₃R₀₄, in which R₀₃ is H, C_1 - C_{18} alkyl, phenyl or benzyl and R₀₄ independently has the meaning of R₀₃.

The strained cycloolefin ring can be monocyclic or polycyclic fused and/or bridged ring systems, for example with 2 to 6, preferably 2 to 4, and particularly preferably 2 or 3 rings, which are unsubstituted or substituted and can contain heteroatoms, for example O, S, N or Si, in one or more rings and/or fused aromatic or heteroaromatic rings, for example o-phenylene, o-naphthylene, o-pyridinylene or o-pyrimidinylene. The individual cyclic rings can contain 3 to 16, preferably 4 to 12, particularly preferably 5 to 8 ring members. The cyclic olefins can contain further non-aromatic double bonds, preferably 2 to 4 such additional double bonds, depending on the ring size.

Fused-on alicyclic rings preferably contain 3 to 8, particularly preferably 4 to 7, and especially preferably 5 or 6 ring C atoms. Fused-on aromatics are preferably naphthylene and, in particular, phenylene.

In a preferred embodiment, in formula (a)

R₀₁ and R₀₂ together are a bond, and A is unsubstituted or substituted C_1 - C_{12} alkylene, preferably C_2 - C_6 alkylene; unsubstituted or substituted C_2 - C_{12} heteroalkylene, preferably C_3 - C_6 heteroalkylene with at least one heteroatom from the group consisting of O, S and N; unsubstituted or substituted C_5 - C_{12} cycloalkylene, preferably C_5 - C_7 cycloalkylene; unsubstituted or substituted C_4 - C_{12} heterocycloalkylene, preferably C_4 - C_7 heterocycloalkylene with at least one heteroatom from the group consisting of O, S and N; unsubstituted or substituted C_2 - C_{12} alkenylene, preferably C_2 - C_6 alkenylene; unsubstituted or substituted C_3 - C_{12} heteroalkenylene, preferably C_3 - C_6 heteroalkenylene with at least one heteroatom from the group consisting of O, S and N; unsubstituted or substituted C_5 - C_{12} cycloalkenylene, preferably C_5 - C_7 cycloalkenylene; or unsubstituted or

substituted C₄-C₁₂heterocycloalkenylene, preferably C₄-C₇heterocycloalkenylene with at least one heteroatom from the group consisting of O, S and N; or R₀₁ and R₀₂ independently of one another are H or C₁-C₆alkyl and A is unsubstituted or substituted C₃-C₁₂-cycloalkenylene, preferably C₅-C₇cycloalkenylene; unsubstituted or substituted C₄-C₁₂heterocycloalkenylene, preferably C₄-C₇heterocycloalkenylene with at least one heteroatom from the group consisting of O, S and N; or unsubstituted or substituted C₅-C₁₂cycloalkdienylene, preferably C₅-C₇cycloalkdienylene; or

R₀₁ is a double bond together with a terminal C atom of the radical A; R₀₂ is H or C₁-C₆alkyl; and A is unsubstituted or substituted C₁-C₁₂alkylene, preferably C₂-C₆alkylene, unsubstituted or substituted C₃-C₁₂heteroalkylene, preferably C₃-C₆heteroalkylene with at least one heteroatom from the group consisting of O, S and N; unsubstituted or substituted C₅-C₁₂cycloalkylene, preferably C₅-C₇cycloalkylene; unsubstituted or substituted C₄-C₁₂heterocycloalkylene, preferably C₄-C₇heterocycloalkylene with at least one heteroatom from the group consisting of O, S and N; unsubstituted or substituted C₂-C₁₂alkenylene, preferably C₂-C₆alkenylene; unsubstituted or substituted C₃-C₁₂heteroalkenylene, preferably C₃-C₆heteroalkenylene with at least one heteroatom from the group consisting of O, S and N; unsubstituted or substituted C₅-C₁₂cycloalkenylene, preferably C₅-C₇cycloalkenylene; or unsubstituted or substituted C₄-C₁₂heterocycloalkenylene, preferably C₄-C₇heterocycloalkenylene with at least one heteroatom from the group consisting of O, S and N; or

R₀₁ and R₀₂ each are a double bond together with in each case a terminal C atom of the radical A, and A is unsubstituted or substituted C₃-C₁₂alkylene, preferably C₃-C₆alkylene; unsubstituted or substituted C₃-C₁₂heteroalkylene, preferably C₃-C₆heteroalkylene with at least one heteroatom from the group consisting of O, S and N; unsubstituted or substituted C₅-C₁₂cycloalkylene, preferably C₅-C₇cycloalkylene; or unsubstituted or substituted C₄-C₁₂heterocycloalkylene, preferably C₄-C₇heterocycloalkylene with at least one heteroatom from the group consisting of O, S and N;

it being possible for phenylene, C₄-C₆cycloalkylene or C₄-C₆heterocycloalkylene to be fused onto the alkylene, heteroalkylene, cycloalkylene, heterocycloalkylene

alkenylene, heteroalkenylene, cycloalkenylene, heterocycloalkenylene, alkdiénylene, heteroalkdiénylene, cycloalkdiénylene and heterocycloalkdiénylene.

It is known to the expert that cyclohexene can be polymerized by metathesis only with difficulty or not at all. Cyclohexene radicals of the formula (a) are therefore not preferred. Structural units of the formula (a) in which R_{01} and R_{02} together do not form a double bond are preferred.

Particularly preferably, in formula (a), R_{01} and R_{02} together are a bond, and A is unsubstituted or substituted C_2-C_8 alkylene, unsubstituted or substituted C_3-C_7 cycloalkylene, unsubstituted or substituted C_2-C_8 alkenylene or unsubstituted or substituted C_3-C_7 cycloalkenylene; or R_{01} and R_{02} independently of one another are H or C_1-C_4 alkyl and A is unsubstituted or substituted C_3-C_7 cycloalkenylene; or R_{01} is a double bond together with a terminal C atom of the radical A; R_{02} is H or C_1-C_4 alkyl; and A is unsubstituted or substituted C_2-C_8 alkenylene, unsubstituted or substituted C_3-C_7 cycloalkylene, unsubstituted or substituted C_2-C_8 alkenylene or unsubstituted or substituted C_3-C_7 cycloalkenylene; or R_{01} and R_{02} each are a double bond together with in each case a terminal C atom of the radical A and A is unsubstituted or substituted C_3-C_8 alkylene or unsubstituted or substituted C_3-C_7 cycloalkylene.

The polymer backbone of the polymers to be used according to the invention can be built up in different ways. The polymers can be homo- or copolymers, containing structural elements of the formula (a) to the extent of at least 5 mol %, preferably 5 to 100 mol %, more preferably 5 to 80 mol %, even more preferably 10 to 70 mol %, particularly preferably 10 to 60 mol %, and especially preferably 20 to 50 mol %, based on the polymer. The polymers can be random copolymers or block copolymers.


The polymers used in the composition according to the invention include oligomers and polymers. The number of recurring structural units can accordingly

be 2 to 10 000, preferably 5 to 5000, particularly preferably 10 to 1000, and especially preferably 20 to 500.

One group of polymers which are possible for the compositions according to the invention comprises, for example, the homo- and copolymers of linear polyepoxides, polyesters, polyamides, polyester-amides, polyurethanes and polyureas in which the divalent diepoxide, dicarboxylic acid or diisocyanate radicals, or in which the divalent diol or diamine radicals, or both of these radicals, contain strained cycloolefin radicals, and which, in the case of the copolymers of these divalent radicals, contain different diepoxide, dicarboxylic acid or diisocyanate, diol or diamine radicals. The strained cycloolefin ring preferably corresponds to the formula (a), including the preferred meanings.

The polyepoxides can be built up from diepoxides, as comonomers (α), having preferably 6 to 40, and particularly preferably 8 to 30 C atoms and diols, as comonomers (β), having preferably 2 to 200, more preferably 2 to 100, and particularly preferably 2 to 50 C atoms. Diepoxides with a strained cycloolefin ring contain preferably 6 to 40, and particularly preferably 10 to 30 C atoms. The diepoxides are preferably the diglycidyl ethers, which can easily be prepared. The monomeric diepoxides can be, for example, the diglycidyl ethers of aliphatic, cycloaliphatic, aromatic or araliphatic diols. Diols with a strained cycloolefin ring contain preferably 5 to 40, and particularly preferably 7 to 30 C atoms. The diols can be, for example, aliphatic, cycloaliphatic, aromatic or araliphatic diols. Diols and diepoxides are familiar to the expert and are not listed here. Among the diepoxides, the diglycidyl ethers and diglycidyl esters are preferred. Diepoxides and diols with a strained cycloolefin ring preferably contain a structural element of the formula (a), including the preferred meanings.

The polyepoxides can contain, for example, recurring structural elements chosen from the group of structural elements of the formulae (b), (c), (d) and (e)



(b).




with the proviso that they contain at least structural elements of the formulae [sic] (b) or (c) or both, in which R_{05} and R_{06} independently of one another are a divalent radical of a strained cycloolefin or a divalent radical with a strained cycloolefin, R_{07} is a divalent radical of a diglycidylether reduced by the glycidyloxy groups and R_{08} is a divalent radical of a diol reduced by the hydroxyl group.

The polymer can contain in each case up to 100 mol % of the structural elements of the formulae (b) and (c) per mole of the polymer. If structural elements of the formulae (b) and (d) or (c) and (e) are present, advantageous mixing ratios are 5 to 95, preferably 10 to 80 mol % of structural elements of the formulae (b) and (c) and 95 to 5, preferably 90 to 20 mol % of the structural elements of the formulae (c) and (e), per mole of the polymer.

The polyepoxides are linear polyethers and are accessible in various ways, for example either by reaction of the diepoxides with the diols or by Diels-Alder reaction of polyepoxides with olefinically unsaturated diepoxide and/or diol structural units with open-chain or, preferably, cyclic 1,3-dienes to form strained cycloolefin rings.


R_{05} and R_{06} can be, for example, mono- or diolefinically unsaturated C_5 - C_9 cycloalkylene or fused polycyclic, preferably bi- or tricyclic, C_7 - C_{15} cycloalkylene. Examples are cyclopentenylene, cycloheptenylene and cyclooctenylene. In a particularly preferred embodiment, R_{05} and R_{06} independently of one another are a norbornene radical of the formula (nr_1) or (nr_2)



R_{07} and R_{08} are preferably C_2-C_{18} , preferably C_2-C_{12} alkylene, polyoxaalkylene having 2 to 50, preferably 2 to 10 oxalkylene units and 2 to 6, preferably 2 to 4 C atoms in the oxyalkylene, C_3-C_{12} , preferably C_3-C_8 cycloalkylene, C_5-C_8 cycloalkylene- CH_2 -, $-CH_2$ -(C_3-C_8 cycloalkylene)- CH_2 -, C_6-C_{14} arylene, bisphenylene, benzylene, xylylene or $-C_6H_4-X_{01}-C_6H_4-$, where X_{01} is O, S, SO, SO_2 , CO, CO_2 , NH, $N(C_1-C_4\text{-alkyl})$, alkylidene having 1 to 18, preferably 1 to 12 C atoms or C_5-C_7 cycloalkylidene. Some examples are ethylene, propylene, butylene, di-, tri- and tetraoxaethylene, cyclopentylene, cyclohexylene, cyclohexylene- CH_2 -, $-CH_2$ -cyclohexylene- CH_2 -, phenylene, $-C_6H_4-O-C_6H_4-$, $-C_6H_4-CH_2-C_6H_4-$, $-C_6H_4-CH(CH_3)-C_6H_4-$, $-C_6H_4-C(CH_3)_2-C_6H_4-$ and $-C_6H_4-C_6H_{10}-C_6H_4-$.

The polyepoxides are novel polymers and the invention likewise relates to these.

The polyesters can contain identical or different structural elements chosen from the group of structural elements of the formulae (f), (g), (h) and (i), where at least the structural elements of the formulae [sic] (f) or (g) or both must be present



in which R_{09} and R_{010} independently of one another are a divalent radical of a strained cycloolefin or a divalent radical with a strained cycloolefin, R_{011} is a divalent radical of a dicarboxylic acid reduced by the carboxyl groups and R_{012} is a divalent radical of a diol reduced by the hydroxyl group.

The polymer can contain in each case up to 100 mol % of the structural elements of the formulae (f) and (g), per mole of the polymer. If structural elements of the formulae (f) and (h) or (g) and (i) are present, advantageous mixing ratios are 5 to 95, preferably 10 to 80 mol % of structural elements of the formulae (f) and (h) and 95 to 5, preferably 90 to 20 mol % of the structural elements of the formulae (g) and (i).

The polyesters are preferably linear and accessible either by esterification or transesterification processes on the corresponding monomers, or by Diels-Alder reaction of polyesters with olefinically unsaturated dicarboxylic acid and/or diol structural units with open-chain or, preferably, cyclic 1,3-dienes to form strained cycloolefin rings. Mono-, di- or tricyclic dienes are preferably used for the Diels-Alder reaction.

R_{09} and R_{010} can be, for example, mono- or diolefinically unsaturated C_5 - C_8 cycloalkylene or fused polycyclic, preferably bi- or tricyclic C_7 - C_{10} cycloalkylene. Examples are cyclopentenylene, cycloheptenylene, cyclooctenylene and, in particular, norbornene radicals of the formulae (nr₁) and (nr₂).

R_{011} is preferably C_2 - C_{18} -, preferably C_2 - C_{12} alkylene or -alkenylene, C_3 - C_{12} -, preferably C_5 - C_8 cycloalkylene or -cycloalkenylene, C_5 - C_8 cycloalkylene- CH_2 -, - CH_2 -(C_5 - C_8 cycloalkylene)- CH_2 -, C_6 - C_{10} arylene, bisphenylene, benzylene, xylylene or - C_6H_4 - X_{01} - C_6H_4 -, where X_{01} is O, S, SO, SO₂, CO, CO₂, NH, N(C_1 - C_4 alkyl), alkylidene having 1 to 18, preferably 1 to 12 C atoms, or C_3 - C_7 cycloalkylidene. Some examples are ethylene, propylene, butylene, hexylene, cyclopentenylene, cyclohexylene, cyclohexylene- CH_2 -, - CH_2 -cyclohexylene- CH_2 -, phenylene, naphthylene, - C_6H_4 - CH_2 - C_6H_4 -, - C_6H_4 - C_6H_4 -, - C_6H_4 -SO₂- C_6H_4 -, - C_6H_4 -CO- C_6H_4 - and - C_6H_4 -O- C_6H_4 -. R_{011} is preferably C_2 - C_6 alkylene, cyclohexylene or o-, m- or p-phenylene.

R_{012} can preferably be C_2 - C_{18} , preferably C_2 - C_{12} alkylene, polyoxaalkylene having 2 to 50, preferably 2 to 10 oxaalkylene units and 2 to 6, preferably 2 to 4 C atoms in the oxyalkylene, C_3 - C_{12} -, preferably C_5 - C_8 cycloalkylene, C_5 - C_8 -cycloalkylene- CH_2 -,

-CH₂-(C₅-C₈cycloalkylene)-CH₂-, C₆-C₁₄arylene, bisphenylene, benzylene, xylylene or -C₆H₄-X₀₁-C₆H₄-, where X₀₁ is O, S, SO, SO₂, CO, CO₂, NH, N(C₁-C₄alkyl), alkylidene having 1 to 18, preferably 1 to 12 C atoms, or C₅-C₇cycloalkylidene. Some examples are ethylene, propylene, butylene, hexylene, di-, tri- and tetraoxaethylene, cyclopentylene, cyclohexylene, cyclohexylene-CH₂-, -CH₂-cyclohexylene-CH₂-, phenylene, -C₆H₄-CH₂-C₆H₄-, -C₆H₄-CH(CH₃)-C₆H₄-, -C₆H₄-C(CH₃)₂-C₆H₄-, -C₆H₄-C₆H₁₀-C₆H₄- and -C₆H₄-O-C₆H₄-. R₀₁₂ is particularly preferably C₂-C₆alkylene, which, in particular, is linear.

The polyesters are novel polymers and the invention likewise relates to these.

The polyamides can contain identical or different structural elements chosen from the group of structural elements of the formulae (j), (k), (l) and (m), where at least the structural elements of the formulae [sic] (j) or (k) or both must be present



in which R₀₁₃ and R₀₁₄ independently of one another are a divalent radical of a strained cycloolefin or a divalent radical with a strained cycloolefin, R₀₁₅ is a divalent radical of a dicarboxylic acid reduced by the carboxyl groups and R₀₁₆ is a divalent radical of a diamine reduced by the amino groups.

The polymer can contain in each case up to 100 mol % of the structural elements of the formulae (j) and (k) per mole of the polymer. If the structural elements of the formulae (j) and (l) or (k) and (m) are present, advantageous mixing ratios are 5 to 95, preferably 10 to 80 mol % of structural elements of the formulae (j) and (l) and

95 to 5, preferably 90 to 20 mol % of the structural elements of the formulae (k) and (m).

The polyamides are preferably linear and accessible either by amidation or transamidation processes on the corresponding monomers, or by Diels-Alder reaction of polyamides with olefinically unsaturated dicarboxylic acid and/or diamine structural units with open-chain or preferably cyclic 1,3-dienes to form strained cycloolefin rings. Mono-, di- or tricyclic dienes are preferably used for the Diels-Alder reaction.

R_{013} and R_{014} can be, for example, mono- or diolefinically unsaturated C_5 - C_8 cycloalkylene or fused polycyclic, preferably bi- or tricyclic C_7 - C_{18} cycloalkylene. Examples are cyclopentenylene, cycloheptenylene, cyclooctenylene and, in particular, norbornene radicals of the formulae (nr₁) and (nr₂).

R_{015} is preferably C_2 - C_{18} -, preferably C_2 - C_{12} alkylene or -alkenylene, C_3 - C_{12} -, preferably C_5 - C_8 cycloalkylene or -cycloalkenylene, C_5 - C_8 cycloalkylene- CH_2 -, $-CH_2$ -(C_5 - C_8 cycloalkylene)- CH_2 -, C_6 - C_{18} arylene, bisphenylene, benzylene, xylylene or $-C_6H_4-X_{01}-C_6H_4-$, where X_{01} is O, S, SO, SO₂, CO, CO₂, NH, N(C_1 - C_4 alkyl) or alkylidene having 1 to 18, preferably 1 to 12 C atoms, or C_5 - C_7 cycloalkylidene. Some examples are ethylene, propylene, butylene, hexylene, cyclopentenylene, cyclohexylene, cyclohexylene- CH_2 -, $-CH_2$ -cyclohexylene- CH_2 -, phenylene, naphthylene, $-C_6H_4-CH_2-C_6H_4-$, $-C_6H_4-C_6H_4-$, $-C_6H_4-SO_2-C_6H_4-$, $-C_6H_4-CO-C_6H_4-$ and $-C_6H_4-O-C_6H_4-$. R_{015} is preferably C_2 - C_8 alkylene, cyclohexylene or o-, m- or p-phenylene.

R_{016} can preferably be C_2 - C_{18} -, preferably C_2 - C_{12} alkylene, C_3 - C_{12} -, preferably C_5 - C_8 cycloalkylene, C_5 - C_8 cycloalkylene- CH_2 -, $-CH_2$ -(C_5 - C_8 cycloalkylene)- CH_2 -, C_6 - C_{14} arylene, bisphenylene, benzylene, xylylene or $-C_6H_4-X_{01}-C_6H_4-$, where X_{01} is O, S, SO, SO₂, CO, CO₂, NH, N(C_1 - C_4 alkyl) or alkylidene having 1 to 18, preferably 1 to 12 C atoms, or C_5 - C_7 cycloalkylidene. Some examples are ethylene, propylene, butylene, hexylene, di-, tri- and tetraoxaethylene, cyclopentenylene,

cyclohexylene, cyclohexylene-CH₂-, -CH₂-cyclohexylene-CH₂-, phenylene, -C₆H₄-CH(CH₃)-C₆H₄-, C₆H₄-O-C₆H₄-, -C₆H₄-CH₂-C₆H₄-, -C₆H₄-C(CH₃)₂-C₆H₄- and -C₆H₄-C₆H₁₀-C₆H₄-. R₀₁₈ is particularly preferably C₂-C₆alkylene, which, in particular, is linear.

The polyamides can also contain structural units of 4 to 12-membered lactams, for example ε-caprolactam.

The polyamides are novel polymers and the invention likewise relates to these.

Polyester-amides are copolymers with diamines and diols which can contain, for example, the structural elements mentioned above for the polyesters and polyamides, in any combination.

The polyester-amides are novel polymers and the invention likewise relates to them.

The polyurethanes and polyureas can contain identical or different structural elements chosen from the group of structural elements of the formulae (n), (o), (p) and (q), where at least the structural elements of the formulae [sic] (n) or (o) or both must be present



in which R₀₁₇ and R₀₁₈ independently of one another are a divalent radical of a strained cycloolefin or a divalent radical with a strained cycloolefin, R₀₁₉ is a divalent radical of a diisocyanate reduced by the cyanate groups and R₀₂₀ is a

divalent radical of a diamine or of a diol reduced by the amino or hydroxyl groups, and the X_{02} independently of one another are -O- or -NH-.

The polyurethanes and -ureas are preferably linear and accessible either by addition polymerization of the corresponding monomers or by Diels-Alder reaction of polyurethanes or polyureas with olefinically unsaturated diisocyanate, diol- and/or diamine structural units with open-chain or preferably cyclic 1,3-dienes to form strained cycloolefin rings. Mono-, di- or tricyclic dienes are preferably used for the Diels-Alder reaction.

The polymer can contain in each case up to 100 mol % of the structural elements of the formulae (n) and (o) per mole of the polymer. If the structural elements of the formulae (n) and (o) or (p) and (q) are present, advantageous mixing ratios are 5 to 95, preferably 10 to 80 mol % of structural elements of the formulae (n) and (p) and 95 to 5, preferably 90 to 20 mol % of the structural elements of the formulae (o) and (q).

R_{017} and R_{018} can be, for example, mono- or diolefinically unsaturated C_5 - C_8 cycloalkylene or fused polycyclic, preferably bi- or tricyclic C_7 - C_{18} cycloalkylene. Examples are cyclopentenylene, cycloheptenylene, cyclooctenylene and, in particular, norbornene radicals of the formulae (nr_1) and (nr_2) .

R_{019} is preferably C_2 - C_{18} -, preferably C_2 - C_{12} alkylene or -alkenylene, C_3 - C_{12} -, preferably C_5 - C_8 cycloalkylene or -cycloalkenylene, C_5 - C_8 cycloalkylene- CH_2 -, - CH_2 -(C_5 - C_8 cycloalkylene)- CH_2 -, C_6 - C_{18} arylene, bisphenylene, benzylene, xylylene or - C_6H_4 - X_{01} - C_6H_4 -, where X_{01} is O, S, SO, SO_2 , CO, CO_2 , NH, $N(C_1$ - C_4 alkyl) or alkylidene having 1 to 18, preferably 1 to 12 C atoms, or C_5 - C_7 cycloalkylidene. Some examples are ethylene, propylene, butylene, hexylene, cyclopentenylene, cyclohexylene, isophoronylene, cyclohexylene- CH_2 -, - CH_2 -cyclohexylene- CH_2 -, phenylene, naphthylene, toluylene, xylylene, - C_6H_4 - C_6H_4 -, - C_6H_4 - CH_2 - C_6H_4 -, - C_6H_4 - SO_2 - C_6H_4 -, - C_6H_4 -CO- C_6H_4 - and - C_6H_4 -O- C_6H_4 -.

R_{020} can preferably be C_2-C_{18} , preferably C_2-C_{12} alkylene, polyoxaalkylene having 2 to 50, preferably 2 to 10 oxaalkylene units and 2 to 6, preferably 2 to 4 C atoms in the oxyalkylene, C_3-C_{12} , preferably C_3-C_6 cycloalkylene, C_5-C_6 cycloalkylene- CH_2 -, $-CH_2-(C_5-C_6$ cycloalkylene)- CH_2 -, C_6-C_{14} arylene, bisphenylene, benzylene, xylylene, $-C_6H_4-X_{01}-C_6H_4-$, where X_{01} is O, S, SO, SO_2 , CO, CO_2 , NH, $N(C_1-C_4$ alkyl) or alkylidene having 1 to 18, preferably 1 to 12 C atoms, or C_3-C_7 cycloalkylidene. Some examples are ethylene, propylene, butylene, hexylene, di-, tri- and tetraoxaethylene, cyclopentylene, cyclohexylene, cyclohexylene- CH_2 -, $-CH_2$ -cyclohexylene- CH_2 -, phenylene, $-C_6H_4-CH_2-C_6H_4-$, $-C_6H_4-CH(CH_3)-C_6H_4-$, $-C_6H_4-C(CH_3)_2-C_6H_4-$, $-C_6H_4-C_6H_{10}-C_6H_4-$ and $-C_6H_4-O-C_6H_4-$. R_{020} is particularly preferably C_2-C_6 alkylene which, in particular, is linear.


The polyurethanes and polyureas are novel polymers and the invention likewise relates to these.

Polymers with a carbon backbone, of which various embodiments may be mentioned, are preferred according to the invention.

One embodiment can be essentially or completely linear metathesis polymers of fused at least bicyclic cycloaliphatic dienes which contain two olefinic double bonds in different rings. The individual rings can contain 3 to 12, preferably 5 to 8 ring C atoms. The polymers contain, for example, recurring structural elements of the formula (r)




in which R_{021} is C_2-C_{10} , preferably C_3-C_6 alkylene, onto which a cycloalkenylene having a total of 5 to 8 C atoms is fused directly or via another fused-on cycloalkylene having 5 to 8 C atoms. Preferred examples are linear polynorbornadiene with recurring structural elements of the formula (r')



(r').


or linear polydicyclopentadiene with recurring structural elements of the formula (r')



(r'').

or copolymers with these two recurring structural elements.

Polymers which are furthermore suitable are linear copolymers with a recurring structural element of the formula (r), preferably in each case one or both the above structural elements (r') and (r'') and structural elements of the formula (r''')



(r''')

of a strained cycloolefin, in which

Q_3 is a linear or branched C_1 - C_{18} alkylene which is unsubstituted or substituted by halogen, = O, -CN, -NO₂, -COOM, -SO₃M, -PO₃M, -COO(M₁)_{1/2}, -SO₃(M₁)_{1/2}, -PO₃(M₁)_{1/2}, C_1 - C_{20} alkyl, $R_1R_2R_3Si(O)_u$, C_1 - C_{20} hydroxyalkyl, C_1 - C_{20} haloalkyl, C_1 - C_6 cianoalkyl, C_3 - C_6 cycloalkyl, C_6 - C_{16} aryl, C_7 - C_{16} aralkyl, C_3 - C_6 heterocycloalkyl, C_3 - C_{16} heteroaryl, C_4 - C_{16} heteroaralkyl or R_4 -X-; or in which two adjacent C atoms are substituted by -CO-O-CO- or -CO-NR₅-CO-; or in which, possibly at adjacent carbon atoms, an alicyclic, aromatic or heteroaromatic ring is fused on which is unsubstituted or is substituted by halogen, -CN, -NO₂, $R_6R_7R_8Si(O)_u$, -COOM, -SO₃M, -PO₃M, -COO(M₁)_{1/2}, -SO₃(M₁)_{1/2}, -PO₃(M₁)_{1/2}, C_1 - C_{20} alkyl, C_1 - C_{20} haloalkyl, C_1 - C_{20} hydroxyalkyl.

C_1-C_6 cyanoalkyl, C_3-C_6 cycloalkyl, C_6-C_{16} aryl, C_7-C_{16} aralkyl,
 C_3-C_6 heterocycloalkyl, C_3-C_{16} heteroaryl, C_4-C_{16} heteroaralkyl or $R_{13}-X_1$;
 X and X_1 independently of one another are -O-, -S-, -CO-, -SO-, -SO₂-,
 -O-C(O)-, -C(O)-O-, -C(O)-NR₅-, -NR₁₀-C(O)-, -SO₂-O- or -O-SO₂-;
 R_1 , R_2 and R_3 independently of one another are C_1-C_{12} alkyl, C_1-C_{12} perfluoro-
 alkyl, phenyl or benzyl;
 R_4 and R_{13} independently are C_1-C_{20} alkyl, C_1-C_{20} haloalkyl, C_1-C_{20} hydroxyalkyl,
 C_3-C_6 cycloalkyl, C_6-C_{16} aryl, C_7-C_{16} aralkyl;
 R_5 and R_{10} independently of one another are hydrogen, C_1-C_{12} alkyl, phenyl or
 benzyl, the alkyl groups in turn being unsubstituted or substituted by
 C_1-C_{12} alkoxy or C_3-C_6 cycloalkyl;
 R_6 , R_7 and R_8 independently of one another are C_1-C_{12} alkyl, C_1-C_{12} perfluoro-
 alkyl, phenyl or benzyl;
 M is an alkali metal and M_1 is an alkaline earth metal; and
 u is 0 or 1;
 the alicyclic ring formed with Q_3 possibly containing further non-aromatic double
 bonds;
 Q_2 is hydrogen, C_1-C_{20} alkyl, C_1-C_{20} haloalkyl, C_1-C_{12} alkoxy, halogen, -CN,
 $R_{11}-X_2$;
 R_{11} is C_1-C_{20} alkyl, C_1-C_{20} haloalkyl, C_1-C_{20} hydroxyalkyl, C_3-C_6 cycloalkyl,
 C_6-C_{16} aryl or C_7-C_{16} aralkyl;
 X_2 is -C(O)-O- or -C(O)-NR₁₂;
 R_{12} is hydrogen, C_1-C_{12} alkyl, phenyl or benzyl;
 the abovementioned cycloalkyl, heterocycloalkyl, aryl, heteroaryl, aralkyl and
 heteroaralkyl groups being unsubstituted or substituted by C_1-C_{12} alkyl,
 C_1-C_{12} alkoxy, -NO₂, -CN or halogen, and the heteroatoms of the abovementioned
 heterocycloalkyl, heteroaryl and heteroaralkyl groups being selected from the
 group -O-, -S-, -NR₅- and -N=; and
 R_9 being hydrogen, C_1-C_{12} alkyl, phenyl or benzyl. Q_2 is with particular preference
 H.

In another embodiment, the polymers with a carbon backbone are copolymers of
 strained cycloolefins with fused at least bicyclic cycloaliphatic dienes which contain

at least two olefinic double bonds in different rings, and ethylenically unsaturated comonomers. The individual rings can contain 3 to 12, preferably 5 to 8 ring C atoms. The polymers contain, for example, recurring structural elements of the formula (r) and of the formula (s)



in which

- R_{021} is C_2-C_{10} , preferably C_2-C_4 alkylene, onto which an alkenylene having 2 to 6, preferably 2 to 5 C atoms is bonded directly or via a fused-on cycloalkylene ring having 5 to 8 C atoms;
- R_{022} is H, F, C_1-C_{12} alkyl, $-COOH$, $-C(O)O-C_1-C_{12}$ alkyl, $-C(O)-NH-C_1-C_{12}$ alkyl or $-C(O)-NH_2$, preferably H, F, C_1-C_4 alkyl, $-COOH$ or $-C(O)-C_1-C_8$ alkyl;
- R_{023} is H, F, Cl, CN or C_1-C_{12} alkyl, preferably H, F, Cl or C_1-C_4 alkyl;
- R_{024} is H, F, Cl, CN, OH, C_1-C_{12} alkyl, C_1-C_{12} alkoxy, phenyl which is unsubstituted or substituted by OH, Cl, Br, C_1-C_4 alkyl, C_1-C_4 alkoxy, $-C(O)OC_1-C_{12}$ alkyl, $-C(O)-NH_2$, $-SO_3H$, $-COOH$, $C(O)-NH-C_1-C_{12}$ alkyl or $-SO_3-C_1-C_{12}$ alkyl, or is $-C(O)OH$, $-C(O)O-C_2-C_{12}$ hydroxyalkyl, $-C(O)O-C_1-C_{12}$ alkyl, $-C(O)-NH_2$ or $-C(O)-NH-C_1-C_{12}$ alkyl; and is preferably H, F, Cl, CN, OH, C_1-C_4 alkyl, C_1-C_4 alkoxy, phenyl which is unsubstituted or substituted by OH, Cl, Br, C_1-C_4 alkyl, C_1-C_4 alkoxy, $-COOH$, $-C(O)OC_1-C_{14}$ alkyl, $-C(O)-NH_2$, $C(O)-NH-C_1-C_4$ alkyl, $-SO_3H$ or $-SO_3-C_1-C_4$ alkyl, or $-COOH$, $-C(O)O-C_1-C_4$ alkyl, $-C(O)O-C_2-C_6$ hydroxyalkyl, $-C(O)-NH-C_1-C_4$ alkyl or $-C(O)-NH_2$; and
- R_{025} is H, F or C_1-C_{12} alkyl, preferably H or F.

Preferred examples of recurring structural elements of the formula (r) are

elements of the formula (r') and (r'')

The polymers can contain the structural elements of the formula (r) in an amount of 5 to 100, preferably 10 to 80, and particularly preferably 20 to 60 mol %, per mole of polymer.

The polymers, with the exception of the copolymers of norbornene and ethylene alone or together with other unsubstituted olefins, are novel and the invention likewise relates to these.

In another embodiment, the polymers with a carbon backbone are metathesis polymers of strained cycloolefins with a double bond in the ring, or copolymeric metathesis polymers of strained cycloolefins with a double bond in the ring and olefinically unsaturated comonomers, of which the olefinic double bonds in the polymer backbone are reacted partly or completely with open-chain or cyclic 1,3-dienes having 4 to 12, preferably 5 to 8 C atoms in a Diels-Alder reaction to give cycloalkenylene radicals having 6 to 14, preferably 7 to 12 C atoms. Preferably 5 to 80%, more preferably 5 to 60%, and in particular 10 to 50% of the double bonds are reacted.

In a preferred embodiment, these metathesis polymers contain recurring structural elements of the formula (t)



in which A₁ is mono- or bicyclic C₅-C₉cycloalkenylene.

The structural element of the formula (t) particularly preferably corresponds to norborn-1,2-enylene of the formula (nr₁)



In another preferred embodiment, the metathesis polymer contains recurring structural units of the formula (u)



and recurring structural elements of the formula (w)



in which A_1 , together with the -CH-CH- group, is bicyclic C_5 - C_8 cycloalkenylene, preferably cyclopent-1,2-en-3,5-ylene, and R_{226} is C_1 - C_{12} , preferably C_3 - C_{12} alkylene, and, if desired, recurring structural elements of the formula (s).

The polymer can contain the structural elements of the formula (u) in an amount of 5 to 100, preferably 5 to 80, particularly preferably 5 to 60, and especially preferably 10 to 50 mol %, and the structural elements of the formula (w) in an amount of 95 to 0, preferably 95 to 20, particularly preferably 95 to 40 and especially preferably 90 to 50 mol %, per mole of polymer. They can contain the structural elements of the formula (s) in an amount of 0 to 80, preferably 0 to 60, and particularly preferably 0 to 50 mol %, per mole of a copolymer.

These metathesis polymers are novel and the invention likewise relates to them.

In another embodiment, the polymers with a carbon backbone are homo- and copolymers of 1,3-dienes and, if desired, olefinically unsaturated monomers, of which the olefinic double bonds in the polymer backbone are reacted partly or completely with open-chain or preferably cyclic 1,3-dienes having 4 to 12, preferably 5 to 8 C atoms in a Diels-Alder reaction to give cycloalkenylene radicals having 6 to 14, preferably 7 to 12 C atoms. Preferably 5 to 80%, more preferably 5

to 60%, and in particular 10 to 50% of the double bonds are reacted. Suitable 1,3-dienes are, for example, 1,3-butadiene, isoprene and chloroprene.


In a preferred embodiment, these polymers contain recurring structural elements of the formula (t).

The structural element of the formula (t) particularly preferably corresponds to norborn-1,2-enylene of the formula (nr₃).

In another preferred embodiment, the polymer contains recurring structural units of the formula (y)



and recurring structural elements of the formula (z)



in which A₁, together with the -CH-CR₀₂₇ group, is bicyclic C₅-C₆cycloalkenylenes, preferably cyclopent-1,2-en-3,5-ylene, and R₀₂₇ is H, Cl or C₁-C₁₂-, preferably C₁-C₆alkyl,

and, if desired, recurring structural elements of the formula (s).

The polymer can contain the structural elements of the formula (y) in an amount of 5 to 100, preferably 5 to 80, particularly preferably 5 to 60, and especially preferably 10 to 50 mol %, and the structural elements of the formula (z) in an amount of 95 to 0, preferably 95 to 20, particularly preferably 95 to 40, and especially preferably 90 to 50 mol %, per mole of polymer. It can contain the structural elements of the formula (s) in an amount of 0 to 80, preferably 0 to 60, and particularly preferably 0 to 50 mol %, per mole of a copolymer.

These polymers are novel and the invention likewise relates to them.

Polymers which are built up only from carbon and hydrogen are particularly preferred.

The processes for the preparation of the abovementioned polymers are known or analogous to known processes. The starting monomers and polymers are likewise known and are in some cases commercially obtainable or can be prepared by analogous processes. Diels-Alder reactions are advantageously carried out in solvents and expediently under increased pressure. Metathesis copolymers and processes for their preparation are described, for example, in US 5 215 798. These polymers or metathesis polymers of strained cycloolefins can also be prepared with the catalysts described below. Diels-Alder reactions can be carried out analogously to the process described in EP 287 762.

The choice of the polymers to be used according to the invention depends chiefly on the intended use and the desired properties. The wide selection by modifications of the polymers allows tailor-made polymers to be provided for the most diverse uses. A further modification possibility results from the concomitant use of strained cycloolefins which are capable of metathesis polymerization, which means that, overall, adaptations specific to desired uses can be carried out.

A very large number of strained cycloolefins which the composition according to the invention can comprise as comonomers are known.

The cyclic olefins can be monocyclic or polycyclic fused and/or bridged ring systems, for example with two to four rings, which are unsubstituted or substituted and can contain heteroatoms, for example O, S, N or Si, in one or more rings and/or fused aromatic or heteroaromatic rings, for example o-phenylene, o-naphthylene, o-pyridinylene or o-pyrimidinylene. The individual cyclic rings can contain 3 to 16, preferably 3 to 12, and particularly preferably 3 to 8 ring members. The cyclic olefins can contain further non-aromatic double bonds, preferably 2 to 4

those which are inert, that is to say do not impair the chemical stability and the heat stability of the catalysts. The cycloolefins are strained rings or ring systems.

If the cyclic olefins contain more than one double bond, for example 2 to 4 double bonds, crosslinked polymers can also be formed, depending on the reaction conditions, the monomer chosen and the amount of catalyst.

Fused-on alicyclic rings contain preferably 3 to 8, particularly preferably 4 to 7, and especially preferably 5 or 6 ring C atoms.

In a preferred embodiment, the comonomeric strained cycloolefins correspond to the formula I



in which

Q_1 is a radical having at least one carbon atom which, together with the $-\text{CH}=\text{CQ}_2-$ group, forms an at least 3-membered alicyclic ring which may contain one or more heteroatoms chosen from the group consisting of silicon, phosphorus, oxygen, nitrogen or sulfur; and which is unsubstituted or substituted by halogen, $=\text{O}$, $-\text{CN}$, $-\text{NO}_2$, $\text{R}_1\text{R}_2\text{R}_3\text{Si}-(\text{O})_n-$, $-\text{COOM}$, $-\text{SO}_3\text{M}$, $-\text{PO}_3\text{M}$, $-\text{COO}(\text{M}_1)_{1/2}$, $-\text{SO}_3(\text{M}_1)_{1/2}$, $-\text{PO}_3(\text{M}_1)_{1/2}$, C_1-C_{20} alkyl, C_1-C_{20} hydroxyalkyl, C_1-C_{20} haloalkyl, C_1-C_6 cyanoalkyl, C_3-C_8 cycloalkyl, C_6-C_{18} aryl, C_7-C_{18} aralkyl, C_3-C_8 heterocycloalkyl, C_3-C_{18} heteroaryl, C_4-C_{18} heteroaralkyl or $\text{R}_4-\text{X}-$; or in which two adjacent C atoms are substituted by $-\text{CO}-\text{O}-\text{CO}-$ or $-\text{CO}-\text{NR}_5-\text{CO}-$; or in which an alicyclic, aromatic or heteroaromatic ring which is unsubstituted or substituted by halogen, $-\text{CN}$, $-\text{NO}_2$, $\text{R}_6\text{R}_7\text{R}_8\text{Si}-(\text{O})_n-$, $-\text{COOM}$, $-\text{SO}_3\text{M}$, $-\text{PO}_3\text{M}$, $-\text{COO}(\text{M}_1)_{1/2}$, $-\text{SO}_3(\text{M}_1)_{1/2}$, $-\text{PO}_3(\text{M}_1)_{1/2}$, C_1-C_{20} alkyl, C_1-C_{20} haloalkyl, C_1-

C_{1-6} alkyl, C_3-C_6 heterocycloalkyl, C_3-C_{16} heteroaryl, C_4-C_{16} heteroaralkyl or $R_{13}-X_1$ may be fused onto adjacent carbon atoms of the alicyclic ring;
 X and X_1 independently of one another are -O-, -S-, -CO-, -SO-, -SO₂-, -O-C(O)-, -C(O)-O-, -C(O)-NR₅-, -NR₁₀-C(O)-, -SO₂-O- or -O-SO₂-;
 R_1 , R_2 and R_3 independently of one another are C_1-C_{12} alkyl, C_1-C_{12} perfluoroalkyl, phenyl or benzyl;
 R_4 and R_{13} independently are C_1-C_{20} alkyl, C_1-C_{20} haloalkyl, C_1-C_{20} hydroxyalkyl, C_3-C_8 cycloalkyl, C_6-C_{16} aryl, C_7-C_{16} aralkyl;
 R_5 and R_{10} independently of one another are hydrogen, C_1-C_{12} alkyl, phenyl or benzyl, where the alkyl groups in their turn are unsubstituted or substituted by C_1-C_{12} alkoxy or C_3-C_8 cycloalkyl;
 R_6 , R_7 and R_8 independently of one another are C_1-C_{12} alkyl, C_1-C_{12} perfluoroalkyl, phenyl or benzyl;
 M is an alkali metal and M_1 is an alkaline earth metal; and
 u is 0 or 1;
 where the alicyclic ring formed with Q_1 may contain further non-aromatic double bonds;
 Q_2 is hydrogen, C_1-C_{20} alkyl, C_1-C_{20} haloalkyl, C_1-C_{12} alkoxy, halogen, -CN, $R_{11}-X_2$;
 R_{11} is C_1-C_{20} alkyl, C_1-C_{20} haloalkyl, C_1-C_{20} hydroxyalkyl, C_3-C_8 cycloalkyl, C_6-C_{16} aryl or C_7-C_{16} aralkyl;
 X_2 is -C(O)-O- or -C(O)-NR₁₂;
 R_{12} is hydrogen, C_1-C_{12} alkyl, phenyl or benzyl;
 where the abovementioned cycloalkyl, heterocycloalkyl, aryl, heteroaryl, aralkyl and heteroaralkyl groups are unsubstituted or substituted by C_1-C_{12} alkyl, C_1-C_{12} alkoxy, -NO₂, -CN or halogen and where the heteroatoms of the abovementioned heterocycloalkyl, heteroaryl and heteroaralkyl groups are chosen from the group consisting of -O-, -S-, -NR₉- and -N=; and
 R_9 is hydrogen, C_1-C_{12} alkyl, phenyl or benzyl.

Fused-on alicyclic rings preferably contain 3 to 8, particularly preferably 4 to 7, and especially preferably 5 or 6 ring C atoms.

If an asymmetric centre is present in the compounds of the formula I, this means that the compounds can occur in optically isomeric forms. Some compounds of the formula I can occur in tautomeric forms (for example keto-enol tautomerism). If an aliphatic C=C double bond is present, geometric isomerism (E form or Z form) can also occur. Exo-endo configurations are furthermore also possible. Formula I thus includes all the possible stereoisomers which are present in the form of enantiomers, tautomers, diastereomers, E/Z isomers or mixtures thereof.

In the definitions of the substituents, the alkyl, alkenyl and alkynyl groups can be straight-chain or branched. The same also applies to the alkyl or each alkyl part of alkoxy-, alkylthio-, alkoxycarbonyl- and of other alkyl-containing groups. These alkyl groups preferably contain 1 to 12, more preferably 1 to 8, and particularly preferably 1 to 4 C atoms. These alkenyl and alkynyl groups preferably contain 2 to 12, more preferably 2 to 8, and particularly preferably 2 to 4 C atoms.

Alkyl includes, for example, methyl, ethyl, isopropyl, n-propyl, n-butyl, iso-butyl, sec-butyl, tert-butyl and the various isomeric pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl, nonadecyl and eicosyl radicals.

Hydroxyalkyl includes, for example, hydroxymethyl, hydroxyethyl, 1-hydroxyisopropyl, 1-hydroxy-n-propyl, 2-hydroxy-n-butyl, 1-hydroxy-iso-butyl, 1-hydroxy-sec-butyl, 1-hydroxy-tert-butyl and the various isomeric pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl, nonadecyl and eicosyl radicals.

Haloalkyl includes, for example, fluoromethyl, difluoromethyl, trifluoromethyl, chloromethyl, dichloromethyl, trichloromethyl, 2,2,2-trifluoroethyl, 2-fluoro thyl, 2-chloro thyl, 2,2,2-trichloroethyl and halogenated, in particular fluorinated or chlorinated, alkanes, for example the isopropyl, n-propyl, n-butyl, iso-butyl, sec-butyl, tert-butyl, and the various isomeric pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl, nonadecyl and eicosyl radicals.

Alkenyl includes, for example, propenyl, isopropenyl, 2-butenyl, 3-butenyl, isobutenyl, n-penta-2,4-dienyl, 3-methyl-but-2-enyl, n-oct-2-enyl, n-dodec-2-enyl, iso-dodecenyl, n-octadec-2-enyl, n-octadec-4-enyl.

Cycloalkyl is preferably C₃-C₈cycloalkyl, in particular C₃- or C₆cycloalkyl. Some example are cyclopropyl, dimethylcyclopropyl, cyclobutyl, cyclopentyl, methylcyclopentyl, cyclohexyl, cycloheptyl and cyclooctyl.

Cyanoalkyl includes, for example, cyanomethyl (methylnitrile [sic]), cyanoethyl (ethylnitrile [sic]), 1-cyanoisopropyl, 1-cyano-n-propyl, 2-cyano-n-butyl, 1-cyano-iso-butyl, 1-cyano-sec-butyl, 1-cyano-tert-butyl and the various isomeric cyanopentyl and -hexyl radicals.

Aralkyl preferably contains 7 to 12 C atoms, and particularly preferably 7 to 10 C atoms. It can be, for example, benzyl, phenethyl, 3-phenylpropyl, α -methylbenzyl, phenbutyl or α,α -dimethylbenzyl.

Aryl preferably contains 6 to 10 C atoms. It can be, for example, phenyl, pentalene, indene, naphthalene, azulene or anthracene.

Heteroaryl preferably contains 4 or 5 C atoms and one or two heteroatoms from the group consisting of O, S and N. It can be, for example, pyrrole, furan, thiophene, oxazole, thiazole, pyridine, pyrazine, pyrimidine, pyridazine, indole, purin or quinoline.

Heterocycloalkyl preferably contains 4 or 5 C atoms and one or two heteroatoms from the group consisting of O, S and N. It can be, for example, oxirane, azirine, 1,2-oxathiolane, pyrazoline, pyrrolidine, piperidine, piperazine, morpholin, tetrahydrofuran or tetrahydrothiophen.

Alkoxy is, for example, methoxy, thoxy, propyloxy, i-propyloxy, n-butyloxy, i-butyloxy, sec-butyloxy and t-butyloxy.

Alkali metal in the context of the present invention is to be understood as meaning lithium, sodium, potassium, rubidium and caesium, in particular lithium, sodium and potassium.

Alkaline earth metal in the context of the present invention is to be understood as meaning beryllium, magnesium, calcium, strontium and barium, in particular magnesium and calcium.

In the above definitions, halogen is to be understood as meaning fluorine, chlorine, bromine and iodine, preferably fluorine, chlorine and bromine.

Compounds of the formula I which are particularly suitable for the composition according to the invention are those in which Q_2 is hydrogen.

Compounds of the formula I which are furthermore preferred for the polymerization are those in which the alicyclic ring which Q_1 forms together with the $-\text{CH}=\text{CQ}_2-$ group contains 3 to 16, more preferably 3 to 12, and particularly preferably 3 to 8 ring atoms, it being possible for this to be a monocyclic, bicyclic, tricyclic or tetracyclic ring system.

The composition according to the invention particularly advantageously comprises compounds of the formula I in which

Q_1 is a radical having at least one carbon atom which, together with the $-\text{CH}=\text{CQ}_2-$ group, forms a 3- to 20-membered alicyclic ring which may contain one or more heteroatoms chosen from the group consisting of silicon, oxygen, nitrogen and sulfur; and which is unsubstituted or substituted by halogen, $=\text{O}$, $-\text{CN}$, $-\text{NO}_2$, $\text{R}_1\text{R}_2\text{R}_3\text{Si}(\text{O})_n-$, $-\text{COOM}$, $-\text{SO}_3\text{M}$, $-\text{PO}_3\text{M}$, $-\text{COO}(\text{M}_1)_{1/2}$, $-\text{SO}_3(\text{M}_1)_{1/2}$, $-\text{PO}_3(\text{M}_1)_{1/2}$, C_1-C_{12} alkyl, C_1-C_{12} haloalkyl, C_1-C_{12} hydroxyalkyl, C_1-C_4 cyanoalkyl, C_3-C_8 cycloalkyl, C_6-C_{12} aryl, C_7-C_{12} aralkyl, C_3-C_8 heterocycloalkyl, C_3-C_{12} heteroaryl, C_4-C_{12} heteroaralkyl or $\text{R}_4-\text{X}-$; or in which two adjacent C atoms in this radical Q_1 are substituted by $-\text{CO}-\text{O}-\text{CO}-$ or $-\text{CO}-\text{NR}_5-\text{CO}-$; or in which an alicyclic, aromatic or heteroaromatic ring which is unsubstituted or substituted by halogen,

-CN, -NO₂, R₆R₇R₈Si-, -COOM, -SO₃M, -PO₃M,
 -COO(M₁)_{1/2}, -SO₃(M₁)_{1/2}, -PO₃(M₁)_{1/2}, C₁-C₁₂alkyl, C₁-C₁₂haloalkyl,
 C₁-C₁₂hydroxyalkyl, C₁-C₄cyanoalkyl, C₃-C₆cycloalkyl, C₆-C₁₂aryl,
 C₇-C₁₂aralkyl, C₃-C₆heterocycloalkyl, C₃-C₁₂heteroaryl, C₄-C₁₂hetero-
 aralkyl or R₁₃-X₁- may be fused onto adjacent carbon atoms;

X and X₁ independently of one another are -O-, -S-, -CO-, -SO-, -SO₂-, -O-C(O)-,
 -C(O)-O-, -C(O)-NR₅-, -NR₁₀-C(O)-, -SO₂-O- or -O-SO₂-;

R₁, R₂ and R₃ independently of one another are C₁-C₆alkyl, C₁-C₆perfluoroalkyl,
 phenyl or benzyl;

M is an alkali metal and M₁ is an alkaline earth metal;

R₄ and R₁₃ independently of one another are C₁-C₁₂alkyl, C₁-C₁₂haloalkyl,
 C₁-C₁₂hydroxyalkyl, C₃-C₆cycloalkyl, C₆-C₁₂aryl, C₇-C₁₂aralkyl;

R₅ and R₁₀ independently of one another are hydrogen, C₁-C₆alkyl, phenyl or
 benzyl, where the alkyl groups in their turn are unsubstituted or
 substituted by C₁-C₆alkoxy or C₃-C₆cycloalkyl;

R₆, R₇ and R₈ independently of one another are C₁-C₆alkyl, C₁-C₆perfluoroalkyl,
 phenyl or benzyl;

u is 0 or 1;

where the alicyclic ring formed with Q₁ may contain further non-aromatic double
 bonds;

Q₂ is hydrogen, C₁-C₁₂alkyl, C₁-C₁₂haloalkyl, C₁-C₆alkoxy, halogen, -CN, R₁₁-,
 X₂-;

R₁₁ is C₁-C₁₂alkyl, C₁-C₁₂haloalkyl, C₁-C₁₂hydroxyalkyl, C₃-C₆cycloalkyl,
 C₆-C₁₂aryl or C₇-C₁₂aralkyl;

X₂ is -C(O)-O- or -C(O)-NR₁₂-; and

R₁₂ is hydrogen, C₁-C₆alkyl, phenyl or benzyl;


where the cycloalkyl, heterocycloalkyl, aryl, heteroaryl, aralkyl and heteroaralkyl
 groups are unsubstituted or substituted by C₁-C₆alkyl, C₁-C₆alkoxy, -NO₂,
 -CN or halogen, and where the heteroatoms of the heterocycloalkyl,
 heteroaryl and heteroaralkyl groups are chosen from the group
 consisting of -O-, -S-, -NR₉- and -N=; and

R₉ is hydrogen, C₁-C₆alkyl, phenyl or benzyl.

Compounds of the formula I from this group which are preferred are those in which

- Q_1 is a radical having at least one carbon atom which, together with the $-\text{CH}=\text{CQ}_2-$ group, forms a 3- to 10-membered alicyclic ring which may contain a heteroatom chosen from the group consisting of silicon, oxygen, nitrogen and sulfur and is unsubstituted or substituted by halogen, $-\text{CN}$, $-\text{NO}_2$, $\text{R}_1\text{R}_2\text{R}_3\text{Si}-$, $-\text{COOM}$, $-\text{SO}_3\text{M}$, $-\text{PO}_3\text{M}$, $-\text{COO}(\text{M}_1)_{1/2}$, $-\text{SO}_3(\text{M}_1)_{1/2}$, $-\text{PO}_3(\text{M}_1)_{1/2}$, C_1-C_6 alkyl, C_1-C_6 haloalkyl, C_1-C_6 hydroxyalkyl, C_1-C_4 cyanoalkyl, C_3-C_6 cycloalkyl, phenyl, benzyl or $\text{R}_4-\text{X}-$; or in which an alicyclic, aromatic or heteroaromatic ring which is unsubstituted or substituted by halogen, $-\text{CN}$, $-\text{NO}_2$, $\text{R}_6\text{R}_7\text{R}_8\text{Si}-$, $-\text{COOM}$, $-\text{SO}_3\text{M}$, $-\text{PO}_3\text{M}$, $-\text{COO}(\text{M}_1)_{1/2}$, $-\text{SO}_3(\text{M}_1)_{1/2}$, $-\text{PO}_3(\text{M}_1)_{1/2}$, C_1-C_6 alkyl, C_1-C_6 haloalkyl, C_1-C_6 hydroxyalkyl, C_1-C_4 cyanoalkyl, C_3-C_6 cycloalkyl, phenyl, benzyl or $\text{R}_{13}-\text{X}_1-$ may be fused onto adjacent carbon atoms;
- R_1 , R_2 and R_3 independently of one another are C_1-C_4 alkyl, C_1-C_4 perfluoroalkyl, phenyl or benzyl;
- M is an alkali metal and M_1 is an alkaline earth metal;
- R_4 and R_{13} independently of one another are C_1-C_6 alkyl, C_1-C_6 haloalkyl, C_1-C_6 hydroxyalkyl or C_3-C_6 cycloalkyl;
- X and X_1 independently of one another are $-\text{O}-$, $-\text{S}-$, $-\text{CO}-$, $-\text{SO}-$ or $-\text{SO}_2-$;
- R_6 , R_7 and R_8 independently of one another are C_1-C_4 alkyl, C_1-C_4 perfluoroalkyl, phenyl or benzyl;
- and Q_2 is hydrogen.

The composition according to the invention is particularly suitable for the polymerization of norbornene and norbornene derivatives. Of these norbornene derivatives, preferred derivatives are those which either correspond to the formula II



(II).


in which

X_3 is $-\text{CHR}_{16}-$, oxygen or sulfur;

R_{14} and R_{15} independently of one another are hydrogen, $-\text{CN}$, trifluoromethyl, $(\text{CH}_3)_3\text{Si-O-}$, $(\text{CH}_3)_3\text{Si-}$ or $-\text{COOR}_{17}$; and

R_{16} and R_{17} independently of one another are hydrogen, $\text{C}_1\text{-C}_{12}$ alkyl, phenyl or benzyl;

or correspond to the formula III



(III).


in which

X_4 is $-\text{CHR}_{19}-$, oxygen or sulfur;

R_{19} is hydrogen, $\text{C}_1\text{-C}_{12}$ alkyl, phenyl or benzyl; and

R_{18} is hydrogen, $\text{C}_1\text{-C}_6$ alkyl or halogen;

or correspond to the formula IV



(IV).

in which


X_5 is CHR_{22} , oxygen or sulfur;

R_{22} is hydrogen, $\text{C}_1\text{-C}_{12}$ alkyl, phenyl or benzyl;

R_{20} and R_{21} independently of one another are hydrogen, CN , trifluoromethyl, $(\text{CH}_3)_3\text{Si-O-}$, $(\text{CH}_3)_3\text{Si-}$ or $-\text{COOR}_{23}$; and

R_{23} is hydrogen, $\text{C}_1\text{-C}_{12}$ alkyl, phenyl or benzyl;

or correspond to the formula V




(M).

In which

X_6 is $-\text{CHR}_{24}-$, oxygen or sulfur;

R_{24} is hydrogen, C_1 - C_{12} alkyl, phenyl or benzyl;


Y is oxygen or ; and

R_{25} is hydrogen, methyl, ethyl or phenyl.


The following compounds of the formula I are particularly suitable, bi- and polycyclic systems being obtainable by Diels-Alder reactions:




(1).




(2).




(3).




(4).





(5).




(6).




(7).




(9),




(10),




(11),




(12),




(13),




(14),




(15),




(16),




(17),




(18),




(19),




(20),




(21),




(22),




(23),




(24),




(25),




(26),




(27),




(28),



(29),




(30),



(31),



(32),




(33),




(34),




(35),




(36),



(37),



(38),




(39),




(40),




(41),




(42),




(43),




(44),




(45),



(46),




(47) and



(48).

The comonomeric polyfunctional strained cycloolefins can be compounds of the formula (f1)



in which T is the radical of a strained cycloolefin, U is a direct bond or an n-valent bridge group and n is an integer from 2 to 8.

The cyclic olefins can be monocyclic or polycyclic fused and/or bridged ring systems, for example with two to four rings, which are unsubstituted or substituted and can contain heteroatoms, for example O, S, N or Si, in one or more rings and/or fused alicyclic, aromatic or heteroaromatic rings, for example o-cyclopentylene, o-phenylene, o-naphthylene, o-pyridinylene or o-pyrimidinylene. The individual cyclic rings can contain 3 to 16, preferably 3 to 12, and particularly preferably 3 to 8 ring members. The cyclic olefins can contain further non-aromatic double bonds, preferably 2 to 4 such additional double bonds, depending on the ring size. The ring substituents are those which are inert, that is to say which do not impair the chemical stability of the one-component catalysts.

Fused-on alicyclic rings preferably contain 3 to 8, particularly preferably 4 to 7, and especially preferably 5 or 6 ring C atoms.

In a preferred embodiment, the radicals T in formula (f1) correspond to cycloolefin radicals of the formula (f2)




in which Q₁ and Q₂ have the abovementioned meanings, including the preferred meanings.

The position of the double bond in the ring of the formula (f2) with respect to the free bond essentially depends on the ring size and the preparation method for the compounds of the formula I.

The cycloalkenyl radical of the formula (f2) is particularly preferably unsubstituted or substituted by cyclopropenyl, cyclobutenyl, cyclopentenyl, cycloheptenyl, cyclooctenyl, cyclopentadienyl, cyclohexadienyl, cycloheptadienyl, cyclooctadienyl and norbornenyl or norbornenyl derivatives, for example 7-oxa-2,2,2-cycloheptene and the corresponding benzo derivatives. Substituents are preferably C_1 - C_4 alkyl and C_1 - C_4 alkoxy.

Particularly suitable radicals of the formula (f2) are norbornenyl and norbornenyl derivatives. Of these norbornenyl derivatives, particularly preferred derivatives are those which either correspond to the formula (f3)



(f3).


in which

X_3 is $-CHR_{16}$, oxygen or sulfur;

R_{14} and R_{15} independently of one another are hydrogen, $-CN$, trifluoromethyl, $(CH_3)_3Si-O-$, $(CH_3)_3Si-$ or $-COOR_{17}$; and

R_{16} and R_{17} independently of one another are hydrogen, C_1 - C_{12} alkyl, phenyl or benzyl;

or correspond to the formula (f4)



(f4).


in which

X_4 is $-\text{CHR}_{19}-$, oxygen or sulfur;

R_{19} is hydrogen, C_1 - C_{12} alkyl, phenyl or benzyl; and

R_{18} is hydrogen, C_1 - C_6 alkyl or halogen.

The cycloalkenyl radical T in the formula (f1) is particularly preferably norbornenyl of the formula (nr_4)



(nr_4).

In formula (f1), n is preferably an integer from 2 to 6, particularly preferably 2 to 4, and especially preferably 2 or 3.

In formula (t), U is preferably an n-valent bridge group.

Possible divalent bridge groups are, for example, those of the formula (f5)



(f5).

in which

X_5 and X_6 independently of one another are a direct bond, $-\text{O}-$, $-\text{CH}_2-\text{O}-$, $-\text{C}(\text{O})\text{O}-$, $-\text{O}(\text{O})\text{C}-$, $-\text{CH}_2-\text{O}(\text{O})\text{C}-$, $-\text{C}(\text{O})-\text{NR}_{029}-$, $-\text{R}_{029}\text{N}(\text{O})\text{C}-$, $-\text{NH}-\text{C}(\text{O})-\text{NR}_{029}-$, $-\text{O}-\text{C}(\text{O})-\text{NH}-$, $-\text{CH}_2-\text{O}-\text{C}(\text{O})-\text{NH}-$ or $-\text{NH}-\text{C}(\text{O})-\text{O}-$, and

R_{028} is C_2 - C_{18} alkylene, C_5 - C_9 cycloalkylene which is unsubstituted or substituted by C_1 - C_4 alkyl or C_1 - C_4 alkoxy, C_6 - C_{18} arylene or C_7 - C_{19} aralkylene which are unsubstituted or substituted by C_1 - C_4 alkyl or C_1 - C_4 alkoxy, or polyoxaalkylene having 2 to 12 oxaalkylene units and 2 to 6 C atoms in the alkylene, and R_{029} is H or C_1 - C_6 alkyl.

Alkylene R_{028} preferably contains 2 to 12, and particularly preferably 2 to 8 C atoms. The alkylene can be linear or branched. Preferred cycloalkylene is cyclopentylene, and in particular cyclohexylene. Some examples of arylene are

phenylene, naphthylene, biphenylene, biphenylene ether and anthracenylene. An example of aralkylene is benzylene. The polyoxaalkylene preferably contains 2 to 6, and particularly preferably 2 to 4 units, and preferably 2 or 3 C atoms in the alkylene.

In a preferred embodiment, in formula (f5),





a) X_3 and X_6 are a direct bond and R_{028} is C_2 - C_{18} alkylene, more preferably C_2 - C_{12} alkylene, or









b) X_3 and X_6 are $-O-$, $-\text{CH}_2\text{O}-$, $-\text{C}(\text{O})\text{O}-$, $-\text{O}(\text{O})\text{C}-$, $-\text{CH}_2\text{O}(\text{O})\text{C}-$, $-\text{CH}_2\text{O}-\text{C}(\text{O})-\text{NH}-$, $-\text{C}(\text{O})-\text{NR}_{029}-$ or $-\text{O}-\text{C}(\text{O})-\text{NH}-$ and








R_{028} is C_2 - C_{12} alkylene, or phenylene, naphthylene or benzylene which are unsubstituted or substituted by C_1 - C_4 alkyl or C_1 - C_4 alkoxy, or

$-\text{R}_{030}-(\text{O}-\text{R}_{030})_x-\text{OR}_{030}-$, in which x is a number from 2 to 4, and R_{030} is $-C_2$ - C_4 alkylene.

Some examples of compounds of the formula (f5) with a divalent bridge group are







The compounds of the formula (f1) with a bridge group of the formula (f5) which is a pure hydrocarbon bridge are obtainable, for example, by means of a Diels-Alder

reaction of a cyclic diene with a linear or branched aliphatic diene (see also EP 287 762), substance mixtures which are either further processed directly or separated beforehand by means of customary methods often being formed. Compounds of the formula (f1) with a bridge group of the formula (f5) in which X_5 and X_6 are not a direct bond are obtainable from the corresponding halides or dihalides, alcohols or diols, amines or diamines, carboxylic acids or dicarboxylic acids, or isocyanates or diisocyanates, via etherification, esterification or amidation reactions in a manner known per se.

Possible trivalent bridge groups are, for example, those of the formula (f6)



in which

X_5 , X_6 and X_7 are $-O-$, $-CH_2-O-$, $-C(O)O-$, $-O(O)C-$, $-CH_2-O(O)C-$, $-C(O)-NR_{029}-$, $-R_{029}N(O)C-$, $-NH-C(O)-NR_{029}-$, $-O-C(O)-NH-$, $-CH_2-O-C(O)-NH-$ or $-NH-C(O)-O-$, and






R_{001} is a trivalent aliphatic hydrocarbon radical having 3 to 20, preferably 3 to 12 C atoms, a trivalent cycloaliphatic radical which has 3 to 8, preferably 5 or 6 ring C atoms and is unsubstituted or substituted by C_1-C_4 alkyl or C_1-C_4 alkoxy, or a trivalent aromatic radical having 6 to 18, preferably 6 to 12 C atoms, which is unsubstituted or substituted by C_1-C_4 alkyl or C_1-C_4 alkoxy, a trivalent araliphatic radical having 7 to 19, preferably 7 to 12 C atoms, which is unsubstituted or substituted by C_1-C_4 alkyl or C_1-C_4 alkoxy, or a trivalent heteroaromatic radical having 3 to 13 C atoms and 1 to 3 heteroatoms from the group consisting of $-O-$, $-N-$ and $-S-$, which is unsubstituted or substituted by C_1-C_4 alkyl or C_1-C_4 alkoxy, and

R_{001} is H or C_1-C_6 alkyl.

In a preferred embodiment, X_5 , X_6 and X_7 are $-O-$, $-CH_2-O-$, $-C(O)O-$, $-O(O)C-$, $-CH_2-O(O)C-$, $-C(O)-NR_{029}-$, $-O-C(O)-NH-$ or $-CH_2-O-C(O)-NH-$.

Preferred radicals R_{03} , are derived, for example, from triols, such as glycerol, trimethylolpropane, butanetriol, pentanetriol, hexanetriol, trihydroxycyclohexane, trihydroxybenzene and cyanuric acid; triamines, such as diethylenetriamine; tricarboxylic acids, such as cyclohexanetricarboxylic acid or trimellitic acid; and trisocyanates, such as benzene trisocyanate or cyanuric trisocyanate.

Some examples of compounds of the formula (f1) with a trivalent bridge group are



Possible tetravalent bridge groups are, for example, those of the formula (f7)



in which



X_3 , X_6 , X_7 and X_8 are $-C(O)O-$, $-CH_2-O(O)C-$ or $-C(O)-NR_{029}-$, and

R_{032} is a tetravalent aliphatic hydrocarbon radical having 4 to 20, preferably 4 to 12 C atoms, a tetravalent cycloaliphatic radical having 4 to 8, preferably 5 or 6 ring C atoms, which is unsubstituted or substituted by C_1-C_4 alkyl or C_1-C_4 alkoxy, or a tetravalent aromatic radical having 6 to 18, preferably 6 to 12 C atoms, which is unsubstituted or substituted by C_1-C_4 alkyl or C_1-C_4 alkoxy, a tetravalent araliphatic radical having 7 to 19, preferably 7 to 12 C atoms, which is unsubstituted or substituted by C_1-C_4 alkyl or C_1-C_4 alkoxy, or a tetravalent heteroaromatic radical having 3 to 13 C atoms and 1 to three heteroatoms from the group consisting of $-O-$, $-N-$ and $-S-$, which is unsubstituted or substituted by C_1-C_4 alkyl or C_1-C_4 alkoxy, and R_{029} is H or C_1-C_6 alkyl.

Some examples of tetrafunctional compounds from which R_{032} can be derived are pentaerythritol, pyromellitic acid and 3,4,3',4'-biphenyltetracarboxylic acid.

Preparation methods which can be used are the same methods as for the preparation of the abovementioned compounds with a di- or trivalent radical.

Some examples of compounds of the formula (f1) with a tetravalent bridge group are



Polyols, such as dipentaerythritol or hexahydrohexane, which can be reacted with corresponding cycloolefin monocarboxylic acids, may be mentioned as an example of compounds which are more than tetravalent and from which the bridge group can be derived.

Polymers and comonomers which contain only carbon and hydrogen are particularly preferred according to the invention. Norbornene is especially preferably contained as a comonomer in amounts of, for example, 20 to 60% by weight.

The comonomeric cycloolefins can be contained in an amount of 0.01 to 99% by weight, preferably 0.1 to 95% by weight, particularly preferably 1 to 90% by weight, and especially preferably 5 to 80% by weight, based on the polymers and monomers present in the composition.

The composition according to the invention can comprise solvents, especially if it is used for the production of coatings.

Suitable inert solvents are, for example, protic-polar and aprotic solvents, which can be used alone or in mixtures of at least two solvents. Examples are: ethers

(dibutyl ether, tetrahydrofuran, dioxane, ethylene glycol monomethyl or dimethyl ether, ethylene glycol monoethyl or diethyl ether, diethylene glycol diethyl ether and triethylene glycol dimethyl ether), halogenated hydrocarbons (methylene chloride, chloroform, 1,2-dichloroethane, 1,1,1-trichloroethane and 1,1,2,2-tetrachloroethane), carboxylic acid esters and lactones (ethyl acetate, methyl propionate, ethyl benzoate, 2-methoxyethyl acetate, γ -butyrolactone, δ -valerolactone and pivalolactone), carboxylic acid amides and lactams (N,N-dimethylformamide, N,N-diethylformamide, N,N-dimethylacetamide, tetramethylurea, hexamethylphosphoric acid triamide, γ -butyrolactam, ϵ -caprolactam, N-methylpyrrolidone, N-acetylpyrrolidone and N-methylcaprolactam), sulfoxides (dimethyl sulfoxide), sulfones (dimethyl sulfone, diethyl sulfone, trimethylene sulfone and tetramethylene sulfone), tertiary amines (N-methylpiperidine and N-methylmorpholine), aliphatic and aromatic hydrocarbons, for example petroleum ether, pentane, hexane, cyclohexane, methylcyclohexane, benzene or substituted benzenes (chlorobenzene, o-dichlorobenzene, 1,2,4-trichlorobenzene, nitrobenzene, toluene and xylene) and nitriles (acetonitrile, propionitrile, benzonitrile and phenylacetonitrile). Preferred solvents are aprotic polar and non-polar solvents.

The choice of solvents depends chiefly on the properties of the one-component catalysts, which must not be deactivated by the solvents used. Ruthenium and osmium catalysts can be used together with polar protic solvents, for example water or alkanols. These catalysts are also insensitive to air, oxygen and moisture, and corresponding crosslinkable compositions can be processed without particular protective measures. In the case of the other one-component catalysts, the exclusion of oxygen and moisture is advisable. The compositions are stable to storage, storage in the dark being advisable because of the sensitivity to light.

The composition according to the invention can comprise formulation auxiliaries and additions to improve the physical or mechanical properties. The compounds mentioned above as solvents are suitable as such substances. Known auxiliaries are stabilizers, for example antioxidants and light stabilizers, plasticizers, dyes,

pigments, tixotropic [sic] agents, viscosity improvers, antistatics, lubricants and mould release auxiliaries.

The compositions according to the invention can be polymerized even if they also comprise fillers or reinforcing fillers in relatively large amounts. They can comprise these fillers in amounts of 0.1 to 90% by weight, preferably 0.5 to 80% by weight, more preferably 1 to 70% by weight, particularly preferably 5 to 60% by weight, and especially preferably 10 to 50% by weight, based on the monomers present.

Suitable reinforcing fillers are, in particular, those having a length to width ratio of at least 2. These are often fibrous or needle-shaped fillers. Some examples are fibres of plastics, carbon fibres, glass fibres, silicatic fibres, such as asbestos, whisker and wood fibres.

Suitable fillers are, for example, metal powders, wood flour, glass powders, glass beads, semimetal and metal oxides, for example SiO_2 (aerosils and quartz), corundum and titanium oxide, semimetal and metal nitrides, for example silicon nitride, boron nitride and aluminium nitride, semimetal and metal carbides [sic], metal carbonates (dolomite and CaCO_3), metal sulfates (barite and gypsum), rock powders and naturally occurring or synthetic minerals, chiefly from the silicate series, for example talc, wollastonite, bentonite and others.

Catalytic amounts for the one-component catalyst in the context of the present invention preferably means an amount of 0.001 to 20 mol %, more preferably 0.01 to 15 mol %, particularly preferably 0.01 to 10 mol %, and especially preferably 0.01 to 5 mol %, based on the amount of the monomer. Because of the high photocatalytic activity in ruthenium and osmium catalysts containing phosphorus groups, amounts of 0.001 to 2% by weight are especially preferred in this case.

The compositions according to the invention advantageously comprise the novel thermal and/or photochemical one-component catalysts below:

1. Heat-stable ruthenium or osmium compounds which can be activated by radiation and have at least one photolabile ligand bonded to the ruthenium or osmium atom, the remaining coordination sites being satisfied by non-photolabile ligands.

Heat stability in the context of the invention means that the photocatalytically active metal compounds form no active species for the ring-opening metathesis polymerization when heated. For example, at room temperature to slightly elevated temperature, such as about +40°C, the catalyst can initiate no ring-opening metathesis polymerization with exclusion of light in the course of weeks. Only an insignificant amount (less than 0.2% by weight) of monomer is reacted during this period. The heat stability can be determined, for example, by storing a toluene solution with 20% by weight of monomer and 0.33% by weight of metal catalyst in the dark at 50°C for 96 hours, and any amount of polymer formed, which can be detected by the build-up in viscosity and can be determined quantitatively by precipitation in a precipitant, for example ethanol, filtration and drying, is not more than 0.5% by weight, and preferably not more than 0.2% by weight.

Organic or inorganic compounds, atoms or ions which are coordinated onto a metal centre are designated as ligands for the ruthenium and osmium compounds to be used according to the invention.

Photolabile ligand in the context of the present invention means that when the catalyst is irradiated by light in the visible or ultraviolet spectral range, the ligand dissociates from the catalyst and forms a catalytically active species for the metathesis polymerization. Nonionic photolabile ligands are preferred according to the invention.

The photolabile ligands can be, for example, nitrogen (N_2), monocyclic, polycyclic or fused arenes having 6 to 24, preferably 6 to 18, and particularly preferably 6 to 12 C atoms, which are unsubstituted or substituted by OH, C_1 - C_4 alkyl, C_1 - C_4 alkoxy, C_6 - C_{12} aryl or halogen, or monocyclic heteroarenes, fused

heteroarenes or fused arene-heteroarenes having 3 to 22, preferably 4 to 16, and in particular 4 to 10 C atoms and 1 to 3 heteroatoms chosen from the group consisting of O, S and N, which are unsubstituted or substituted by C₁-C₄alkyl, C₁-C₄alkoxy or halogen; or aliphatic, cycloaliphatic, aromatic or araliphatic nitriles having 1 to 22, preferably 1 to 18, particularly preferably 1 to 12, and especially preferably 1 to 7 C atoms, which are unsubstituted or substituted by C₁-C₄alkyl, C₁-C₄alkoxy or halogen. The preferred substituents are methyl, ethyl, methoxy, ethoxy, fluorine, chlorine and bromine. The arenes and heteroarenes are preferably substituted by one or two radicals, and particularly preferably are unsubstituted. Among the heteroarenes, the electron-rich heteroarenes are preferred. The arenes and heteroarenes can be both π - and σ -bonded; in the last case, they are then the corresponding aryl and heteroaryl radicals. The aryl preferably contains 6 to 18, particularly preferably 6 to 12 C atoms. The heteroaryl preferably contains 4 to 16 C atoms.

Some examples of arenes and heteroarenes are benzene, p-cumene, biphenyl, naphthalene, anthracene, acenaphthene, fluorene, phenanthrene, pyrene, chrysene, fluoranthrene, furan, thiophene, pyrrole, pyridine, γ -pyran, γ -thiopyran, pyrimidine, pyrazine, indole, coumarone, thionaphthene, carbazole, dibenzofuran, dibenzothiophene, pyrazole, imidazole, benzimidazole, oxazole, thiazole, isoxazole, isothiazole, quinoline, isoquinoline, acridine, chromene, phenazine, phenoxazine, phenothiazine, triazines, thianthrene and purine. Preferred arenes and heteroarenes are benzene, naphthalene, thiophene and benzothiophene. The arene is especially preferably benzene and the heteroarene is especially preferably thiophene.

The nitriles can be substituted, for example by methyl, ethyl, fluorine or chlorine; the nitriles are preferably unsubstituted. The alkylnitriles are preferably linear. Some examples of nitriles are acetonitrile, propionitrile, butyronitrile, pentynitrile, hexynitrile, cyclopentyl- and cyclohexylnitrile, benzonitrile, methylbenzonitrile, benzylnitrile and naphthylnitrile. The nitriles are preferably linear C₁-C₄alkylnitriles or benzonitrile. Of the alkylnitriles, acetonitrile is particularly

In a preferred sub-group, the photolabile ligands are N_2 , benzene which is unsubstituted or substituted by one to three C_1 - C_4 alkyl, thiophene, benzonitrile or acetonitrile.

Non-photolabile ligand (also called highly coordinating ligand) in the context of the present invention means that when the catalyst is irradiated in the visible or near-ultraviolet spectral range, the ligand does not dissociate or dissociates to only an insignificant extent from the catalyst.

The non-photolabile ligands can be solvating inorganic and organic compounds which contain the heteroatoms O, S or N and are often also used as solvents, or cyclopentadienyl or indenyl which are unsubstituted or substituted by C_1 - C_4 alkyl, C_1 - C_4 alkoxy, $(C_1$ - C_4 alkyl) $_3$ Si or $(C_1$ - C_4 alkyl) $_3$ SiO-. Examples of such compounds are H_2O , H_2S and NH_3 ; halogenated or unhalogenated, in particular fluorinated or chlorinated, aliphatic or cycloaliphatic alcohols or mercaptans having 1 to 18, preferably 1 to 12, and particularly preferably 1 to 6 C atoms, aromatic alcohols or thiols having 6 to 18, preferably 6 to 12 C atoms, and araliphatic alcohols or thiols having 7 to 18, preferably 7 to 12 C atoms; aliphatic, cycloaliphatic, araliphatic or aromatic ethers, thioethers, sulfoxides, sulfones, ketones, aldehydes, carboxylic acid esters, lactones, optionally N- C_1 - C_4 mono- or -dialkylated carboxylic acid amides having 2 to 20, preferably 2 to 12, and in particular 2 to 6 C atoms and optionally N- C_1 - C_4 alkylated lactams; aliphatic, cycloaliphatic, araliphatic or aromatic, primary, secondary and tertiary amines having 1 to 20, preferably 1 to 12, and particularly preferably 1 to 6 C atoms; and unsubstituted or substituted cyclopentadienyls, for example cyclopentadienyl, indenyl and mono- or polymethylated or trimethylsilylated cyclopentadienyls or indenyls.

Examples of such non-photolabile ligands are methanol, ethanol, n- and i-propanol, n-, i- and t-butanol, 1,1,1-trifluoroethanol, bistrifluoromethylmethanol, tristrifluoromethylmethanol, pentanol, hexanol, methyl- or ethylmercaptan, cyclopentanol, cyclohexanol, cyclohexylmercaptan, phenol, methylphenol, fluorophenol, phenylmercaptan, benzylmercaptan, benzyl alcohol, diethyl ether, dimethyl ether, diisopropyl ether, di-n- or di-t-butyl ether, tetrahydrofuran,



tetrahydropyran, dioxane, diethyl thioether, tetrahydrothiophene, dimethyl sulfoxide, diethyl sulfoxide, tetra- and pentamethylene sulfoxide, dimethyl sulfone, diethyl sulfone, tetra- and pentamethylene sulfone, acetone, methyl ethyl ketone, diethyl ketone, phenyl methyl ketone, methyl isobutyl ketone, benzyl methyl ketone, acetaldehyde, propionaldehyde, trifluoroacetaldehyde, benzaldehyde, ethyl acetate, butyrolactone, dimethylformamide, dimethylacetamide, pyrrolidone and N-methylpyrrolidone, indenyl, cyclopentadienyl, methyl- or dimethyl- or pentamethylcyclopentadienyl and trimethylsilylcyclopentadienyl.

The primary amines can be those of the formula $R_{25}NH_2$, the secondary amines those of the formula $R_{25}R_{26}NH$ and the tertiary amines those of the formula $R_{25}R_{26}R_{27}N$, in which R_{25} is C_1 - C_{18} alkyl, C_5 - or C_6 cycloalkyl which is unsubstituted or substituted by C_1 - C_4 alkyl or C_1 - C_4 alkoxy, or C_6 - C_{18} aryl or C_7 - C_{12} aralkyl which are unsubstituted or substituted by C_1 - C_4 alkyl or C_1 - C_4 alkoxy, R_{26} independently has the meaning of R_{25} , or R_{25} and R_{26} together are tetramethylene, pentamethylene, 3-oxa-1,5-pentylene or $-CH_2-CH_2-NH-CH_2-CH_2-$ or $-CH_2-CH_2-N(C_1-C_4alkyl)-CH_2-CH_2-$, R_{25} and R_{26} independently of one another have the abovementioned meanings, and R_{27} independently has the meaning of R_{25} . The alkyl preferably contains 1 to 12, and particularly preferably 1 to 6 C atoms. The aryl preferably contains 6 to 12 C atoms and the aralkyl preferably contains 7 to 9 C atoms. Examples of amines are methyl-, dimethyl-, trimethyl-, ethyl-, diethyl-, triethyl-, methylethyl-, dimethylethyl, n-propyl-, di-n-propyl-, tri-n-butyl-, cyclo-hexyl-, phenyl- and benzylamine, and pyrrolidone, N-methylpyrrolidine, piperidine, piperazine, morpholine and N-methylmorpholine.


In a preferred sub-group, the non-photolabile ligands are H_2O , NH_3 and unsubstituted or partly or completely fluorinated C_1 - C_4 alkanols. H_2O , NH_3 , cyclopentadienyl, methanol and ethanol are especially preferred.

The ruthenium and osmium compounds to be used according to the invention can be mono- or polynuclear, for example those having two or three metal centres. The metal atoms can be bonded here via a bridge group or metal-metal bonds.

Among the compounds with a plurality of metal centres, those of the formula VIIIa or VIIIb



in which Lig is a photolabile ligand and Me is Ru or Os, A₉, A₁₀ and A₁₁ are a divalent bridge group, and Y⁻ is a monovalent non-coordinating anion, are preferred. The bridge group is preferably ionic, and particularly preferably a halide, especially preferably chloride, bromide or iodide. The photolabile ligand is preferably identical or different arenes, and Y⁻ can be the anions listed below, and especially chloride, bromide or iodide. An example of such complexes is [C₆H₆Ru(Cl)₃RuC₆H₆][Cl]. Preferred catalysts according to the invention correspond to the formula IX



in which

Me is ruthenium or osmium;

n is 0, 1, 2, 3, 4, 5, 6, 7 or 8;

L₁ is a photolabile ligand;

L₂, L₃, L₄, L₅ and L₆ independently of one another are a non-photolabile or a photolabile ligand;

m is 1, 2, 3, 4, 5 or 6;

o, p, q, r and s independently of one another are 0, 1, 2, 3, 4 or 5;

z₁, z₂, z₃, z₄, z₅, z₆ and z₇ independently of one another are -4, -3, -2, -1, 0, +1 or +2; and

L₇ is a non-coordinating cation or anion;

where the sum of $m + o + p + q + r + s$ is an integer from 2 to 6 and t is the quotient of $(n + m \cdot z_1 + o \cdot z_2 + p \cdot z_3 + q \cdot z_4 + r \cdot z_5 + s \cdot z_6)/z_7$.

In the formula IX, L_7 is preferably halogen (for example Cl, Br and I), the anion of an oxygen acid BF_4 , PF_6 , SiF_6 or AsF_6 .


The anions of oxygen acids can be, for example, sulfate, phosphate, perchlorate, perbromate, periodate, antimonate, arsenate, nitrate, carbonate, the anion of a C_1 - C_6 carboxylic acid, for example formate, acetate, propionate, butyrate, benzoate, phenylacetate or mono-, di- or trichloro- or -fluoroacetate, sulfonates, for example methylsulfonate, ethylsulfonate, propylsulfonate, butylsulfonate, trifluoromethylsulfonate (triflate) or phenylsulfonate or benzylsulfonate which are unsubstituted or substituted by C_1 - C_4 alkyl, C_1 - C_4 alkoxy or halogen, in particular fluorine, chlorine or bromine, for example tosylate, mesylate, brosylate, p-methoxy- or p-ethoxyphenylsulfonate, pentafluorophenylsulfonate or 2,4,6-triisopropylsulfonate, and phosphonates, for example methylphosphonate, ethylphosphonate, propylphosphonate, butylphosphonate, phenylphosphonate, p-methylphenylphosphonate and benzylphosphonate.

Preferably, in the formula IX, Me is ruthenium, in particular Ru^{2+} .

A group of compounds of the formula IX which is to be singled out in particular is that in which the ligands L_1 , L_2 , L_3 , L_4 , L_5 and L_6 independently of one another are aliphatic, cycloaliphatic, aromatic or araliphatic nitriles having 1 to 22 C atoms, which are unsubstituted or substituted by C_1 - C_4 alkyl, C_1 - C_4 alkoxy or halogen, or C_6 - C_{18} aryl; or L_1 , L_2 and L_3 together are monocyclic, polycyclic or fused arenes having 6 to 24, preferably 6 to 18, and particularly preferably 6 to 12 C atoms, which are unsubstituted or substituted by -OH, C_1 - C_4 alkyl, C_1 - C_4 alkoxy, C_6 - C_{12} aryl or halogen, or monocyclic heteroarenes, fused heteroarenes or fused aromatic heteroarenes having 4 to 22 C atoms and 1 to 3 heteroatoms chosen from the group consisting of O, S, and N, which are unsubstituted or substituted by -OH, C_1 - C_4 alkyl, C_1 - C_4 alkoxy or halogen, and L_4 , L_5 and L_6 together have the same

meaning, or individually, independently of one another, are N_2 or the said nitrile or the said C_6-C_{14} aryl.

A preferred sub-group of the above compounds of the formula IX are those in which the ligands L_1 , L_2 , L_3 , L_4 , L_5 and L_6 independently of one another are N_2 , C_1-C_{20} alkylnitrile, C_6-C_{12} arylnitrile, C_7-C_{12} aralkylnitrile, C_6-C_{12} aryl or L_1 , L_2 and L_3 each together are the groups A_1 or A_2



in which

R_{28} , R_{29} , R_{30} , R_{31} , R_{32} , R_{33} , R_{34} , R_{35} , R_{36} and R_{37} independently of one another are hydrogen, C_1-C_{20} alkyl, C_1-C_{20} alkoxy, aryl or $SiR_{38}R_{39}R_{40}$ where, in the case of groups A_1 and A_2 on adjacent carbon atoms, an aromatic or heteroaromatic ring, the heteroatoms of which are chosen from oxygen, sulfur and nitrogen, can be fused on; and R_{38} , R_{39} and R_{40} independently of one another are C_1-C_{12} alkyl, C_5 - or C_6 cycloalkyl, or phenyl or benzyl which are unsubstituted or substituted by C_1-C_6 alkyl or C_1-C_6 alkoxy, preferably C_1-C_6 alkyl, phenyl or benzyl, particularly preferably C_1-C_4 alkyl, phenyl or benzyl, and L_4 , L_5 and L_6 likewise together have this meaning or are each individually N_2 , the said nitriles or the said C_6-C_{12} aryl, or are an arene or heteroarene.

From this group of compounds of the formula IX which is to be singled out, preferred compounds are those in which

L_1 , L_2 , L_3 , L_4 , L_5 and L_6 independently of one another are C_1-C_{12} alkylnitrile, C_6-C_{12} arylnitrile, or L_1 , L_2 and L_3 each together are the groups A_1 or A_2 and L_4 , L_5 and L_6 likewise together have this meaning or each individually are N_2 , the said

R_{28} , R_{29} , R_{30} , R_{31} , R_{32} , R_{33} , R_{34} , R_{35} , R_{36} and R_{37} independently of one another are hydrogen, C_1 - C_6 alkyl, C_1 - C_6 alkoxy, $SiR_{38}R_{39}R_{40}$ or phenyl, where, in the case of the groups A_1 and A_2 on adjacent carbon atoms, a benzene ring can be fused on, and R_{38} , R_{39} and R_{40} are methyl, ethyl or phenyl.

In an especially preferred embodiment of the process according to the invention, the catalyst used is that of the formula IX, in which

L_1 , L_2 , L_3 , L_4 , L_5 and L_6 independently of one another are methylnitrile, ethylnitrile or phenylnitrile, or L_1 , L_2 and L_3 each together are the groups A_1 or A_2 and L_4 , L_5 and L_6 likewise together have this meaning or each individually are the said nitriles, in which R_{28} , R_{29} , R_{30} , R_{31} , R_{32} , R_{33} , R_{34} , R_{35} , R_{36} and R_{37} independently of one another are hydrogen, methyl, methoxy or phenyl, where, in the case of the groups A_1 and A_2 on adjacent carbon atoms, a benzene ring can be fused on.

Another particularly preferred sub-group of the compounds of the formula IX are those in which L_1 , L_2 and L_3 together are monocyclic, polycyclic or fused arenes having 6 to 24, preferably 6 to 18, and particularly preferably 6 to 12 C atoms, which are unsubstituted or substituted by C_1 - C_4 alkyl, C_1 - C_4 alkoxy, C_6 - C_{12} aryl or halogen, or monocyclic heteroarenes, fused heteroarenes or fused arene-heteroarenes having 4 to 22, preferably 4 to 16, and in particular 4 to 10 C atoms and 1 to 3 heteroatoms chosen from the group consisting of O, S and N, which are unsubstituted or substituted by C_1 - C_4 alkyl, C_1 - C_4 alkoxy or halogen, and L_4 , L_5 and L_6 are a non-photolabile ligand, the previous preferred meanings also applying here.

In this sub-group, L_1 , L_2 and L_3 are preferably benzene or naphthalene, and the non-photolabile ligand is preferably H_2O , NH_3 , C_1 - C_4 alkanol or -alkanethiol which are unsubstituted or substituted by fluorine, aliphatic ethers, thioethers, sulfoxides and sulfones having 2 to 8 C atoms, dimethylformamide or N-methylpyrrolidone.

In another preferred sub-group of compounds of the formula X, the compounds are ruthenium and osmium compounds of the formula X



in which L_1 is a photolabile ligand and L_2 is a non-photolabile ligand, Me is Ru or Os, Y_1 is a non-coordinating anion and x is the numbers 1, 2 or 3. For the photolabile ligands, non-photolabile ligands, Me and Y_1 , the abovementioned preferred meanings apply. Particularly preferably, L_1 is N_3 or a nitrile, for example C₁-C₄alkylnitrile (acetonitrile), benzonitrile or benzylnitrile, L_2 is NH_3 or an amine having 1 to 12 C atoms, Y_1 is a non-coordinating anion and x is the number 1 or 2.

Catalysts which are particularly suitable for the present invention are (tos is tosylate and tis is 2,4,6-triisopropylphenylsulfonate): $Ru(CH_3CN)_6(tos)_2$, $Ru(CH_3CH_2CN)_6(tos)_2$, $Ru(CH_3CN)_6(CF_3SO_3)_2$, $Ru(CH_3CH_2CN)_6(CF_3SO_3)_2$, $Ru(C_6H_6)_2(tos)_2$, $[Ru(C_6H_6)(C_6H_5OCH_3)](BF_4)_2$, $[Ru(C_6H_6)(C_6H_5i\text{-propyl})](BF_4)_2$, $[Ru(C_6H_6)(1,3,5\text{-trimethylphenol})](BF_4)_2$, $[Ru(C_6H_6)(\text{hexamethylbenzene})](BF_4)_2$, $[Ru(C_6H_6)(\text{biphenyl})](BF_4)_2$, $[Ru(C_6H_6)(\text{chrysene})](BF_4)_2$, $[Ru(C_6H_6)(\text{naphthalene})](BF_4)_2$, $[Ru(\text{cyclopentadienyl})(4\text{-methylcumyl})]PF_6$, $[Ru(\text{cyanophenyl})_6](tos)_2$, $[Ru(\text{cyanophenyl})_6](CF_3SO_3)_2$, $[Ru(C_6H_6)(\text{tetramethylthiophene})_3](tos)_2$, $[Ru(C_6H_6)(CH_3CN)_3](tos)_2$, $[Ru(C_6H_6)(\text{tetramethylthiophene})_3](CF_3SO_3)_2$, $[Ru(C_6H_6)(CH_3CN)_3](CF_3SO_3)_2$, $[Ru(C_6H_6)(CH_3OH)_3](tos)_2$, $[Ru(C_6H_6)(CH_3OH)_3](tis)_2$, $[Os(NH_3)_5N_2](PF_6)_2$, $[Ru(NH_3)_5N_2](PF_6)_2$, $[Ru(NH_3)_5(CH_3CN)]BF_4$, $[Ru(C_6H_6)(NH_3)_3](tis)_2$, $[Ru(C_6H_6)(\text{tetrahydrothiophene})_3](CF_3SO_3)_2$, $[Ru((CH_3)_2S)_3C_6H_5](tos)_2$, $[Ru(\text{dimethyl sulfoxide})_3C_6H_5](PF_6)_2$, $[Ru(\text{dimethylformamide})_3C_6H_5](PF_6)_2$, $[Ru(C_6H_6)Cl_2]_2$ and $[Os(C_6H_6)Cl_2]_2$.

Ruthenium and osmium catalysts to be used according to the invention are either known and in some cases commercially obtainable, or can be prepared analogously to known processes. Such catalysts and their preparation are described, for example, in Gilkerson, W.R., Jackson, M.D., J. Am. Chem. Soc. 101:4096-411 (1979), Bennett, M.A., Matheson, T.W., J. Organomet. Chem. 175:87-93 (1979), Moorehouse, S., Wilkinson, G., J. Chem. Soc.; Dalton Trans., 2187-2190 (1974) and Luo, S., Rauchfuss, T.B., Wilson, S.R., J. Am. Chem. Soc. 114:8515-8520 (1992).

2. Heat-stable molybdenum(VI) or tungsten(VI) compounds which can be activated by heat or with radiation and have at least two methyl groups or two monosubstituted methyl groups bonded to the metal, the substituent having no hydrogen atom in the α position.

The other valencies of the molybdenum- and tungsten are preferably satisfied by heat-stable neutral ligands, a very large number of which are known. The number of neutral ligands may also exceed the stoichiometrically possible number (solvates). Heat stability has been explained above. At temperatures above 50°C, for example 60 to 300°C, these molybdenum and tungsten compounds are also activated by heat.

The molybdenum and tungsten compounds to be used according to the invention can be those which contain one metal atom, or two metal atoms bonded via a single, double or triple bond. The methyl group or monosubstituted methyl group bonded to the metal is bonded at least twice, particularly preferably two to six times, and especially preferably two to four times, as a ligand. This ligand preferably is that of the formula IX



in which R is H, $-\text{CF}_3$, $-\text{SiR}_{38}\text{R}_{39}\text{R}_{40}$, $-\text{CR}_{41}\text{R}_{42}\text{R}_{43}$, or $\text{C}_6\text{-C}_{10}$ aryl or $\text{C}_4\text{-C}_9$ heteroaryl having 1 to 3 heteroatoms from the group consisting of O, S and N, which are unsubstituted or substituted by $\text{C}_1\text{-C}_6$ alkyl or $\text{C}_1\text{-C}_6$ alkoxy; and R_{41} , R_{42} and R_{43} independently of one another are $\text{C}_1\text{-C}_{10}$ alkyl, which is unsubstituted or substituted by $\text{C}_1\text{-C}_{10}$ alkoxy, or R_{41} and R_{42} have this meaning and R_{43} is $\text{C}_6\text{-C}_{10}$ aryl or $\text{C}_4\text{-C}_9$ heteroaryl, which is unsubstituted or substituted by $\text{C}_1\text{-C}_6$ alkyl or $\text{C}_1\text{-C}_6$ alkoxy; and R_{38} , R_{39} and R_{40} are as defined above.

Alkyl R_{38} to R_{43} can be linear or branched and preferably contain 1 to 8, and particularly preferably 1 to 4 C atoms. Aryl R_{38} to R_{43} is preferably phenyl or

Aryl R in formula XI is preferably phenyl or naphthyl. Heteroaryl R in formula XI is preferably pyridinyl, furanyl, thiophenyl or pyrrolyl.

Preferred substituents for R_{38} to R_{43} in the context of the definitions are methyl, ethyl, methoxy and ethoxy. Examples of the radicals R_{38} to R_{43} have been given above under the compounds of the formula I.

In a preferred embodiment, the group R in formula XI is H, $-\text{C}(\text{CH}_3)_3$, $-(\text{CH}_2)_2\text{C}_6\text{H}_5$, phenyl which is unsubstituted or substituted by methyl, ethyl, methoxy or ethoxy, $-\text{CF}_3$, or $-\text{Si}(\text{CH}_3)_3$.

The other valencies of the Mo(VI) and W(VI) atoms may be satisfied by identical or different ligands from the group consisting of $=\text{O}$, $=\text{N}-\text{R}_{44}$, secondary amines having 2 to 18 C atoms, $\text{R}_{45}\text{O}-$, $\text{R}_{45}\text{S}-$, halogen, unsubstituted or substituted cyclopentadienyl, bridged biscyclopentadienyl, tridentate monoanionic ligands and neutral ligands, for example ethers, nitriles, CO and tertiary phosphines and amines, in which the R_{45} independently of one another are linear or branched C_1-C_{18} alkyl which is unsubstituted or substituted by C_1-C_6 alkoxy or halogen, C_5- or C_6 cycloalkyl which is unsubstituted or substituted by C_1-C_6 alkyl, C_1-C_6 alkoxy or halogen, phenyl which is unsubstituted or substituted by C_1-C_6 alkyl, C_1-C_6 alkoxy, C_1-C_6 alkoxymethyl, C_1-C_6 alkoxyethyl or halogen, or benzyl or phenylethyl which are unsubstituted or substituted by C_1-C_6 alkyl, C_1-C_6 alkoxy, C_1-C_6 alkoxymethyl, C_1-C_6 alkoxyethyl or halogen; and R_{44} is linear or branched C_1-C_{18} alkyl which is unsubstituted or substituted by C_1-C_6 alkoxy, C_5- or C_6 cycloalkyl which is unsubstituted or substituted by C_1-C_6 alkyl, C_1-C_6 alkoxy or halogen, phenyl which is unsubstituted or substituted by C_1-C_6 alkyl, C_1-C_6 alkoxy, C_1-C_6 alkoxymethyl, C_1-C_6 alkoxyethyl, $\text{di}(\text{C}_1-\text{C}_6\text{alkyl})\text{amino}$, $\text{di}(\text{C}_1-\text{C}_6\text{alkyl})\text{amino}-\text{C}_1-\text{C}_3\text{alkyl}$ or halogen, or benzyl or phenylethyl which are unsubstituted or substituted by C_1-C_6 alkyl, C_1-C_6 alkoxy, C_1-C_6 alkoxymethyl, C_1-C_6 alkoxyethyl or halogen.

Secondary amines are preferably those of the formula $\text{R}_{46}\text{R}_{47}\text{N}-$, in which R_{46} and R_{47} independently of one another are linear or branched C_1-C_{18} alkyl; C_5- or C_6 cycloalkyl; benzyl or phenylethyl which are unsubstituted or substituted by

C_1 - C_6 alkoxy, or halogen, or $(C_1$ - C_6 alkyl) $_3$ Si; or R_{46} and R_{47} together are tetramethylene, pentamethylene or 3-oxapentane-1,5-diyl. The alkyl preferably contains 1 to 12, and particularly preferably 1 to 6 C atoms. Some examples are dimethyl-, diethyl-, di-n-propyl-, di-i-propyl-, di-n-butyl-, methylethyl-, dibenzyl-, benzylmethyl-, diphenyl-, phenyl-methylamino and di(trimethylsilyl)amino.

Halogen as a ligand or substituent is preferably F or Cl, and particularly preferably Cl.

The cyclopentadienyl can be unsubstituted or substituted by one to five C_1 - C_4 alkyl, in particular methyl, or $-Si(C_1$ - C_4 alkyl), in particular $-Si(CH_3)_3$. Bridged cyclopentadienyls are, in particular, those of the formula R_{48} -A- R_{48} , in which R_{48} is cyclopentadienyl which is unsubstituted or substituted by one to five C_1 - C_4 alkyl, in particular methyl, or $-Si(C_1$ - C_4 alkyl), in particular $-Si(CH_3)_3$, and A is $-CH_2-$, $-CH_2-CH_2-$, $-Si(CH_3)_2-$, $-Si(CH_3)_2-Si(CH_3)_2-$ or $-Si(CH_3)_2-O-Si(CH_3)_2-$.

Ethers as neutral ligands can be dialkyl ethers having 2 to 8 C atoms or cyclic ethers with 5 or 6 ring members. Some examples are diethyl ether, methyl ethyl ether, diethyl [sic] ether, di-n-propyl ether, di-i-propyl ether, di-n-butyl ether, ethylene glycol dimethyl ether, tetrahydrofuran and dioxane.

Nitriles as neutral ligands can be aliphatic or aromatic nitriles having 1 to 12, preferably 1 to 8 C atoms. Some examples are acetonitrile, propionitrile, butylnitrile, benzonitrile and benzylnitrile.

Tertiary amines and phosphines as neutral ligands can be those having 3 to 24, preferably 3 to 18 C atoms. Some examples are trimethylamin and -phosphin, triethylamine and -phosphine, tri-n-propylamine and -phosphin, tri-n-butylamine and -phosphine, triphenylamine and -phosphine, tricyclohexylamine and -phosphine, phenyldimethylamine and -phosphin, benzyldimethylamine and -phosphine, 3,5-dimethylphenyl-dimethylamin and -phosphine.


The tridentate monoanionic ligands can be, for example, hydro(tris-pyrazol-1-yl)borates or alkyl(trispyrazol-1-yl)borates, which are unsubstituted or substituted by one to three C_1-C_4 alkyl [see Trofimenko, S., Chem. Rev., 93:943-980 (1993)], or $[C_5(R'_3)Co(R_{50}R_{51}P=O)_3]$, in which R' is H or methyl and R_{50} and R_{51} independently of one another are C_1-C_4 alkyl, C_1-C_4 alkoxy or phenyl [see Kläui, W., Angew. Chem. 102:661-670 (1990)].

Halogen as a substituent for the radicals R_{44} and R_{45} is preferably fluorine, and particularly preferably chlorine. The substituents alkyl, alkoxy or alkoxy in alkoxyethyl or -ethyl preferably contain 1 to 4, and in particular 1 or 2 C atoms. Examples are methyl, ethyl, n- and i-propyl, n-, i- and t-butyl, methoxy, ethoxy, n- and i-propyloxy and n-, i- and t-butyloxy.


Alkyl R_{44} and R_{45} preferably contain 1 to 12, particularly preferably 1 to 8, and especially preferably 1 to 4 C atoms. The alkyl is preferably branched alkyl. Some examples of R_{44} are methoxy, ethoxy, n- and i-propyloxy, n-, i- and t-butyloxy, hexafluoro-i-propyloxy and hexa- and perfluorobutyloxy.

Some examples of substituted phenyl and benzyl R_{44} and R_{45} are p-methylphenyl or benzyl, p-fluoro- or p-chlorophenyl or -benzyl, p-ethylphenyl or -benzyl, p-n- or i-propylphenyl or -benzyl, p-i-butyphenyl or -benzyl, 3-methylphenyl or -benzyl, 3-i-propylphenyl or -benzyl, 2,6-dimethylphenyl or -benzyl, 2,6-di-i-propylphenyl or -benzyl, 2,6-di-n- or -t-butylphenyl and -benzyl. R_{45} is particularly preferably phenyl which is unsubstituted or substituted by C_1-C_4 alkyl or C_1-C_4 alkoxy.


In a preferred embodiment, the molybdenum and tungsten compounds are, in particular, those of one of the formulae XII to XIIc




(XII).



(XIIa).



(XIIb).



(XIIc)

in which

Me is Mo(VI) or W(VI);

at least two, preferably 2 to 4, of the radicals R_{33} to R_{38} are a radical $-CH_2-R$ of the formula XI in which R is as defined above;

in each case two of the other radicals of R_{33} to R_{38} are $=O$ or $=N-R_{44}$, and R_{44} is as defined above; and/or

the other radicals of R_{33} to R_{38} are secondary amino having 2 to 18 C atoms, $R_{45}O-$ or $R_{45}S-$, halogen, cyclopentadienyl or bridged biscyclopentadienyl or a neutral ligand, in which R_{45} is as defined above. For the radicals R, R_{44} and R_{45} , the abovementioned preferred meanings apply.

In a particularly preferred embodiment, molybdenum or tungsten compounds of the formula XII which are employed in the composition according to the invention are those in which

a) R_{33} to R_{38} are a radical of the formula XI $-CH_2-R$, or


b) R_{33} and R_{34} are a radical of the formula XI $-\text{CH}_2\text{-R}$, R_{33} and R_{34} together are the radical $=\text{N-R}_{44}$, and R_{37} and R_{38} together independently of one another are $\text{R}_{45}\text{-O-}$ or halogen, or

c) R_{33} and R_{34} together and R_{35} and R_{36} together are the radical $=\text{N-R}_{44}$, and R_{37} and R_{38} are a radical of the formula XI $-\text{CH}_2\text{-R}$,

in which R, R_{44} and R_{45} have the above meanings. For R, R_{44} and R_{45} , the above preferred meanings apply.

Particularly preferred compounds of the formula XIIc are those in which R_{33} , R_{34} and R_{35} are a radical of the formula XI, the radical of the formula XI particularly preferably being $-\text{CH}_2\text{-Si}(\text{C}_1\text{-C}_4\text{alkyl})_3$.

Molybdenum or tungsten compounds which are especially preferably used in the composition according to the invention are those of the formulae XIII, XIIIa or XIIIb



in which

M is Mo(VI) or W(VI),

R is H, $-\text{C}(\text{CH}_3)_3$, $-\text{C}(\text{CH}_3)_2-\text{C}_6\text{H}_5$, $-\text{C}_6\text{H}_5$ or $-\text{Si}(\text{C}_1-\text{C}_4\text{alkyl})_3$.

R_{33} is phenyl or phenyl which is substituted by 1 to 3 $\text{C}_1-\text{C}_4\text{alkyl}$ or $\text{C}_1-\text{C}_4\text{alkoxy}$.

R_{33} is linear or branched $\text{C}_1-\text{C}_4\text{alkoxy}$ which is unsubstituted or substituted by fluorine, and

R_{34} has the same meaning as R_{33} or is F, Cl or Br. R_{33} is particularly preferably branched alkoxy, which is unsubstituted or partly or completely substituted by F, for example i-propyloxy, i- and t-butyloxy, hexafluoropropyloxy [sic] and nonafluoropropyloxy. R_{34} is preferably Cl.

Some examples of molybdenum and tungsten compounds are:

$\text{W}(=\text{N}-\text{C}_6\text{H}_5)(\text{OC}(\text{CH}_3)_3)(\text{Cl})[(\text{CH}_2\text{Si}(\text{CH}_3)_3)_2]$, $[(\text{CH}_3)_3\text{SiCH}_2]_3\text{Mo}\equiv\text{Mo}[\text{CH}_2\text{Si}(\text{CH}_3)_3]_3$.

$\text{W}(=\text{N}-\text{C}_6\text{H}_5)(\text{OC}(\text{CF}_3)_2\text{CH}_3)_2[(\text{CH}_2\text{Si}(\text{CH}_3)_3)_2]$, $\text{W}(=\text{NC}_6\text{H}_5)[\text{CH}_2\text{Si}(\text{CH}_3)_3]_3\text{Cl}$.

$\text{Mo}(=\text{N}-2,6\text{-dimethylC}_6\text{H}_3)_2[(\text{CH}_2-\text{C}_6\text{H}_5)_2]$, $\text{W}[2,6-(\text{CH}_3)_2\text{C}_6\text{H}_3\text{N}]_2(\text{CH}_2-\text{C}_6\text{H}_5)_2$.

$\text{Mo}(=\text{N}-2,6\text{-diisopropylC}_6\text{H}_3)_2[(\text{CH}_2-\text{C}_6\text{H}_5)_2]$.

$\text{Mo}(=\text{N}-2,6\text{-diisopropylC}_6\text{H}_3)_2[(\text{CH}_2\text{C}(\text{CH}_3)_2-\text{C}_6\text{H}_5)_2]$ and

$\text{Mo}(=\text{N}-2,6\text{-dimethylC}_6\text{H}_3)_2(\text{CH}_3)_2(\text{tetrahydrofuran})$.

The molybdenum and tungsten catalysts to be used according to the invention are known or can be prepared by known and analogous processes starting from the metal halides by means of Grignard reactions [see, for example, Huq, F., Mowat, W., Shortland, A., Skapski, A.C., Wilkinson, G., J. Chem. Soc., Chem. Commun. 1079-1080 (1971) or Schrock, R.R., Murddeck, J.S., Bazan, G.C., Robbins, J., DiMare, M., O'Regan, M., J. Am. Chem. Soc., 112:3875-3886 (1990)].

3. Heat-stable titanium(IV), niobium(V), tantalum (V), molybdenum(VI) or tungsten(VI) compounds in which a silylmethyl group and at least one halogen are bonded to the metal. These one-component catalysts are particularly photocatalytically active.

The titanium(IV), niobium(V) and tantalum(V) compounds to be used according to the invention are those which contain one metal atom. The molybdenum(VI) and tungsten(VI) compounds to be used according to the invention can be those which contain one metal atom, or two metal atoms bonded via a single, double or triple

bond. The other valencies of the titanium, niobium, tantalum, molybdenum and tungsten are preferably satisfied by heat-stable neutral ligands, the definition of heat stability having been given above. The halogen bonded to the metal atom is preferably F, Cl, Br and I, more preferably F, Cl and Br, and particularly preferably F or Cl. The silylmethyl ligand preferably corresponds to the formula XIV



in which

R_{38} , R_{39} and R_{40} independently of one another are C_1 - C_{18} alkyl, C_5 - or C_6 cycloalkyl or phenyl or benzyl which are unsubstituted or substituted by C_1 - C_6 alkyl or C_1 - C_6 alkoxy.

Alkyl R_{38} to R_{40} can be linear or branched and preferably contains 1 to 12, particularly preferably 1 to 8, and in particular 1 to 4 C atoms. The particularly preferred alkyl is methyl and ethyl.

Preferred substituents for phenyl and benzyl R_{38} to R_{40} in the context of the definitions are methyl, ethyl, methoxy and ethoxy.

In a preferred embodiment R_{38} to R_{40} in the group of formula XIV are C_1 - C_4 alkyl, phenyl or benzyl.

Some examples of the group of the formula XIV are $-\text{CH}_2-\text{Si}(\text{CH}_3)_3$, $-\text{CH}_2-\text{Si}(\text{C}_2\text{H}_5)_3$, $-\text{CH}_2-\text{Si}(\text{n-C}_3\text{H}_7)_3$, $-\text{CH}_2-\text{Si}(\text{n-C}_4\text{H}_9)_3$, $-\text{CH}_2-\text{Si}(\text{CH}_3)_2(\text{n-C}_4\text{H}_9)$, $-\text{CH}_2-\text{Si}(\text{CH}_3)_2(\text{t-C}_4\text{H}_9)$, $-\text{CH}_2-\text{Si}(\text{CH}_3)_2(\text{C}_2\text{H}_5)$, $-\text{CH}_2-\text{Si}(\text{CH}_3)_2[\text{C}(\text{CH}_3)_2\text{CH}(\text{CH}_3)_2]$, $-\text{CH}_2-\text{Si}(\text{CH}_3)_2(\text{n-C}_{12}\text{H}_{25})$, $-\text{CH}_2-\text{Si}(\text{CH}_3)_2(\text{n-C}_{18}\text{H}_{37})$, $-\text{CH}_2-\text{Si}(\text{C}_6\text{H}_5)_3$, $-\text{CH}_2-\text{Si}(\text{CH}_2-\text{C}_6\text{H}_5)_3$, $-\text{CH}_2-\text{Si}(\text{C}_6\text{H}_5)(\text{CH}_3)_2$ and $-\text{CH}_2-\text{Si}(\text{CH}_2-\text{C}_6\text{H}_5)(\text{CH}_3)_2$. $-\text{CH}_2-\text{Si}(\text{CH}_3)_3$ is especially preferred.


The other valencies of the Ti(IV), Nb(V), Ta(V), Mo(VI) and W(VI) atoms may be satisfied by identical or different neutral ligands, for example chosen from the group consisting of $=\text{O}$, $=\text{N-R}_{41}$, secondary amines having 2 to 18 C atoms, $\text{R}_{45}\text{O-}$,

$R_{43}S-$, halogen, substituted or unsubstituted cyclopentadienyl, bridged biscyclopentadienyl, tridentate monoanionic ligands and neutral ligands, for example ethers, nitriles, CO and tertiary phosphines and amines, in which the R_{43} independently of one another are linear or branched C_1-C_{18} alkyl which is unsubstituted or substituted by C_1-C_6 alkoxy or halogen, C_3- or C_6 cycloalkyl which is unsubstituted or substituted by C_1-C_6 alkyl, C_1-C_6 alkoxy or halogen, phenyl which is unsubstituted or substituted by C_1-C_6 alkyl, C_1-C_6 alkoxy,


C_1-C_6 alkoxymethyl, C_1-C_6 alkoxyethyl or halogen, or benzyl or phenylethyl which are unsubstituted or substituted by C_1-C_6 alkyl, C_1-C_6 alkoxy, C_1-C_6 alkoxymethyl, C_1-C_6 alkoxyethyl or halogen; and R_{44} is linear or branched C_1-C_{18} alkyl which is unsubstituted or substituted by C_1-C_6 alkoxy, C_3- or C_6 cycloalkyl which is unsubstituted or substituted by C_1-C_6 alkyl, C_1-C_6 alkoxy or halogen, phenyl which is unsubstituted or substituted by C_1-C_6 alkyl, C_1-C_6 alkoxy, C_1-C_6 alkoxymethyl, C_1-C_6 alkoxyethyl, di(C_1-C_6 -alkyl)amino, di(C_1-C_6 -alkyl)amino- C_1-C_3 alkyl or halogen, or benzyl or phenylethyl, which are unsubstituted or substituted by C_1-C_6 alkyl, C_1-C_6 alkoxy, C_1-C_6 alkoxymethyl, C_1-C_6 alkoxyethyl or halogen, with the proviso that in the case of the titanium compounds, the ligand is not =O or =N- R_{44} .

The definitions and preferences of R_{44} and R_{45} , of secondary amines, of halogen as a further ligand on the metal atoms or as substituent, of cyclopentadienyl, ethers, nitriles, tertiary amines and phosphines as neutral ligands and of tridentate monoanionic ligands have been given previously. Likewise given previously were the definitions and preferences of alkyl, alkoxy or alkoxy as a substituent in alkoxymethyl or -ethyl.

In a preferred embodiment, the metal compounds are those, in particular, of the formulae XV, XVa or XVb



(XV).



in which

Me_1 is Mo(VI) or W(VI);

Me_2 is Nb(V) or Ta(V);

one of the radicals R_{69} to R_{74} is a radical $-CH_2-SiR_{38}R_{39}R_{40}$ of the formula XIV;

at least one of the radicals R_{69} to R_{74} is F, Cl or Br;

R_{38} , R_{39} and R_{40} independently of one another are C_1 - C_6 alkyl, C_5 - or C_6 cycloalkyl, or phenyl or benzyl which are unsubstituted or substituted by C_1 - C_6 alkyl or C_1 - C_6 alkoxy;

in formula XV two or in each case two, and in formula XVa two of the other radicals of R_{69} to R_{74} each together are $=O$ or $=N-R_{44}$, and R_{44} is linear or branched C_1 - C_{18} alkyl which is unsubstituted or substituted by C_1 - C_6 alkoxy, C_5 - or C_6 cycloalkyl which is unsubstituted or substituted by C_1 - C_6 alkyl, C_1 - C_6 alkoxy or halogen, phenyl which is unsubstituted or substituted by C_1 - C_6 alkyl, C_1 - C_6 alkoxy, C_1 - C_6 alkoxymethyl, C_1 - C_6 alkoxyethyl, $di(C_1$ - C_6 alkyl)amino, $di(C_1$ - C_6 alkyl)amino- C_1 - C_3 alkyl or halogen, or benzyl or phenylethyl which are unsubstituted or substituted by C_1 - C_6 alkyl, C_1 - C_6 alkoxy, C_1 - C_6 alkoxymethyl, C_1 - C_6 alkoxyethyl, $di(C_1$ - C_6 alkyl)amino, $di(C_1$ - C_6 alkyl)amino- C_1 - C_3 alkyl or halogen, and the other radicals are secondary amino having 2 to 18 C atoms, $R_{45}O$ - or $R_{45}S$ -, halogen, unsubstituted or substituted cyclopentadienyl or bridged biscyclopentadienyl or a neutral ligand, in which the R_{45} independently of one another are linear or branched C_1 - C_{18} alkyl which is unsubstituted or substituted by C_1 - C_6 alkoxy or halogen, C_5 - or C_6 cycloalkyl which is unsubstituted or substituted by C_1 - C_6 alkyl, C_1 - C_6 alkoxy or halogen, phenyl which is unsubstituted or substituted by C_1 - C_6 alkyl, C_1 - C_6 alkoxy, C_1 - C_6 alkoxymethyl, C_1 - C_6 alkoxyethyl, $di(C_1$ - C_6 alkyl)amino, $di(C_1$ - C_6 alkyl)amino- C_1 - C_3 alkyl or halogen, or benzyl or phenylethyl which are unsubstituted or substituted by C_1 - C_6 alkyl, C_1 - C_6 alkoxy, C_1 - C_6 alkoxymethyl, C_1 - C_6 alkoxyethyl, $di(C_1$ - C_6 alkyl)amino, $di(C_1$ - C_6 alkyl)amino- C_1 - C_3 alkyl or halogen; or

in the formulae XV, XVa and XVb, the other radicals independently of one another are secondary amino having 2 to 18 C atoms, $R_{43}O-$ or $R_{43}S-$, halogen, unsubstituted or substituted cyclopentadienyl or bridged biscyclopentadienyl or a neutral ligand, in which the R_{43} independently of one another are linear or branched C_1-C_{18} alkyl which is unsubstituted or substituted by C_1-C_6 alkoxy or halogen, C_5- or C_6 cycloalkyl which is unsubstituted or substituted by C_1-C_6 alkyl, C_1-C_6 alkoxy or halogen, phenyl which is unsubstituted or substituted by C_1-C_6 alkyl, C_1-C_6 alkoxy, C_1-C_6 alkoxymethyl, C_1-C_6 alkoxyethyl, $di(C_1-C_6-alkyl)-$ amino, $di(C_1-C_6-alkyl)$ amino- C_1-C_3 alkyl or halogen, or benzyl or phenylethyl which are unsubstituted or substituted by C_1-C_6 alkyl, C_1-C_6 alkoxy, C_1-C_6 alkoxymethyl, C_1-C_6 alkoxyethyl, $di(C_1-C_6-alkyl)$ amino, $di(C_1-C_6-alkyl)$ amino- C_1-C_3 alkyl or halogen.

For the radicals R_{69} to R_{74} , the abovementioned preferred meanings apply

In a particularly preferred embodiment, metal compounds of the formulae XV, XVa or XVb which are used in the process according to the invention are those in which

R_{69} is a radical of the formula $XIV -CH_2-SiR_{70}R_{71}R_{72}$ and R_{73} is F, Cl or Br, and (a) in formula XV R_{71} and R_{72} , and R_{73} and R_{74} in each case together are the radical $=N-R_{44}$, or R_{71} and R_{72} together are the radical $=N-R_{44}$, and R_{73} and R_{74} independently of one another are unsubstituted or substituted cyclopentadienyl,





$R_{43}O-$ or halogen, or

b) in formula XVa R_{71} and R_{72} together are the radical $=N-R_{44}$, and R_{44} is unsubstituted or substituted cyclopentadienyl, $R_{43}O-$ or halogen, or in formula XVa R_{71} , R_{72} and R_{73} independently of one another are unsubstituted or substituted cyclopentadienyl, $R_{43}O-$ or halogen, or

c) in formula XVb R_{71} and R_{72} independently of one another are unsubstituted or substituted cyclopentadienyl, $R_{43}O-$ or halogen,

in which R_{70} to R_{74} have the above meanings. For R_{70} , R_{71} , R_{72} , R_{73} and R_{74} , the above preferred meanings apply.

Metal compounds which are especially preferably used in the process according to the invention are those of the formulae XVI, XVIa, XVIb, XVIc or XVIId



in which

Me₁ is Mo(VI) or W(VI);

Me₂ is Nb(V) or Ta(V);

R₇₅ is -Si(C₁-C₄alkyl)₃;

Z is Cl or Br;

R₈₃ is phenyl or phenyl which is substituted by 1 to 3 C₁-C₄alkyl or C₁-C₄alkoxy.

(a) R₇₃ and R₇₄ in formula XVI together are the group =NR₈₃ or individually independently of one another are F, Cl, Br, linear or branched C₁-C₄alkoxy which is unsubstituted or substituted by fluorine, phenoxy which is unsubstituted or substituted by C₁-C₄alkyl or C₁-C₄alkoxy, or cyclopentadienyl which is unsubstituted or substituted by C₁-C₄alkyl;

(b) R₇₁, R₇₂, R₇₃ and R₇₄ in formula XVIa independently of one another are F, Cl, Br, linear or branched C₁-C₄alkoxy which is unsubstituted or


substituted by fluorine, phenyloxy which is unsubstituted or substituted by C₁-C₄alkyl or C₁-C₄alkoxy, or cyclopentadienyl which is unsubstituted or substituted by C₁-C₄alkyl;

(c) R₇₃ in formula XVIb is F, Cl, Br, linear or branched C₁-C₄alkoxy which is unsubstituted or substituted by fluorine, phenyloxy which is unsubstituted or substituted by C₁-C₄alkyl or C₁-C₄alkoxy, or cyclopentadienyl which is unsubstituted or substituted by C₁-C₄alkyl;

(d) R₇₁, R₇₂ and R₇₃ in formula XVIc independently of one another are F, Cl, Br, linear or, in particular, branched C₁-C₄alkoxy which is unsubstituted or substituted by fluorine, phenyloxy which is unsubstituted or substituted by C₁-C₄alkyl or C₁-C₄alkoxy, or cyclopentadienyl which is unsubstituted or substituted by C₁-C₄alkyl; and

(e) R₇₁ and R₇₂ in formula XVIc independently of one another are F, Cl, Br, linear or, in particular, branched C₁-C₄alkoxy which is unsubstituted or substituted by fluorine, phenyloxy which is unsubstituted or substituted by C₁-C₄alkyl or C₁-C₄alkoxy, or cyclopentadienyl which is unsubstituted or substituted by C₁-C₄alkyl. The alkoxy is particularly preferably branched alkoxy, which is optionally partly or completely substituted by F, for example i-propyloxy, i- and t-butyloxy, hexafluoropropyloxy [sic] and nonafluoropropyloxy. The phenyloxy radical is, in particular, phenyloxy substituted in the 2,6-positions [sic] by C₁-C₄alkyl, for example 2,6-dimethylphenyloxy. Examples of substituted cyclopentadienyl radicals are mono- to pentamethylcyclopentadienyl and trimethylsilylcyclopentadienyl. R₈₃ is preferably phenyl or phenyl which is substituted by C₁-C₄alkyl [sic], in particular phenyl, 3,5-dimethyl-, 2,6-dimethyl-, 3,5-diethyl- and 2,6-diethylphenyl.

Especially preferred compounds in the process according to the invention are those of the formulae XVII, XVIIa, XVIIb, XVIIc and XVIId





in which

Me_1 is Mo(VI) or W(VI);

Me_2 is Nb(V) or Ta(V);

X_n is F or Cl;


R_{63} is phenyl or phenyl which is substituted by 1 or 2 C_1 - C_4 alkyl groups;

R_{62} is branched C_3 - or C_4 alkyl which is unsubstituted or partly or completely substituted by fluorine, or phenyloxy or phenyloxy which is substituted by 1 to 3 methyl or ethyl groups;

R_{72} and R_{73} independently of one another are cyclopentadienyl which is unsubstituted or substituted by 1 to 5 methyl groups X_n or $R_{62}O$ -; and

R_{71} which is unsubstituted or substituted by 1 to 5 methyl groups, X_n or $R_{72}O$ -.

Some examples of titanium(IV), niobium(V), tantalum(V), molybdenum(VI) and tungsten(VI) compounds are [Cp is cyclopentadienyl and Me is Nb(V) or Ta(V)]:



Th titanium, niobium, tantalum, molybdenum and tungsten compounds to be used according to th invention are known or can be prepared by known and

metal halides by means of Grignard reactions [Schrock, R.R., Murdzeck, J.S., Bazan, G.C., Robbins, J., DiMare, M., O'Regan, M., J. Am. Chem. Soc., 112:3875-3886 (1990)].

4. Other suitable photactive one-component catalysts are niobium(V) or tantalum(V) compounds which have at least two methyl groups or two monosubstituted methyl groups bonded to the metal, the substituent containing no hydrogen atom in the α position. These compounds are also thermal catalysts.

The niobium(V) and tantalum(V) compounds to be used according to the invention contain one metal atom. The methyl group or monosubstituted methyl group bonded to the metal is bonded at least twice, particularly preferably two to five times, and especially preferably twice or three times as a ligand. This ligand preferably is that of the formula XI



in which R has the meanings and preferred meanings given above.


The other valencies of the niobium and tantalum atom are preferably satisfied by heat-stable neutral ligands, a very large number of which are known. The number of neutral ligands may also exceed the stoichiometrically possible number (solvates). The definition of heat stability has been given above.

The other valencies of the Nb(V) and Ta(V) atoms may be satisfied by identical or different neutral ligands, for example chosen from the group consisting of =O, =N-R₄, secondary amines having 2 to 18 C atoms, R₄O-, R₄S-, halogen, unsubstituted or substituted cyclopentadienyl, bridged biscyclopentadienyl, tridentate monoanionic ligands and neutral ligands, for example ethers, nitriles, CO and tertiary phosphines and amines, in which the R₄ independently of on another are linear or branched C₁-C₁₈alkyl which is unsubstituted or substituted by C₁-C₆alkoxy or halogen, C₅- or C₆cycloalkyl which is unsubstituted or substituted by C₁-C₆alkyl, C₁-C₆alkoxy or halogen, phenyl which is unsubstituted or substituted

by C₁-C₈alkyl, C₁-C₈alkoxy, C₁-C₈alkoxymethyl, C₁-C₈alkoxyethyl or halogen, or benzyl or phenylethyl which are unsubstituted or substituted by C₁-C₈alkyl, C₁-C₈alkoxy, C₁-C₈alkoxymethyl, C₁-C₈alkoxyethyl or halogen; and R₄₄ is linear or branched C₁-C₁₈alkyl which is unsubstituted or substituted by C₁-C₈alkoxy, C₃- or C₆cycloalkyl which is unsubstituted or substituted by C₁-C₈alkyl, C₁-C₈alkoxy or halogen, phenyl which is unsubstituted or substituted by C₁-C₈alkyl, C₁-C₈alkoxy, C₁-C₈alkoxymethyl, C₁-C₈alkoxyethyl, di(C₁-C₈alkyl)-amino, di(C₁-C₈alkyl)amino-C₁-C₃alkyl, or halogen, or benzyl or phenylethyl which are unsubstituted or substituted by C₁-C₈alkyl, C₁-C₈alkoxy, C₁-C₈alkoxymethyl, C₁-C₈alkoxyethyl or halogen.

The definitions and preferences of R₄₄ and R₄₅, of secondary amines, of halogen as a further ligand on the metal atoms or as substituent, of cyclopentadienyl, ethers, nitriles, tertiary amines and phosphines as neutral ligands and of tridentate monoanionic ligands have been given previously. Likewise given previously were the definitions and preferences of alkyl, alkoxy or alkoxy as a substituent in alkoxymethyl or -ethyl.

In a preferred embodiment, the niobium and tantalum compounds are, in particular, those of the formula XVIII



(XVIII),

in which

M is Nb(V) or Ta(V),

at least two, preferably 2 or 3, of the radicals R₈₂ to R₈₆ are a radical -CH₂-R of the formula XI in which R has the meanings and preferred meanings given above; two of the other radicals of R₈₂ to R₈₆ together are =O or =N-R₄₄, and R₄₄ is linear or branched C₁-C₁₈alkyl which is unsubstituted or substituted by C₁-C₈alkoxy,


C₁-C₆alkoxy or halogen, phenyl which is unsubstituted or substituted by C₁-C₆alkyl, C₁-C₆alkoxy, C₁-C₆alkoxymethyl, C₁-C₆alkoxyethyl, di(C₁-C₆alkyl)-amino, di(C₁-C₆alkyl)amino-C₁-C₃alkyl or halogen, or benzyl or phenylethyl which are unsubstituted or substituted by C₁-C₆alkyl, C₁-C₆alkoxy, C₁-C₆alkoxymethyl, C₁-C₆alkoxyethyl, di(C₁-C₆alkyl)amino, di(C₁-C₆alkyl)amino-C₁-C₃alkyl or halogen; and/or

the other radicals of R₃₂ to R₃₆ independently of one another are secondary amino having 2 to 18 C atoms, R₄₅O-, R₄₅S-, halogen, cyclopentadienyl or bridged biscyclopentadienyl or a neutral ligand, in which the R₄₅ independently of one another are linear or branched C₁-C₁₈alkyl which is unsubstituted or substituted by C₁-C₆alkoxy or halogen, C₅- or C₆cycloalkyl which is unsubstituted or substituted by C₁-C₆alkyl, C₁-C₆alkoxy or halogen, phenyl which is unsubstituted or substituted by C₁-C₆alkyl, C₁-C₆alkoxy, C₁-C₆alkoxymethyl, C₁-C₆alkoxyethyl, di(C₁-C₆alkyl)amino, di(C₁-C₆alkyl)amino-C₁-C₃alkyl or halogen, or benzyl or phenylethyl which are unsubstituted or substituted by C₁-C₆alkyl, C₁-C₆alkoxy, C₁-C₆alkoxymethyl, C₁-C₆alkoxyethyl, di(C₁-C₆alkyl)amino, di(C₁-C₆alkyl)amino-C₁-C₃alkyl or halogen.

In a particularly preferred embodiment, the niobium and tantalum compounds of the formula XVIII used are those in which

- R₃₂ to R₃₆ are each a radical of the formula XI -CH₂-R, or
 - R₃₂ and R₃₃ are each a radical of the formula XI -CH₂-R, R₃₄ and R₃₅ together are the radical =N-R₄₄, and R₃₆ is unsubstituted or substituted cyclopentadienyl, R₄₅O- or halogen, or
 - R₃₂, R₃₃ and R₃₄ are each a radical of the formula XI -CH₂-R, and R₃₅ and R₃₆ together are the radical =N-R₄₄, or
- [lacuna] R₃₂, R₃₃, R₃₄ and R₃₅ are a radical of the formula XI -CH₂-R, and R₃₆ is unsubstituted or substituted cyclopentadienyl, R₄₅O- or halogen, in which R, R₄₄ and R₄₅ have the above meanings. For R, R₄₄ and R₄₅, the above preferred meanings apply.

Niobium and tantalum compounds which are especially preferably used in the process according to the invention are those of the formulae IXX, IXXa or IXXb



in which

Me is Nb(V) or Ta(V),

R_v is H, $-\text{C}(\text{CH}_3)_3$, $-\text{C}(\text{CH}_3)_2\text{-C}_6\text{H}_5$, $-\text{C}_6\text{H}_5$ or $-\text{Si}(\text{C}_1\text{-C}_4\text{alkyl})_3$,

R_{s3} is phenyl or phenyl which is substituted by 1 to 3 $\text{C}_1\text{-C}_4\text{alkyl}$ or $\text{C}_1\text{-C}_4\text{alkoxy}$,

R_{s4} in formula IXX is the group $-\text{CH}_2\text{-R}$ or F, Cl, Br, linear or, in particular,

branched $\text{C}_1\text{-C}_4\text{alkoxy}$ which is unsubstituted or substituted by fluorine, phenyloxy

which is unsubstituted or substituted by $\text{C}_1\text{-C}_4\text{alkyl}$ or $\text{C}_1\text{-C}_4\text{alkoxy}$, or

cyclopentadienyl which is unsubstituted or substituted by $\text{C}_1\text{-C}_4\text{alkyl}$;

R_{s2} , R_{s3} and R_{s4} in formula IXXa independently of one another are F, Cl, Br, linear

or, in particular, branched $\text{C}_1\text{-C}_4\text{alkoxy}$ which is unsubstituted or substituted by

fluorine, phenyloxy which is unsubstituted or substituted by $\text{C}_1\text{-C}_4\text{alkyl}$ or

$\text{C}_1\text{-C}_4\text{alkoxy}$, or cyclopentadienyl which is unsubstituted or substituted by

$\text{C}_1\text{-C}_4\text{alkyl}$; and

R_{s2} and R_{s3} in formula IXXb independently of one another are F, Cl, Br, linear or, in

particular, branched $\text{C}_1\text{-C}_4\text{alkoxy}$ which is unsubstituted or substituted by fluorine

phenyloxy which is unsubstituted or substituted by $\text{C}_1\text{-C}_4\text{alkyl}$ or

$\text{C}_1\text{-C}_4\text{alkoxy}$, or cyclopentadienyl which is unsubstituted or substituted by

$\text{C}_1\text{-C}_4\text{alkyl}$. The alkoxy is particularly preferably branched alkoxy, which is

unsubstituted or completely or partly substituted by F, for example i-propyloxy, i- and t-butyloxy, hexafluoropropyloxy [sic] or nonafluoropropyloxy.

Some examples of niobium(V) and tantalum(V) compounds are [Cp is cyclopentadienyl and Me is Nb(V) or Ta(V)]:

Me[CH₂Si(CH₃)₃]₃, Cp₂Me[(CH₂C(CH₃)₂-C₆H₅)₂], Me(=N-2,6-dimethylC₆H₃)(CH₃)₃,
Me(=N-C₆H₅)[OC(CH₃)₂][(CH₂Si(CH₃)₃)₂],
Me(=N-2,6-diisopropylC₆H₃)[(CH₂-C₆H₅)₂],
Me(=N-C₆H₅)[OCCH₂(CF₃)₂][(CH₂Si(CH₃)₃)₂], CpMe[OCCH₂(CF₃)₂][(CH₂-C₆H₅)₂],
Me(=N-2,6-diisopropylC₆H₃)[(CH₂C(CH₃)₂-C₆H₅)₂]Cl, Cp₂Me(CH₃)₂[OCH(CH₃)₂],
Me(=N-2,6-dimethylC₆H₃)[(CH₂-C₆H₅)₂], CpMe[OCH(CH₃)₂][(CH₂Si(CH₃)₃)₂],
Cp₂Me[(CH₂-C₆H₅)₂], Me[CH₂Si(CH₃)₃]Cl₂, Me[CH₂Si(CH₃)₃][OCH₂C(CH₃)₃],
Cp₂Me[3,5-dimethylC₆H₃O][CH₂Si(CH₃)₃]₂, Me(2,6-diisopropylphenyloxy)₂(CH₃)₃,
Cp₂Me(CH₃)₃, Me(2,6-dimethylphenyloxy)₂(CH₃)₃,
Me[CH₂Si(CH₃)₃][OCH(CH₃)₂], CpMe[OC(CH₃)₂][(CH₂-C₆H₅)₂] and
Cp₂Me[(CH₂Si(CH₃)₃)₂].

The niobium and tantalum compounds to be used according to the invention are known or can be prepared by known and analogous processes starting from the optionally substituted metal halides via Grignard reactions and/or substitution reactions [Schrock, R.R., Murdzek, J.S., Bazan, G.C., Robbins, J., DiMare, M., O'Regan, M., J. Am. Chem. Soc., 112:3875-3886 (1990)].

5. Other suitable photoactive one-component catalysts are titanium(IV) compounds which contain at least two methyl groups or two monosubstituted methyl groups bonded to the metal, the substituent containing no hydrogen atom in the α position. These compounds are also thermal catalysts.

The titanium(IV) compounds to be used according to the invention contain on metal atom. The methyl group or monosubstituted methyl group bonded to the metal is bonded at least twice, particularly preferably two to four times, and especially preferably twice or three times as a ligand. This ligand preferably is that of the formula XI



(XI),


in which R has the abovementioned meanings and preferred meanings.

The other valencies of the titanium atom are preferably satisfied by heat-stable neutral ligands, a large number of which are known. The number of neutral ligands may also exceed the stoichiometrically possible number (solvates). Heat stability has been explained above.

The other valencies of the titanium(IV) atoms may be satisfied by identical or different neutral ligands, for example chosen from the group consisting of secondary amines having 2 to 18 C atoms, $\text{R}_{45}\text{O}-$, $\text{R}_{45}\text{S}-$, halogen, unsubstituted or substituted cyclopentadienyl, bridged biscyclopentadienyl, tridentate monoanionic ligands and neutral ligands, for example ethers, nitriles, CO and tertiary phosphines and amines, in which the R_{45} independently of one another are linear or branched C_1 - C_{18} alkyl which is unsubstituted or substituted by C_1 - C_6 alkoxy or halogen, C_5 - or C_6 cycloalkyl which is unsubstituted or substituted by C_1 - C_6 alkyl, C_1 - C_6 alkoxy or halogen, phenyl which is unsubstituted or substituted by C_1 - C_6 alkyl, C_1 - C_6 alkoxy, C_1 - C_6 alkoxymethyl, C_1 - C_6 alkoxyethyl or halogen, or benzyl or phenylethyl which are unsubstituted or substituted by C_1 - C_6 alkyl, C_1 - C_6 alkoxy, C_1 - C_6 alkoxymethyl, C_1 - C_6 alkoxyethyl or halogen.

The definitions and preferences of R_{45} , of secondary amines, of halogen as a further ligand on the metal atoms or as substituent, of cyclopentadienyl, ethers, nitriles, tertiary amines and phosphines as neutral ligands and of tridentate monoanionic ligands have been given previously. Likewise given previously were the definitions and preferences of alkyl, alkoxy or alkyl as a substituent in alkoxymethyl or -ethyl.

In a preferred embodiment, the titanium(IV) compounds are, in particular, those of the formula XX



(XX)

in which


at least two, preferably 2 or 3, of the radicals R_{97} to R_{100} are a radical $-CH_2-R$ of the formula XI in which R has the abovementioned meanings and preferred meanings; and

the other radicals R_{97} to R_{100} are secondary amino having 2 to 18 C atoms, $R_{45}O-$, $R_{45}S-$, halogen, cyclopentadienyl or bridged biscyclopentadienyl or a neutral ligand, in which the R_{45} independently of one another are linear or branched C_1-C_{18} alkyl which is unsubstituted or substituted by C_1-C_6 alkoxy or halogen, C_5- or C_6 cycloalkyl which is unsubstituted or substituted by C_1-C_6 alkyl, C_1-C_6 alkoxy or halogen, phenyl which is unsubstituted or substituted by C_1-C_6 alkyl, C_1-C_6 alkoxy, C_1-C_6 alkoxymethyl, C_1-C_6 alkoxyethyl, di(C_1-C_6 alkyl)amino, di(C_1-C_6 alkyl)amino- C_1-C_3 alkyl or halogen, or benzyl or phenylethyl which are unsubstituted or substituted by C_1-C_6 alkyl, C_1-C_6 alkoxy, C_1-C_6 alkoxymethyl, C_1-C_6 alkoxyethyl, di(C_1-C_6 alkyl)amino, di(C_1-C_6 alkyl)amino- C_1-C_3 alkyl or halogen.

In a particularly preferred embodiment, titanium(IV) compounds of the formula XX which are used in the process according to the invention are those in which

- R_{97} to R_{100} are a radical of the formula XI $-CH_2-R$, or
 - R_{97} and R_{99} are a radical of the formula XI $-CH_2-R$, and R_{98} and R_{100} independently of one another are unsubstituted or substituted cyclopentadienyl, $R_{45}O-$ or halogen, or
 - R_{97} , R_{98} and R_{99} are a radical of the formula XI $-CH_2-R$, and R_{100} is unsubstituted or substituted cyclopentadienyl, $R_{45}O-$ or halogen,
- where R and R_{45} have the above meanings. For R and R_{45} , the above preferred meanings apply.

Titanium(IV) compounds which are especially preferably used in the process according to the invention are those of the formulae XXIa or XXIb



in which

R_v is H, $-\text{C}(\text{CH}_3)_3$, $-\text{C}(\text{CH}_3)_2\text{-C}_6\text{H}_5$, $-\text{C}_6\text{H}_5$ or $-\text{Si}(\text{C}_1\text{-C}_4\text{alkyl})_3$, and R_{97} and R_{98} independently of one another are F, Cl, Br, linear or, in particular, branched $\text{C}_1\text{-C}_4$ alkoxy which is unsubstituted or substituted by fluorine, phenoxy which is unsubstituted or substituted by $\text{C}_1\text{-C}_4$ alkyl or $\text{C}_1\text{-C}_4$ alkoxy, or cyclopentadienyl which is unsubstituted or substituted by $\text{C}_1\text{-C}_4$ alkyl. The alkoxy is particularly preferably branched alkoxy, which is unsubstituted or partly or completely substituted by F, for example *i*-propyloxy, *i*- and *t*-butyloxy, hexafluoropropyloxy and nonafluoropropyloxy.

In a preferred embodiment of the invention, the titanium(IV) compounds contain a halogen atom, in particular Cl or Br, bonded to the titanium if the radical R in the group $-\text{CH}_2\text{-R}$ is $-\text{SiR}_{38}\text{R}_{39}\text{R}_{40}$. In this case, especially preferred compounds are those of the formula XXII



in which

Y_1 is F, Cl or Br.

R_{38} , R_{39} and R_{40} independently of one another are $\text{C}_1\text{-C}_{10}$ alkyl, $\text{C}_3\text{-}$ or C_6 cycloalkyl or phenyl or benzyl which are unsubstituted or substituted by $\text{C}_1\text{-C}_6$ alkyl or $\text{C}_1\text{-C}_6$ alkoxy; and

R_{97} is the group $-\text{CH}_2\text{-SiR}_{38}\text{R}_{39}\text{R}_{40}$, F, Cl, Br, linear or, in particular, branched $\text{C}_1\text{-C}_4$ alkoxy which is unsubstituted or substituted by fluorine, phenoxy which is unsubstituted or substituted by $\text{C}_1\text{-C}_4$ alkyl or $\text{C}_1\text{-C}_4$ alkoxy, or cyclopentadienyl which is unsubstituted or substituted by $\text{C}_1\text{-C}_4$ alkyl. R_{38} , R_{39} and R_{40} are preferably $\text{C}_1\text{-C}_4$ alkyl, phenyl or benzyl, and R_{47} is preferably Cl, $\text{C}_3\text{-}$ or C_4 alkyl which is

unsubstituted or substituted by fluorine, or phenyl or benzyl which are unsubstituted or substituted by C₁-C₄alkyl or C₁-C₄alkoxy.

Some examples of titanium(IV) compounds are [Cp is cyclopentadienyl]:
 $\text{Ti}[(\text{CH}_2\text{Si}(\text{CH}_3)_3)_2]_2$, $\text{Ti}[\text{OCH}(\text{CF}_3)_2]_2[(\text{CH}_2\text{Si}(\text{CH}_3)_3)_2]$, $\text{CpTi}[(\text{CH}_2\text{C}(\text{CH}_3)_2\text{-C}_6\text{H}_5)_2]\text{Cl}$,
 $\text{CpTi}[(\text{CH}_2\text{-C}_6\text{H}_5)_3]$, $\text{TiCl}_2[(\text{CH}_2\text{Si}(\text{CH}_3)_3)_2]$, $[\text{OCH}(\text{CF}_3)_2]\text{Ti}[(\text{CH}_2\text{-C}_6\text{H}_5)_2]$,
 $\text{CpBrTi}[(\text{CH}_2\text{C}(\text{CH}_3)_2\text{-C}_6\text{H}_5)_2]$, $\text{CpTi}[2,6\text{-dimethylC}_6\text{H}_3\text{O}][(\text{CH}_2\text{Si}(\text{CH}_3)_3)_2]$,
 $\text{Ti}[\text{OCH}(\text{CH}_3)_2]_2[(\text{CH}_2\text{-C}_6\text{H}_5)_2]$, $\text{CpTi}[\text{OCH}(\text{CH}_3)_2][(\text{CH}_2\text{Si}(\text{CH}_3)_3)_2]$,
 $\text{CpTi}[\text{OCH}(\text{CF}_3)_2][(\text{CH}_2\text{-C}_6\text{H}_5)_2]$, $\text{CpTi}(\text{methyl})_3$, $\text{CpTi}(\text{methyl})_2[\text{OCH}(\text{CH}_3)_2]$,
 $\text{Ti}[(\text{CH}_2\text{Si}(\text{CH}_3)_3)_2]\text{Br}_2$, $\text{Ti}(2,6\text{-dimethylphenyloxy})_2(\text{CH}_3)_2$, $\text{Cp}_2\text{Ti}(\text{CH}_3)_2$,
 $\text{Ti}[(\text{CH}_2\text{Si}(\text{CH}_3)_3)_2][\text{OCH}(\text{CH}_3)]$ and $\text{Ti}(2,6\text{-diisopropylphenyloxy})_2(\text{CH}_3)_2$.

The titanium(IV) compounds to be used according to the invention are known or can be prepared by known and analogous processes starting from the metal halides via Grignard reactions or other known substitution reactions [see Clauss, K., Bestian, H., Justus Liebigs Ann. Chem. 654:8-19 (1962)].

6. Other suitable photocatalytically active compounds are ruthenium or osmium compounds which contain at least one phosphine group, at least one photolabile ligand and optionally neutral ligands bonded to the metal atom, 2 to 5 ligands in total being bonded, and which contain acid anions for charge balancing. In total in the context of the invention means the sum of the phosphine groups, photolabile ligands and neutral ligands. The neutral ligands are also called non-photolabile ligands. Preferably 2 to 4, and particularly preferably 2 or 3 ligands are bonded in total.

These osmium compounds are also thermally active catalysts. The ruthenium compounds are thermal catalysts if the phosphine group contains no linear alkyl or alkoxy groups, but bulky groups, for example secondary and tertiary alkyl or alkoxy groups (i-propyl, i- and t-butyl), or cycloalkyl groups, or phenyl groups or phenyloxy groups which are unsubstituted or substituted by 1 to 3 C₁-C₄alkyl or -alkoxy.

The phosphine group is preferably tertiary phosphines and phosphites having 3 to 40, more preferably 3 to 30, and particularly preferably 3 to 24 C atoms.

The other valencies of the ruthenium and osmium are preferably satisfied by heat-stable neutral ligands, a very large number of which are known. The number of neutral ligands can also exceed the stoichiometrically possible number (solvates).

The ruthenium and osmium compounds to be used according to the invention can contain a monophosphine bonded one to three times, and preferably two or three times, and a diphosphine bonded once to the metal atom. Preferably 1 to 2 photolabile ligands are bonded in the ruthenium and osmium catalysts. The phosphine ligands preferably are those of the formulae XXIII and XXIIIa



in which R_{91} , R_{92} and R_{93} independently of one another are H, $\text{C}_1\text{-C}_{20}$ alkyl, $\text{C}_1\text{-C}_{20}$ alkoxy, $\text{C}_4\text{-C}_{12}$ cycloalkyl or cycloalkoxy which are unsubstituted or substituted by $\text{C}_1\text{-C}_6$ alkyl, $\text{C}_1\text{-C}_6$ haloalkyl or $\text{C}_1\text{-C}_6$ alkoxy or $\text{C}_6\text{-C}_{18}$ aryl or $\text{C}_6\text{-C}_{18}$ aryloxy which are unsubstituted or substituted by $\text{C}_1\text{-C}_6$ alkyl, $\text{C}_1\text{-C}_6$ haloalkyl or $\text{C}_1\text{-C}_6$ alkoxy, or $\text{C}_7\text{-C}_{18}$ aralkyl or $\text{C}_7\text{-C}_{18}$ aralkyloxy which are unsubstituted or substituted by $\text{C}_1\text{-C}_6$ alkyl, $\text{C}_1\text{-C}_6$ haloalkyl or $\text{C}_1\text{-C}_6$ alkoxy; the radicals R_{91} and R_{92} together are tetra- or pentamethylene or tetra- or pentamethylenedioxy which are unsubstituted or substituted by $\text{C}_1\text{-C}_6$ alkyl, $\text{C}_1\text{-C}_6$ haloalkyl or $\text{C}_1\text{-C}_6$ alkoxy, or tetra- or pentamethylene or tetra- or pentamethylenedioxy which are unsubstituted or substituted by $\text{C}_1\text{-C}_6$ alkyl, $\text{C}_1\text{-C}_6$ haloalkyl or $\text{C}_1\text{-C}_6$ alkoxy and fused with 1 or 2 1,2-phenylene, or tetramethylenedioxy which is unsubstituted or substituted by $\text{C}_1\text{-C}_6$ alkyl, $\text{C}_1\text{-C}_6$ haloalkyl or $\text{C}_1\text{-C}_6$ alkoxy and is fused in the 1,2- and 3,4-positions with 1,2-phenylene, and R_{93} has the abovementioned meaning; and Z_1 is linear or branched $\text{C}_2\text{-C}_{12}$ alkylene which is unsubstituted or substituted by $\text{C}_1\text{-C}_4$ alkoxy, 1,2- or 1,3-cycloalkylene having 4 to 8 C atoms, which is unsubstituted or substituted by $\text{C}_1\text{-C}_4$ alkyl or $\text{C}_1\text{-C}_4$ alkoxy, or 1,2- or

1,3-heterocycloalkylene having 5 or 6 ring members and one heteroatom from the group consisting of O or N, which is unsubstituted or substituted by C₁-C₄alkyl or C₁-C₄alkoxy.

The radicals R₉₁, R₉₂ and R₉₃ are preferably identical radicals.

If R₉₁, R₉₂ and R₉₃ are substituted, the substituents are preferably C₁-C₄alkyl, C₁-C₄haloalkyl or C₁-C₄alkoxy. Halogen is preferably Cl, and particularly preferably F. Examples of preferred substituents are methyl, methoxy, ethyl, ethoxy and trifluoromethyl. R₉₁, R₉₂ and R₉₃ are preferably substituted by 1 to 3 substituents.

Alkyl R₉₁, R₉₂ and R₉₃ can be linear or branched and can preferably contain 1 to 12, more preferably 1 to 8, and particularly preferably 1 to 6 C atoms. Examples of alkyl are methyl, ethyl, n- and i-propyl, n-, i- and t-butyl, the isomers of pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl and eicosyl. Preferred examples are methyl, ethyl, n- and i-propyl, n-, i- and t-butyl, 1-, 2- or 3-pentyl and 1-, 2-, 3- or 4-hexyl.

Alkoxy R₉₁, R₉₂ and R₉₃ can be linear or branched and can preferably contain 1 to 12, more preferably 1 to 8, and particularly preferably 1 to 6 C atoms. Examples of alkoxy are methoxy, ethoxy, n- and i-propyloxy, n-, i- and t-butyloxy, the isomers of pentyloxy, hexyloxy, heptyloxy, octyloxy, nonyloxy, decyloxy, undecyloxy, dodecyloxy, tridecyloxy, tetradecyloxy, pentadecyloxy, hexadecyloxy, heptadecyloxy, octadecyloxy and eicosyloxy. Preferred examples are methoxy, ethoxy, n- and i-propyloxy, n-, i- and t-butyloxy, 1-, 2- or 3-pentyloxy and 1-, 2-, 3- or 4-hexyloxy.

Cycloalkyl R₉₁, R₉₂ and R₉₃ are preferably C₃-C₆cycloalkyl, and particularly preferably C₃- or C₆cycloalkyl. Some examples are cyclobutyl, cycloheptyl, cyclooctyl and, in particular, cyclopentyl and cyclohexyl. Examples of substituted cycloalkyl are methyl-, dimethyl-, trimethyl-, methoxy-, dimethoxy-, trimethoxy-, trifluoromethyl-, bistrifluoromethyl and tristrifluoromethylcyclopentyl and -cyclohexyl.

Cycloalkyloxy R_{91} , R_{92} and R_{93} are preferably C_3 - C_6 cycloalkyloxy, and particularly preferably C_3 - or C_6 cycloalkyloxy. Some examples are cyclobutyloxy, cycloheptyloxy, cyclooctyloxy and, in particular, cyclopentyloxy and cyclohexyloxy. Examples of substituted cycloalkyl are methyl-, dimethyl-, trimethyl-, methoxy-, dimethoxy-, trimethoxy-, trifluoromethyl-, bistrifluoromethyl and trifluoromethylcyclopentyloxy and -cyclohexyloxy.


Aryl R_{91} , R_{92} and R_{93} are preferably C_6 - C_{12} aryl and particularly preferably phenyl or naphthyl. Examples of substituted aryl are methyl-, dimethyl-, trimethyl-, methoxy-, dimethoxy-, trimethoxy-, trifluoromethyl-, bistrifluoromethyl and trifluoromethylphenyl.

Aryloxy R_{91} , R_{92} and R_{93} are preferably C_6 - C_{12} aryloxy, and particularly preferably unsubstituted or substituted phenyloxy or naphthyloxy. Examples of substituted aryloxy are methyl-, dimethyl-, trimethyl-, methylisopropyl-, isopropyl-, diisopropyl-, triisopropyl-, tert-butyl-, methyl-tert-butyl-, di-tert-butyl-, tri-tert-butyl-, methoxy-, dimethoxy-, trimethoxy-, trifluoromethyl-, bistrifluoromethyl and trifluoromethylphenyloxy.


Aralkyl R_{91} , R_{92} and R_{93} are preferably C_7 - C_{13} aralkyl, the alkylene group in the aralkyl preferably being methylene. The aralkyl is particularly preferably benzyl. Examples of substituted aralkyl are methyl-, dimethyl-, trimethyl-, methoxy-, dimethoxy-, trimethoxy-, trifluoromethyl-, bistrifluoromethyl and trifluoromethylbenzyl.

Aralkyloxy R_{91} , R_{92} and R_{93} are preferably unsubstituted or substituted C_7 - C_{13} aralkyloxy, the alkylene group in the aralkyloxy preferably being methylene. The aralkyloxy is particularly preferably unsubstituted or substituted benzyloxy. Examples of substituted aralkyloxy are methyl-, dimethyl-, trimethyl-, methoxy-, dimethoxy-, trimethoxy-, trifluoromethyl-, bistrifluoromethyl and trifluoromethylbenzyloxy.

Examples of tetra- and pentamethylene which are bonded to the P atom and are unsubstituted or substituted or fused are



Other suitable phosphines are cycloaliphatics having 6 to 8 ring carbon atoms which are bridged with a $=PRa$ group, for example



in which Ra is C_1 - C_6 alkyl, cyclohexyl, benzyl, or phenyl which is unsubstituted or substituted by 1 or 2 C_1 - C_4 alkyl.

Linear or branched alkylene Z , is preferably 1,2-alkylene or 1,3-alkylene having preferably 2 to 6 C atoms, for example ethylene, 1,2-propylene or 1,2-butylenes.

Examples of cycloalkylene Z , are 1,2- and 1,3-cyclopentylene and 1,2- or 1,3-cyclohexylene. Examples of heterocycloalkylene Z , are 1,2- and 1,3-pyrrolidine, 1,2- and 1,3-piperidine, and 1,2- and 1,3-tetrahydrofuran.


In a preferred embodiment, the phosphine ligands are those of the formula XXIII in which R_{91} , R_{92} and R_{93} independently of one another are H, C_1 - C_6 alkyl, cyclopentyl or cyclohexyl which are unsubstituted or substituted by C_1 - C_4 alkyl, or phenyl which are unsubstituted or substituted by C_1 - C_4 alkyl, C_1 - C_4 alkoxy or trifluoromethyl, or benzyl which is unsubstituted or substituted by C_1 - C_4 alkyl.

C_1 - C_4 alkoxy or trifluoromethyl. Particularly preferred examples of phosphine ligands of the formula XXIII are $(C_6H_5)_3P$, $(C_6H_5CH_2)_3P$, $(C_3H_{11})_3P$, $(CH_3)_3P$.

$(C_2H_5)_3P$, $(n-C_3H_7)_3P$, $(i-C_3H_7)_3P$, $(n-C_4H_9)_3P$, $(C_6H_5)_2HP$, $(C_6H_5CH_2)_2HP$, $(C_6H_{11})_2HP$,
 $(C_2H_5)_2HP$, $(n-C_3H_7)_2HP$, $(i-C_3H_7)_2HP$, $(n-C_4H_9)_2HP$, $(C_6H_5)H_2P$,
 $(n-C_4H_9)H_2P$, $(C_6H_5CH_2)H_2P$, $(C_6H_{11})H_2P$, $(CH_3)_2HP$, $(CH_3)HP$, $(C_2H_5)H_2P$,
 $(n-C_3H_7)H_2P$, $(i-C_3H_7)H_2P$, PH_3 , (2-methyl- C_6H_4) $_3P$, (3- CH_3 - C_6H_4) $_3P$, (4- C_2H_5 -
 C_6H_4) $_3P$, (4- CH_3 - C_6H_4) $_3P$, (2,4-di- CH_3 - C_6H_3) $_3P$, (2,6-di- CH_3 - C_6H_3) $_3P$, (2- C_2H_5 -
 C_6H_4) $_3P$, (3- C_2H_5 - C_6H_4) $_3P$, (2- $n-C_3H_7$ - C_6H_4) $_3P$, (3- $n-C_3H_7$ - C_6H_4) $_3P$, (4- $n-C_3H_7$ -
 C_6H_4) $_3P$, (2- $i-C_3H_7$ - C_6H_4) $_3P$, (3- $i-C_3H_7$ - C_6H_4) $_3P$, (4- $i-C_3H_7$ - C_6H_4) $_3P$, (2- $n-C_4H_9$ -
 C_6H_4) $_3P$, (3- $n-C_4H_9$ - C_6H_4) $_3P$, (4- $n-C_4H_9$ - C_6H_4) $_3P$, (2- $i-C_4H_9$ - C_6H_4) $_3P$, (3- $i-C_4H_9$ -
 C_6H_4) $_3P$, (4- $i-C_4H_9$ - C_6H_4) $_3P$, (2- $t-C_4H_9$ - C_6H_4) $_3P$, (3- $t-C_4H_9$ - C_6H_4) $_3P$, (4- $t-C_4H_9$ -
 C_6H_4) $_3P$, (2- CH_3 -6- $t-C_4H_9$ - C_6H_3) $_3P$, (3- CH_3 -6- $t-C_4H_9$ - C_6H_3) $_3P$, (3- CH_3 -6- $t-C_4H_9$ -
 C_6H_3) $_3P$, (2,6-di- $t-C_4H_9$ - C_6H_3) $_3P$, (2,3-di- $t-C_4H_9$ - C_6H_3) $_3P$, $(C_6H_{11})_3P$, $(C_6H_{11})_2HP$,
 $(C_3H_9)_3P$, $(C_3H_9)_2HP$ and (2,4-di- $t-C_4H_9$ - C_6H_3) $_3P$.

In another preferred embodiment, the phosphine ligands correspond to the
 formula XXIII in which R_{91} , R_{92} and R_{93} independently of one another are H,
 C_1 - C_6 alkoxy, cyclopentyloxy or cyclohexyloxy which is unsubstituted or substituted
 by C_1 - C_4 alkyl, phenyloxy or phenyl which is unsubstituted or substituted by
 C_1 - C_4 alkyl, C_1 - C_4 alkoxy or trifluoromethyl, or benzyloxy which is unsubstituted or
 substituted by C_1 - C_4 alkyl, C_1 - C_4 alkyl, C_1 - C_4 alkoxy or trifluoromethyl.

Examples of phosphites are $(CH_3O)_3P$, $(C_2H_5O)_3P$, $(n-C_3H_7O)_3P$, $(i-C_3H_7O)_3P$,
 $(n-C_4H_9O)_3P$, $(i-C_4H_9O)_3P$, $(t-C_4H_9O)_3P$, $(C_6H_5O)_3P$, (3- CH_3 -6- $t-C_4H_9$ - C_6H_3O) $_3P$, (2-
 CH_3 - C_6H_4O) $_3P$, (3- CH_3 - C_6H_4O) $_3P$, (4- CH_3 - C_6H_4O) $_3P$, (2,4-di- CH_3 - C_6H_3O) $_3P$, (2,6-di-
 CH_3 - C_6H_3O) $_3P$, (2- C_2H_5 - C_6H_4O) $_3P$, (3- C_2H_5 - C_6H_4O) $_3P$, (4- C_2H_5 - C_6H_4O) $_3P$, (2- n -
 C_3H_7 - C_6H_4O) $_3P$, (3- $n-C_3H_7$ - C_6H_4O) $_3P$, (4- $n-C_3H_7$ - C_6H_4O) $_3P$,
 $(2-i-C_3H_7$ - C_6H_4O) $_3P$, (3- $i-C_3H_7$ - C_6H_4O) $_3P$, (4- $i-C_3H_7$ - C_6H_4O) $_3P$,
 $(2-n-C_4H_9$ - C_6H_4O) $_3P$, (3- $n-C_4H_9$ - C_6H_4O) $_3P$, (4- $n-C_4H_9$ - C_6H_4O) $_3P$,
 $(2-i-C_4H_9$ - C_6H_4O) $_3P$, (3- $i-C_4H_9$ - C_6H_4O) $_3P$, (4- $i-C_4H_9$ - C_6H_4O) $_3P$,
 $(2-CH_3$ -6- $t-C_4H_9$ - C_6H_3O) $_3P$, (2,3-di- $t-C_4H_9$ - C_6H_3O) $_3P$, ((2,6-di- $t-C_4H_9$ - C_6H_3O) $_3P$,
 $3-t-C_4H_9$ - C_6H_4O) $_3P$, (3- CH_3 -6- $t-C_4H_9$ - C_6H_3O) $_3P$, (2,4-di- $t-C_4H_9$ - C_6H_3O) $_3P$,
 $(4-t-C_4H_9$ - C_6H_4O) $_3P$, (2- $t-C_4H_9$ - C_6H_4O) $_3P$ and phosphites of the formula



in which Ra is C₁-C₆alkyl, cyclohexyl, benzyl, or phenyl which is unsubstituted or substituted by 1 or 2 C₁-C₄alkyl.

Particularly preferred phosphines are tri-*i*-propylphosphine, tri-*t*-butylphosphine, tricyclopentylphosphine and tricyclohexylphosphine.

Organic or inorganic compounds, atoms or ions which are coordinated to a metal centre are designated as ligands for the ruthenium and osmium compounds to be used according to the invention.

The meanings and preferred meanings of photolabile ligands and non-photolabile ligands (also called highly coordinating ligands) have been mentioned above.

In a preferred embodiment, the Ru and Os catalysts to be used according to the invention contain only photolabile ligands, phosphine groups and anions for charge balancing. The catalysts which are especially preferred are those which contain an arene group as a photolabile ligand, a tertiary phosphine group, and mono- or divalent anions for charge balancing.

Suitable anions of inorganic or organic acids are, for example, hydride (H⁻), halide (for example F⁻, Cl⁻, Br⁻ and I⁻), the anion of an oxygen acid, and BF₄⁻, PF₆⁻, SbF₆⁻ or AsF₆⁻. It should be mentioned that the abovementioned cyclopentadienyl is a ligand and anion.

Other suitable anions are C₁-C₁₂⁻, preferably C₁-C₆⁻, and particularly preferably C₁-C₄alcoholates, which, in particular, are branched, for example corresponding to

the formula $R_1R_2R_3C-O^-$, in which R_1 is H or C_1-C_{10} alkyl, R_2 is C_1-C_{10} alkyl and R_3 is C_1-C_{10} alkyl or phenyl, and the sum of the C atoms of R_1 , R_2 and R_3 is 11. Examples are, in particular, i-propyloxy and t-butyloxy.

Other suitable anions are $C_3-C_{18}^-$, preferably $C_3-C_{14}^-$ and particularly preferably C_3-C_{12} acetylides, which can correspond to the formula $R_4-C\equiv C^-$, in which R_4 is C_1-C_{18} alkyl, preferably α -branched C_3-C_{12} alkyl, for example of the formula $R_1R_2R_3C-$, or are [sic] phenyl or benzyl which are unsubstituted or substituted by 1 to 3 C_1-C_4 alkyl or C_1-C_4 alkoxy. Some examples are i-propyl-, i- and t-butyl-, phenyl-, benzyl-, 2-methyl-, 2,6-dimethyl-, 2-i-propyl-, 2-i-propyl-6-methyl-, 2-t-butyl-, 2,6-di-t-butyl- and 2-methyl-6-t-butylphenylacetylide.

The meanings and preferred meanings of anions of oxygen acids have been mentioned above.

H^- , F^- , Cl^- , Br^- , BF_4^- , PF_6^- , SbF_6^- , AsF_6^- , $CF_3SO_3^-$, $C_6H_5SO_3^-$, 4-methyl- $C_6H_5SO_3^-$, 2,6-dimethyl- $C_6H_5SO_3^-$, 2,4,6-trimethyl- $C_6H_5SO_3^-$ and 4- $CF_3-C_6H_5SO_3^-$ and cyclopentadienyl (Cp^-) are particularly preferred.

The number of the non-photolabile ligands depends on the number of the phosphine groups, the size of the non-photolabile ligands and the number of photolabile ligands.

In a preferred embodiment, the ruthenium and osmium compounds are particularly preferably those of one of the formulae XXIV to XXIVf





in which

R_{97} is a tertiary phosphine of the formula XXIII or XXIIIa;

Me is Ru or Os;

n is the numbers 1, 2 or 3;

Z is the anion of an inorganic or organic acid;

(a) L_9 is an arene or heteroarene ligand;


(b) L_9 is a monovalent photolabile ligand which is different to L_8 ; and


(c) L_{10} is a monovalent non-photolabile ligand.

For R_{97} , L_8 , L_9 and L_{10} , the preferred meanings mentioned above for the individual meanings apply.

In the formulae XXIV to XXIVf, n is preferably 1 or 2, and especially 1. For R_{97} , the preferred meanings mentioned for the phosphine ligands of the formula XXIII apply, and these are, in particular, tertiary phosphines.

Ruthenium and osmium compounds which are especially preferably used in the process according to the invention are those of one of the formulae XXV to XXVf





in which

Me is Ru or Os;

Z in formulae XXV to XXVe is H⁺, cyclopentadienyl, Cl⁻, Br⁻, BF₄⁻, PF₆⁻, SbF₆⁻, AsF₆⁻, CF₃SO₃⁻, C₆H₅-SO₃⁻, 4-methyl-C₆H₅-SO₃⁻, 3,5-dimethyl-C₆H₅-SO₃⁻,

2,4,6-trimethyl-C₆H₅-SO₃⁻ and 4-CF₃-C₆H₅-SO₃⁻ and in formula XXVf is H⁺, cyclopentadienyl, BF₄⁻, PF₆⁻, SbF₆⁻, AsF₆⁻, CF₃SO₃⁻, C₆H₅-SO₃⁻, 4-methyl-C₆H₅-SO₃⁻, 2,6-dimethyl-C₆H₅-SO₃⁻, 2,4,6-trimethyl-C₆H₅-SO₃⁻ or 4-CF₃-C₆H₅-SO₃⁻;

R₉₄, R₉₅ and R₉₆ independently of one another are C₁-C₆alkyl, or cyclopentyl or cyclohexyl or cyclopentyloxy or cyclohexyloxy which are unsubstituted or substituted by 1 to 3 C₁-C₄alkyl, or phenyl or benzyl or phenyloxy or benzyloxy which are unsubstituted or substituted by 1 to 3 C₁-C₄alkyl;

L₉ is C₆-C₁₀arene or C₅-C₁₀heteroarene which are unsubstituted or substituted by 1 to 3 C₁-C₄alkyl, C₁-C₄alkoxy, -OH, -F or Cl;

L₉ is C₁-C₆alkyl-CN, benzonitrile or benzylnitrile; and

L₁₀ is H₂O or C₁-C₆alkanol.

Preferred arenes and heteroarenes are benzene, toluene, xylene, trimethylbenzene, naphthalene, biphenyl, anthracene, acenaphthene, fluorene, phenanthrene, pyrene, chrysene, fluoranthrene, furan, thiophene, pyrrole, pyridine, γ-pyran, γ-thiopyran, pyrimidine, pyrazine, indole, coumarone, thionaphthen, carbazole, dibenzofuran, dibenzothiophene, pyrazole, imidazole, benzimidazole, xazole, thiazole, isoxazole, isothiazole, quinoline, isoquinoline, acridine, chromene, phenazine, phenoxazine, phenothiazine, triazine, thianthr ne and purin. More preferred arenes and heteroarenes are benzene, naphthalen, cumene, thiophene and benzothiophene. The aren is especially preferably benzene or a benzene substituted by C₁-C₄alkyl, for example toluene, xylene.

isopropylbenzene, tert-butylbenzene or cumene, and the heteroarene is preferably thiophene.

If the preparation of the ruthenium and osmium catalysts is carried out in solvents which can coordinate to a metal atom, for example alkanols, solvated Ru/Os cation complexes can form, and these are also included in the context of the use of according to the invention.

Some examples of ruthenium and osmium compounds to be used according to the invention are [Tos is tosylate]: $(C_6H_{11})_2HPRu(p\text{-cumene})Cl_2$, $(C_6H_{11})_3PRu(p\text{-cumene})Cl_2$, $(C_6H_{11})_3PRu(p\text{-cumene})(Tos)_2$, $(C_6H_{11})_3PRu(p\text{-cumene})Br_2$, $(C_6H_{11})_3PRu(p\text{-cumene})ClF$, $(C_6H_{11})_3PRu(C_6H_6)(Tos)_2$, $(C_6H_{11})_3PRu(CH_3-C_6H_3)(Tos)_2$, $(C_6H_{11})_3PRu(i-C_3H_7-C_6H_3)(Tos)_2$, $(C_6H_{11})_3PRu(chrysene)(Tos)_2$, $(C_6H_{11})_3PRu(biphenyl)(Tos)_2$, $(C_6H_{11})_3PRu(anthracene)(Tos)_2$, $(C_6H_{11})_3PRu(C_{10}H_8)(Tos)_2$, $(i-C_3H_7)_3PRu(p\text{-cumene})Cl_2$, $(CH_3)_3PRu(p\text{-cumene})Cl_2$, $(n-C_4H_9)_3PRu(p\text{-cumene})Cl_2$, $[(C_6H_{11})_3P]_2Ru(CH_3-CN)(Tos)_2$, $(C_6H_{11})_3PRu(CH_3-CN)(C_2H_5-OH)(Tos)_2$, $(C_6H_{11})_3PRu(p\text{-cumene})(CH_3-CN)_2(PF_6)_2$, $(C_6H_{11})_3PRu(p\text{-cumene})(CH_3-CN)_2(Tos)_2$, $(n-C_4H_9)_3PRu(p\text{-cumene})(CH_3-CN)_2(Tos)_2$, $(C_6H_{11})_3PRu(CH_3CN)Cl_2$, $(C_6H_{11})_3PRu(CH_3-CN)_2Cl_2$, $(C_6H_{11})_3PRu(p\text{-cumene})(C_2H_5OH)(BF_4)_2$, $(C_6H_{11})_3PRu(p\text{-cumene})(C_2H_5OH)_2(BF_4)_2$, $(C_6H_{11})_3PRu(p\text{-cumene})(C_2H_5OH)_2(PF_6)_2$, $(C_6H_{11})_3PRu(C_6H_6)(C_2H_5OH)_2(Tos)_2$, $(C_6H_{11})_3POs(p\text{-cumene})Cl_2$, $(i-C_3H_7)_3POs(p\text{-cumene})Cl_2$, $(CH_3)_3POs(p\text{-cumene})Cl_2$, $(C_6H_5)_3POs(p\text{-cumene})Cl_2$, $[(C_6H_{11})_3P]_3Ru(p\text{-cumene})Cl_2$ and $RuCl_2(p\text{-cumene})[(C_6H_{11})_2PCH_2CH_2P(C_6H_{11})_2]$.

The ruthenium and osmium compounds to be used according to the invention are known or can be prepared by known and analogous processes starting from the metal halides (for example MeX_3 or $[MeareneX_2]_2$) and reaction with phosphines and ligand-forming agents.

7. Further suitable one-component catalysts are divalently cationic ruthenium or osmium compounds with a metal atom to which 1 to 3 tertiary phosphine ligands with, in the case of ruthenium compounds, sterically bulky substituents, if desired,

non-photolabile neutral ligands and anions are bonded for charge balancing, with the proviso that in ruthenium(trisphenylphosphine)dihalides or -hydride-halides the phenyl groups are substituted by C_1-C_{18} alkyl, C_1-C_{18} haloalkyl or C_1-C_{18} alkoxy.

The ruthenium and osmium compounds preferably contain 2 or 3 tertiary phosphine groups. Phosphine groups in the context of the invention are understood as meaning tertiary phosphines and phosphites. The number of additional non-photolabile neutral ligands depends on the one hand on the number of phosphine and phosphite ligands, and on the other hand on the valency of the neutral ligands. Monovalent or divalent neutral ligands are preferred.

In a preferred embodiment, the divalently cationic ruthenium and osmium compounds to be used according to the invention contain 3 phosphine or phosphite groups and two monovalent anions for charge balancing; or 3 phosphine or phosphite groups, two monovalent or one divalent non-photolabile neutral ligand, and two monovalent anions for charge balancing; or 2 phosphine or phosphite groups, one monoanionic, additionally monovalent non-photolabile neutral ligands and one monovalent anion for charge balancing.

The meanings and preferred meanings of non-photolabile ligands (also called highly coordinating ligands) have been mentioned above.

Sterically bulky substituents in the context of the invention are understood as meaning those which shield the ruthenium and osmium atoms sterically. It has thus been found, surprisingly, that linear alkyl groups as substituents in the phosphine and phosphite ligands result in ruthenium compounds without any thermal activity for the metathesis polymerization of strained cycloolefins. It has also been observed that in the case of osmium compounds, surprisingly, linear alkyl groups as substituents in the phosphine and phosphite ligands have an excellent thermocatalytic activity for the metathesis polymerization of strained cycloolefins; however, phosphine and phosphite ligands with sterically bulky substituents are also preferably used for the osmium compounds. It has furthermore been found that the steric shielding of triphenylphosphine ligands in

ruthenium dihalides and ruthenium hydride-halides is inadequate, and such catalysts have only a moderate catalytic activity for the metathesis polymerization of strained cycloolefins. The catalytic activity can surprisingly be increased considerably if the tertiary phosphine groups contain phenyl substituted by alkyl or alkoxy groups.

The meanings and preferred meanings of phosphine ligands have been mentioned above. Alkyl R_{91} , R_{92} and R_{93} are particularly preferably α -branched alkyl, for example of the formula $-CR_bR_cR_d$, in which R_b is H or C_1 - C_{12} alkyl, R_c is C_1 - C_{12} alkyl, and R_d is C_1 - C_{12} alkyl or phenyl which is unsubstituted or substituted by C_1 - C_4 alkyl or C_1 - C_4 alkoxy, and the sum of the C atoms in the radical $-CR_bR_cR_d$ is 3 to 18. Examples of alkyl are i-propyl, i- and t-butyl, 1-methyl- or 1,1-dimethylprop-1-yl, 1-methyl- or 1,1-dimethylbut-1-yl, 1-methyl- or 1,1-dimethylpent-1-yl, 1-methyl- or 1,1-dimethylhex-1-yl, 1-methyl- or 1,1-dimethylhept-1-yl [sic], 1-methyl- or 1,1-dimethyloct-1-yl, 1-methyl- or 1,1-dimethylnon-1-yl, 1-methyl- or 1,1-dimethyldec-1-yl, 1-methyl- or 1,1-dimethylundec-1-yl, 1-methyl- or 1,1-dimethyldodec-1-yl, 1-methyl- or 1,1-dimethyltridec-1-yl, 1-methyl- or 1,1-dimethyltetradec-1-yl, 1-methyl- or 1,1-dimethylpentadec-1-yl, 1-methyl- or 1,1-dimethylhexadec-1-yl, 1-methylheptadec-1-yl, phenyl-dimethyl-methyl. Preferred examples are i-propyl, i- and t-butyl.

In the case of the osmium compounds used, R_{91} , R_{92} and R_{93} can also be linear alkyl having 1 to 18, preferably 1 to 12, more preferably 1 to 8, and particularly preferably 1 to 6 C atoms, for example methyl, ethyl, n-propyl, n-butyl, n-pentyl, n-hexyl, n-heptyl and n-octyl.

Alkoxy R_{91} , R_{92} and R_{93} can contain 3 to 12, more preferably 3 to 8, and particularly preferably 3 to 6 C atoms. The alkoxy is particularly preferably α -branched alkoxy, for example of the formula $-OCR_bR_cR_d$, in which R_b is H or C_1 - C_{12} alkyl, R_c is C_1 - C_{12} alkyl, and R_d is C_1 - C_{12} alkyl or phenyl which is unsubstituted or substituted by C_1 - C_4 alkyl or C_1 - C_4 alkoxy, and the sum of the C atoms in the radical $-OCR_bR_cR_d$ is 3 to 18. Examples of alkoxy are i-propyloxy, i- and t-butyloxy, 1-methyl- or 1,1-dimethylprop-1-oxyl, 1-methyl- or 1,1-dimethylbut-1-oxyl, 1-

methyl- or 1,1-dimethylpent-1-oxyl, 1-methyl- or 1,1-dimethylhex-1-oxyl, 1-methyl- or 1,1-dimethylhept-1-oxyl, 1-methyl- or 1,1-dimethyloct-1-oxyl, 1-methyl- or 1,1-dimethylnon-1-oxyl, 1-methyl- or 1,1-dimethyldodec-1-oxyl, 1-methyl- or 1,1-dimethylundec-1-oxyl, 1-methyl- or 1,1-dimethyltridec-1-oxyl, 1-methyl- or 1,1-dimethyltetradec-1-oxyl, 1-methyl- or 1,1-dimethylpentadec-1-oxyl, 1-methyl- or 1,1-dimethylhexadec-1-oxyl, 1-methylheptadec-1-oxyl, phenyl-dimethyl-methyl. Preferred examples are i-propyloxy, i- and t-butyloxy.

In the case of the osmium compounds used, R_{91} , R_{92} and R_{93} can also be linear alkoxy having 1 to 18, preferably 1 to 12, more preferably 1 to 3, and particularly preferably 1 to 6 C atoms, for example methoxy, ethoxy, n-propyloxy, n-butyloxy, n-pentyloxy, n-hexyloxy, n-heptyloxy and n-octyloxy.

Cycloalkyl R_{91} , R_{92} and R_{93} are preferably C_3 - C_6 cycloalkyl, and particularly preferably C_5 - or C_6 cycloalkyl. Some examples are cyclobutyl, cycloheptyl, cyclooctyl and in particular, cyclopentyl and cyclohexyl, which are preferably unsubstituted or substituted by 1 to 3 alkyl, haloalkyl or alkoxy groups.

Cycloalkyloxy R_{91} , R_{92} and R_{93} are preferably C_3 - C_6 cycloalkyloxy, and particularly preferably C_5 - or C_6 cycloalkyloxy. Some examples are cyclobutyloxy, cycloheptyloxy, cyclooctyloxy and, in particular, cyclopentyloxy and cyclohexyloxy, which are preferably unsubstituted or substituted by 1 to 3 alkyl, haloalkyl or alkoxy groups.

In a preferred embodiment, the phosphine ligands are those of the formula XXIII in which R_{91} , R_{92} and R_{93} independently of one another are α -branched C_3 - C_6 alkyl, cyclopentyl or cyclohexyl which are unsubstituted or substituted by C_1 - C_4 alkyl, or phenyl which is unsubstituted or substituted by C_1 - C_4 alkyl, C_1 - C_4 alkyl [sic] C_1 - C_4 alkoxy or trifluoromethyl. Particularly preferred examples of phosphine ligands of the formula XXIII are $(C_6H_5)_3P$, $(C_5H_9)_3P$, $(C_4H_9)_3P$, $(i-C_3H_7)_3P$, $(i-C_4H_9)_3P$, $(t-C_4H_9)_3P$, $[C_2H_5-CH(CH_3)]_3P$, $[C_2H_5-C(CH_3)_2]_3P$, $(2\text{-methylphenyl})_3P$, $(2,3\text{-dimethylphenyl})_3P$, $(2,4\text{-dimethylphenyl})_3P$.

(2,6-dimethylphenyl)₃P, (2-methyl-4-i-propylphenyl)₃P,
 (2-methyl-3-i-propylphenyl)₃P, (2-methyl-5-i-propylphenyl)₃P,
 (2,4-di-t-butylphenyl)₃P, (2-methyl-6-i-propylphenyl)₃P,
 (2-methyl-3-t-butylphenyl)₃P, (2,5-di-t-butylphenyl)₃P,
 (2-methyl-4-t-butylphenyl)₃P, (2-methyl-5-i-butylphenyl)₃P,
 (2,3-di-t-butylphenyl)₃P and (2,6-di-t-butylphenyl)₃P.

In another preferred embodiment, the phosphite ligands are those of the formula XXIII in which R₃₁, R₃₂ and R₃₃ independently of one another are α-branched C₃-C₆alkoxy, or cyclopentyloxy or cyclohexyloxy which are unsubstituted or substituted by C₁-C₄alkyl; or phenoxy which is unsubstituted or substituted by C₁-C₄alkyl, C₁-C₄alkoxy or trifluoromethyl. Examples of phosphites have been mentioned above.

Examples and preferred meanings of suitable anions have been mentioned above.

In a preferred embodiment, the ruthenium and osmium compounds are particularly preferably those of the formulae XXVI, XXVIa, XXVIb, XXVIc or XXVI d



in which

Me is Ru or Os;

Y_1 is the anion of a monobasic acid;

L_{11} is a phosphine of the formula XXIII or XXIIIa;

L_{12} is a neutral ligand;

L_{13} is cyclopentadienyl which is unsubstituted or substituted by C_1 - C_4 alkyl; and

L_{14} is CO.

For the individual meanings of L_{11} , L_{12} , L_{13} and Y_1 , the above preferred meanings apply.

In a particularly preferred embodiment, in formula XXVI L_{12} is a C_1 - C_4 alkanol, in formula XXVib, Y_1 is Cl or Br, in formula XXVlc Y_1 is H, and in the formulae XXVI to XXVlc L_{11} is tri-*i*-propylphosphine, tricyclohexylphosphine, triphenylphosphine or triphenylphosphine which is substituted by 1 to 3 C_1 - C_4 alkyl in the phenyl groups.

Some examples of ruthenium and osmium compounds to be used according to the invention are $[(C_6H_{11})_3P]_2Ru(CH_3OH)_2(Tos)_2$, $[(C_6H_{11})_3P]_2RuCl_2$ and $[(C_6H_{11})_3P]_2Ru(CH_3OH)_2$.

The ruthenium and osmium compounds to be used according to the invention are known or can be prepared by known and analogous processes starting from the metal halides (for example MeX_3 , $[Me(diolefin)X_2]_2$ or $[Me-areneX_2]_2$) and reaction with phosphines and ligand-forming agents.

The compositions according to the invention are surprisingly stable to storage and can be marketed as such. However, it is also possible to mix the individual components together before processing. If air- and/or moisture-sensitive catalysts are used, storage with exclusion of air and moisture is advisable. Since the novel crosslinking principle is not based on a free radical, anionic or cationic reaction, practically no interruption or slowing of the reaction is observed on carrying out the polymerization in air, which offers considerable advantages during processing, for example no extensive protective precautions. The possibility of using solvent-free systems in the case of liquid polymers of low molecular weight or in the case of

solutions with reactive strained cycloolefins which are capable of metathesis polymerization as comonomers is a great surprising advantage.

The invention also relates to a process for the preparation of crosslinked polymers by metathesis polymerization, wherein a composition of

- (a) a catalytic amount of a one-component catalyst for metathesis polymerization and
- (b) at least one polymer with strained cycloalkenylene radicals bonded in the polymer backbone, alone or mixed with strained cycloolefins,
- (c) is polymerized by heating,
- (d) is polymerized by irradiation,
- (e) is polymerized by heating and irradiation,
- (f) the one-component catalyst is activated by brief heating and the polymerization is brought to completion by irradiation, or
- (g) the one-component catalyst is activated by brief irradiation and the polymerization is brought to completion by heating.

Heating can mean a temperature of 50 to 300°C, preferably 60 to 250°C, particularly preferably 100 to 200°C, and especially preferably 60 to 150°C. The polymerization times essentially depend on the catalyst activity, and the times can extend from several seconds to minutes and hours.

In the process according to the invention, it is not necessary to maintain the irradiation of the reaction mixture over the entire duration of the reaction. Once the polymerization has been initiated photochemically, the subsequent course of the reaction takes place independently, even in the dark. Irradiation is advantageously carried out with light of a wavelength in the range from 50 nm to 1000 nm, preferably in the range from 200 nm to 500 nm and especially preferably in the UV range. The irradiation time depends on the nature of the light source. Suitable sources of irradiation are, for example, the sun, sources of laser radiation, X-ray radiation and, in particular, sources of UV radiation. UV lasers or UV lamps are preferably employed according to the invention. The irradiation of the catalyst can be carried out both before, during and after the addition of the monomer.

Suitable irradiation times are from one second to several hours, in particular minutes to hours. The sequence of the addition of monomers and catalysts is not critical. The monomer can be both initially introduced into the reaction vessel and added after introduction of the catalyst. Likewise, the catalyst can be pre-irradiated and then added to the monomer. It is furthermore also possible to irradiate the solution comprising catalyst and monomer.

In the case of irradiation using photoactive catalysts, the process according to the invention is preferably carried out at room temperature to slightly elevated temperature. An increase in temperature in this case essentially serves to increase the rate of reaction. At the temperatures chosen to accelerate the reaction, a photopolymerization therefore also chiefly takes place. However, it should be mentioned that the catalysts can be converted into thermoactive catalysts by adequate irradiation or elevated temperature. It is furthermore to be noted that some catalysts are capable of initiating the metathesis polymerization both thermally and [lacuna] irradiation.

In particular, the process according to the invention is carried out with irradiation preferably at temperatures of -20 to $+110^{\circ}\text{C}$, particularly preferably 20 to 80°C .

The irradiation time essentially depends on the desired reaction procedure. Brief irradiation is chosen, for example, if the polymerization is only to be initiated by irradiation and is to be brought to completion by heating. This can mean an irradiation time of up to 60 seconds, preferably 5 to 60 seconds, and particularly preferably 10 to 40 seconds. A longer irradiation time is chosen, for example, if the polymerization is to be carried out chiefly with irradiation and the final polymerization is to be brought to completion only by after-heating.

A quite particular and surprising advantage of the process according to the invention is that on -component catalysts used act as thermal catalysts after the irradiation. This results in the possibility of continuing the polymerization and

which has a short irradiation time which

offers economic and industrial advantages in various areas of production of shaped articles or coatings.

The present invention also relates to crosslinked metathesis polymers of a polymer with strained cycloalkenylene radicals bonded in the polymer backbone, alone or as a mixture with strained cycloolefins.

The present invention also relates to metathesis polymers, crosslinked using a one-component catalyst, from a composition comprising

(a) a catalytic amount of a one-component catalyst for the metathesis polymerization and

(b) at least one polymer with strained cycloalkenylene radicals bonded in the polymer backbone, alone or as a mixture with strained cycloolefins.

Materials for production of shaped articles by machining, or shaped articles of all types directly, as well as coatings and relief images can be produced with the process according to the invention. The invention also relates to shaped articles of crosslinked metathesis polymers of the composition according to the invention.

The polymers according to the invention can have very different properties, depending on the monomer used. Some are distinguished by a very high permeability to oxygen, low dielectric constants, good heat stability and low absorption of water. Others have outstanding optical properties, for example high transparency and low refractive indices. Furthermore, the low shrinkage is to be singled out in particular. They can therefore be used in very different industrial fields.

As layers on the surfaces of carrier materials, the compositions according to the invention are distinguished by a high adhesive strength. The coated materials are furthermore distinguished by a high surface smoothness and gloss. Among the good mechanical properties, the low shrinkage and the high impact strength are to be singled out in particular, and also the heat stability. The ease of removal from

the moulds during processing in moulds and the high resistance to solvents are furthermore to be mentioned.

These polymers are suitable for the production of medical equipment, implants or contact lenses; for the production of electronic components; as binders for coatings; as photocurable compositions for model construction or as adhesives for gluing substrates of low surface energy (for example Teflon, polyethylene and polypropylene, silicone rubber), and as photopolymerizable compositions in stereolithography. The compositions according to the invention can also be used for the production of coatings by photopolymerization, it being possible for on the one hand clear (transparent) and even pigmented compositions to be used. Both white and coloured pigments can be used.

The photocurable compositions according to the invention are particularly suitable for the production of protective coatings and relief images. The invention also relates to a variant of the process according to the invention for the production of coated materials or relief images on carrier materials, in which a composition according to the invention and, if desired, a solvent are applied as a layer to a carrier, for example by dipping, brushing, pouring, rolling, knife-coating or whirler coating processes, the solvent is removed, if desired, and the layer is irradiated or heated for polymerization, or the layer is irradiated through a photomask and the non-irradiated portions are then removed with a solvent. This can then also be followed by heat treatment. Using this process, surfaces of substrates can be modified or protected, or, for example, printed circuits, printing plates or printing rolls can be produced. In the production of printed circuits, the compositions according to the invention can also be employed as solder resists. Other possible uses are the production of screen printing masks and the use as radiation-curable printing inks for offset, screen and flexographic printing. Because of the high adhesion and the low absorption of water, the protective coatings on carrier materials are especially suitable for corrosion protection.

The present invention furthermore relates to a coated carrier material, wherein a layer of a composition according to the invention is applied to a substrate.

The present invention also relates to a coated substrate with a cured layer of a composition according to the invention. The exceptionally high adhesive strength of the layers, even on metal surfaces, is to be singled out in particular, even when the products are pure hydrocarbon polymers.

Suitable substrates (carrier materials) are, for example, those of glass, minerals, ceramics, plastics, wood, semimetals, metals, metal oxides and metal nitrides. The layer thicknesses essentially depend on the desired use, and can be, for example, 0.1 to 1000 μm , preferably 0.5 to 500 μm , particularly preferably 1 to 100 μm . The coated materials are distinguished by a high adhesive strength and good thermal and mechanical properties.

The coated materials according to the invention can be prepared by known methods, for example brushing, knife-coating or casting processes, such as curtain pouring or spin coating.

The compositions according to the invention can also be used as adhesives which cure by means of heat or by means of radiation, for firmly bonding the most diverse materials, it being possible for outstanding peel strengths to be achieved.


In addition to the high adhesive strengths, the outstanding processability, the good surface properties (smoothness, gloss), the high crosslinking density and the resistance to solvents and other liquids, the polymers according to the invention are also distinguished in particular by very good physico-mechanical properties, for example high heat resistance, breaking and flexural strength and impact strength, and outstanding electrical properties, for example low surface tensions and charges (very low ϵ and $\tan \delta$ values). The high permeability to oxygen and the low absorption of water are furthermore to be mentioned. Polymers built up only from carbon and hydrogen are particularly valuable ecologically, since, for example, they can be incinerated by pyrolysis [sic] or without the formation of harmful by-products. Because of their outstanding electrical properties, these polymers are particularly suitable for applications in the field of electrical

engineering and electronics, in particular as insulating materials (for example coil encapsulation).

The following examples illustrate the invention in more detail.

A) Preparation of polymers with strained cycloolefin rings in the polymer backbone


Example A1: Preparation of



55.1 g (0.5 mol) of Vestenamer[®] 6213 (cyclooctene polymerized by metathesis, Hüls AG) are dissolved in 200 ml of toluene, the solution is mixed with 33.05 g (0.25 mol) of dicyclopentadiene and the mixture is heated at 190°C in an autoclave for 8 hours. During this operation, the dicyclopentadiene is cleaved to give cyclopentadiene, which reacts with the Vestenamer to form norbornene groups. The reaction mixture is then poured into methanol/acetone (1:1), while stirring, and the polymer which has precipitated out is filtered off and then dried. Yield 50.4 g (76%). Elemental analysis, % calculated (found): C 88.57 (88.38), H 11.43 (11.60).

¹H-NMR analysis shows that 35% of the double bonds of the Vestenamer have been converted into norbornene units ($x = 0.35$ and $y = 0.65$). $M_n = 8500$ g/mol; $M_w = 170,000$ g/mol, determined by gel permeation chromatography in tetrahydrofuran with polystyrene standards.

Example A2: Preparation of




55.1 g (0.5 mol) of Vestenamer[®] L3000 (cyclooctene of low molecular weight polymerized by metathesis, Hüls AG, Marl) are mixed with 33.5 g (0.25 mol) of dicyclopentadiene without a solvent and the mixture is heated at 190°C in an autoclave for 8 hours. Working up and analysis of the reaction mixture are carried

out analogously to Example A1. Yield 47.5 g (77%). Elemental analysis, % calculated (found): C 88.57 (88.54), H 11.43 (11.32).


¹H-NMR analysis shows that 28% of the double bonds of the Vestenamer have been converted into norbornene units ($x = 0.28$ and $y = 0.72$). $M_n = 500$ g/mol; $M_w = 5000$ g/mol.

Example A3: Preparation of linear polydicyclopentadiene with structural elements



0.25 g of $[W(N-C_6H_5)(CH_2Si(CH_3)_3)_2(OC(CH_3)_3)Cl]$ is dissolved in 150 ml of toluene, and 30 ml of dicyclopentadiene are added. Irradiation is carried out for 30 minutes with a 1000W Xenon lamp with an IR water filter from a distance of one metre. Thereafter, 1 ml of benzaldehyde is added and the mixture is stirred at room temperature for a further hour. It is added dropwise to 1.5 l of methanol and the polymer which has precipitated out is filtered off and dried in vacuo at room temperature. The yield of crude product is 22.6 g. 200 ml of toluene are added to the crude product and the mixture is stirred at room temperature for 3 days. It is centrifuged and the toluene solution is decanted off, and subsequently stirred into 1.5 l of methanol. The white polymer which has precipitated out is filtered off and dried in vacuo. The yield of polymer is 5.62 g (19%). The polymer is very readily soluble in toluene.

Example A4: Preparation of




(a) 15.0 g (0.091 mol) of norbornene-1,2-dicarboxylic anhydride are dissolved in 200 ml of toluene at 80°C. A solution of 5.29 g (0.0455 mol) of 1,6-diaminohexane

in 50 ml of toluene is added dropwise with stirring. After 30 minutes at 80°C the mixture is cooled and filtered. The residue is powdered and dried under a high vacuum at 40°C for 24h. Yield: 16.5 g (81.6%). Melting point: 164°C; IR (KBr): $\nu(\text{C=O})$: 1635 cm^{-1} (amide) and 1695 cm^{-1} (carboxylic acid); $^1\text{H-NMR}$ (DMSO-d_6): inter alia 5.92-6.16 ppm: 4 olefin-H of the norbornene units; elemental analysis ($\text{C}_{24}\text{H}_{32}\text{N}_2\text{O}_6$): calculated: C 64.85; H 7.26; N 6.30; found: C 66.64, H 8.34; N 7.22

(b) 1.0 g (11 mmol) of 1,4-butanediol and 7.84 g (11 mmol) of the product obtained in (a) are dissolved in 50 ml of dimethylformamide. 4.54 g (22 mmol) of dicyclohexylcarbodiimide are added in portions with stirring and under an N_2 atmosphere, and the mixture is heated at 50°C for 14 h. After cooling, the mixture is filtered and the filtrate is precipitated in 1 l of water. Filtration and drying give the title compound. Yield: 4.2 g (84%); GPC (THF, PS standards): $M_n=5100$ g/mol; $M_w=13,000$ g/mol; elemental analysis ($\text{C}_{28}\text{H}_{38}\text{N}_2\text{O}_8$): calculated: C 67.44; H 7.68; N 5.62; found: C 66.88, H 7.70; N 5.87; soluble in DMSO, DMF, CHCl_3 , THF, dioxane

Example A5: Preparation of



(a) 15.0 g (0.090 mol) of 7-oxanorbornene-1,2-dicarboxylic anhydride are dissolved in 135 ml of dioxane at 60°C. A solution of 5.23 g (0.045 mol) of 1,6-diaminohexane in 50 ml of toluene is added dropwise with stirring. After 30 minutes at 60°C the mixture is cooled and filtered. The residue is powdered and dried under a high vacuum at 40°C for 24h. Yield: 13.09 g (64.9%). Melting point: 120°C (decomposes); IR (KBr): $\nu(\text{C=O})$: 1632 cm^{-1} (amide) and 1700 cm^{-1} (carboxylic acid); $^1\text{H-NMR}$ (DMSO-d_6): inter alia 6.0-6.5 ppm: 4 olefin-H of the 7-oxanorbornene units; elemental analysis ($\text{C}_{22}\text{H}_{28}\text{N}_2\text{O}_8$): calculated: C 64.85; H 7.26; N 6.30; found: C 66.64, H 8.34; N 7.22

(b) 1.0 g (11 mmol) of 1,4-butanediol and 5.0 g (11 mmol) of the product obtained in (a) are dissolved in 50 ml of dimethylformamide. 4.54 g (22 mmol) of

dicyclohexylcarbodiimide are added in portions with stirring and under an N_2 atmosphere, and the mixture is heated at $50^\circ C$ for 14 h. After cooling, the mixture is filtered and the filtrate is concentrated in a rotary evaporator. Drying gives the title compound. Yield: 5.2 g (94%); GPC (THF, PS standards): $M_n=7400$ g/mol; $M_w=20,800$ g/mol; elemental analysis ($C_{28}H_{34}N_2O_8$) $_n$: calculated: C 62.14; H 6.82; N 5.57; found: C 61.74, H 7.12; N 6.01; soluble in DMSO, DMF, $CHCl_3$, THF, dioxane

B) Use examples

Example B1: Thermal polymerization

In 1 ml of a 20% solution of the polymer according to Example A1 in chloroform, (a) 5 mg of $Ru[p\text{-cumene}][P(C_6H_{11})_3]_3Cl_2$ or (b) 5 mg of $Ru[P(C_6H_{11})_3]_3(CH_3OH)_2$ are dissolved. The mixtures are cast to films on glass plates with a doctor blade of 100 μm slit width. The solvent is evaporated off at room temperature for 1 hour and the film is then dried at $50^\circ C$ in vacuo for 1 hour. The coated plates are stable to storage. The layers can be detached with toluene. The coated glass plates are heated either at $65^\circ C$ for 4 hours or at $80^\circ C$ for 2 hours. After cooling, the plates are placed in water, whereupon a transparent, practically colourless and unsupported film can be detached from the glass plate. The crosslinking is demonstrated by the insolubility and swellability of the film in toluene. The films have an elasticity modulus of 2 MPa (Minimat tensile tester). Dielectric constants (ϵ) and $\tan \delta$ loss factors ($\tan \delta$) at $30^\circ C$ and various frequencies (ν):

ν	ϵ	$\tan \delta$ (%)
200 Hz	2.8	< 0.01
1000 Hz	2.7	0.01
10,000 Hz	2.7	0.015
100 kHz	2.6	0.025
1 MHz	2.5	0.03
10 MHz	2.4	0.05
100 MHz	2.3	0.05
1 GHz	2.2	not determined

Example B2: Thermal polymerization

Analogously to Example B1, 5 mg of $\text{Ru}[\text{p-cumene}][\text{P}(\text{C}_6\text{H}_{11})_3]_2\text{Cl}_2$, as the catalyst, are dissolved in 1 g of the polymer according to Example A2 by heating to 60°C and the solvent-free mixture is applied hot to a heated glass plate with a doctor blade. The coated plate is heated at 80°C for 2 hours. After cooling, a pale yellow transparent and unsupported film is detached from the glass plate. The film is insoluble in toluene.

Example B3: Thermal polymerization

Analogously to Example B1, a 5% solution of the polymer according to Example A3 is dissolved in toluene with 0.5% by weight of $\text{Ru}[\text{p-cumene}][\text{P}(\text{C}_6\text{H}_{11})_3]_2\text{Cl}_2$ as the catalyst, and the mixture is applied to a heated glass plate with a layer thickness of $20\text{ }\mu\text{m}$ using a doctor blade. The coated plate is heated at 80°C for 2 hours. After cooling, a transparent and unsupported film which swells only very slightly in toluene is detached from the glass plate.

Example B4: Thermal polymerization

The procedure is analogous to Example 3 and a film is formed on a copper foil. After the polymerization, the film has excellent adhesion to the copper foil. The coated copper foil is steeped in water for one week; even after this, the film cannot be detached from the copper film.

Example A5: Photopolymerization

A layer about $1\text{ }\mu\text{m}$ thick is applied to an Si semiconductor plate (wafer) by means of spin coating with a 10% solution of the polymer according to Example A1 and and [sic] 1% by weight (based on the polymer) of $\text{Ta}[\text{CH}_2\text{-Si}(\text{CH}_3)_3]_2\text{Cl}_2$, as the catalyst, in toluene. The layer is exposed to an Oriel 350W UV lamp under a mask for 15 seconds, subsequently heated at 80°C for 30 seconds and then developed with methylene chloride. A relief image with a resolution of about $1\text{ }\mu\text{m}$ is obtained.

Example B6: Photopolymerization

The solution used according to Example B5 is applied to a copper-coated epoxy laminate (printed circuit board) with a layer thickness of $50\text{ }\mu\text{m}$ using a doctor

blade (slit width 500 μm). The layer is then heated at 70°C for 1 minute and subsequently exposed to a Höhnle 3000W UV lamp under a printed circuit board mask for 3 minutes. It is then heated at 70°C for 3 minutes and subsequently developed with methylene chloride. A negative relief image of high resolution is obtained.

Example B7: Photopolymerization

A layer about 1 μm thick is applied to an Si semiconductor plate (wafer) by means of spin coating with a 10% solution of the polymer according to Example A3 and and [sic] 2% by weight (based on the polymer) of $\text{Ta}[\text{CH}_2\text{-Si}(\text{CH}_3)_3]_3\text{Cl}_2$, as the catalyst, in toluene. The layer is exposed to an Oriel 350W UV lamp under a resist mask for 5 seconds, subsequently heated at 80°C for 30 seconds and then developed with toluene. A relief image with a resolution of about 0.7 μm is obtained.

Example B8: Photopolymerization

A layer about 1 μm thick is applied to an Si semiconductor plate (wafer) by means of spin coating with a 10% solution of the polymer according to Example A4 and and [sic] 1% by weight (based on the polymer) of $\text{Ta}[\text{CH}_2\text{-Si}(\text{CH}_3)_3]_3\text{Cl}_2$ in dioxane. The layer is exposed to an Oriel 350W UV lamp under a resist mask for 100 seconds and then developed with dioxane. A relief image with a high resolution is obtained.

Example B9: Photopolymerization

A layer about 1 μm thick is applied to an Si semiconductor plate (wafer) by means of spin coating with a 10% solution of the polymer according to Example A5 and and [sic] 1% by weight (based on the polymer) of $\text{Ta}[\text{CH}_2\text{-Si}(\text{CH}_3)_3]_3\text{Cl}_2$ in dioxane. The layer is exposed to an Oriel 350W UV lamp under a resist mask for 100 seconds and then developed with dioxane. A relief image with a high resolution is obtained.

Example B10: Photocrosslinking

0.5 g of the polymer according to Example A4 are dissolved in 5 ml of dioxane together with 5 mg of $[\text{Ru}(\text{C}_6\text{H}_5)_2](\text{Tos})_2$. The solution is poured onto a glass plate and a film about 30 μm thick is produced by means of a doctor blade. Exposure is carried out for 3 minutes under a UV lamp, after which the clear, transparent films can no longer be dissolved, in particular neither in DMSO nor in dioxane.

Example B11: Photocrosslinking

0.5 g of the polymer according to Example A4 are dissolved in 5 ml of dioxane together with 5 mg of $[\text{Ru}(\text{CH}_3\text{CN})_6](\text{Tos})_2$. The solution is poured onto a glass plate and a film about 30 μm thick is produced by means of a doctor blade. Exposure is carried out for 3 minutes under a UV lamp, after which the clear, transparent films can no longer be dissolved, in particular neither in DMSO nor in dioxane.

Example B12: Photocrosslinking

0.5 g of the polymer according to Example A4 are dissolved in 5 ml of dioxane together with 5 mg of $[\text{Ru}(\text{CH}_3\text{CH}_2\text{CN})_6](\text{Tos})_2$. The solution is poured onto a glass plate and a film about 30 μm thick is produced by means of a doctor blade. Exposure is carried out for 3 minutes under a UV lamp, after which the clear, transparent films can no longer be dissolved, in particular neither in DMSO nor in dioxane.

Example B13: Photocrosslinking

0.5 g of the polymer according to Example A5 are dissolved in 5 ml of dioxane together with 5 mg of $[\text{Ru}(\text{C}_6\text{H}_5)_2](\text{Tos})_2$. The solution is poured onto a glass plate and a film about 30 μm thick is produced by means of a doctor blade. Exposure is carried out for 3 minutes under a UV lamp, after which the clear, transparent films can no longer be dissolved, in particular neither in DMSO nor in dioxane.

Example B14: Photocrosslinking

0.5 g of the polymer according to Example A5 are dissolved in 5 ml of dioxane together with 5 mg of $[\text{Ru}(\text{CH}_3\text{CN})_6](\text{Tos})_2$. The solution is poured onto a glass

plate and a film about 30 μm thick is produced by means of a doctor blade. Exposure is carried out for 3 minutes under a UV lamp, after which the clear, transparent films can no longer be dissolved, in particular neither in DMSO nor in dioxane.

Example B15: Photocrosslinking

0.5 g of the polymer according to Example A5 are dissolved in 5 ml of dioxane together with 5 mg of $[\text{Ru}(\text{CH}_3\text{CH}_2\text{CN})_6](\text{Tos})_2$. The solution is poured onto a glass plate and a film about 30 μm thick is produced by means of a doctor blade. Exposure is carried out for 3 minutes under a UV lamp, after which the clear, transparent films can no longer be dissolved, in particular neither in DMSO nor in dioxane.

Example B16: Thermal crosslinking

A film about 50 μm thick is produced on a glass plate by means of a doctor blade from a 10% solution of the polymer according to Example A4 in dioxane together with 1% (based on the polymer) of $\text{RuCl}_2(\text{p-cumene})\text{P}(\text{C}_6\text{H}_{11})_3$ and subsequent evaporation of the solvent at 80°C. The film is crosslinked by heating at 120°C for 1h. After detaching it from the glass plate, a tear-resistant film is obtained which is insoluble in both dioxane and DMF.

Example B17: Thermal crosslinking

A film about 50 μm thick is produced on a glass plate by means of a doctor blade from a 10% solution of the polymer according to Example A5 in dioxane together with 1% (based on the polymer) of $\text{RuCl}_2(\text{p-cumene})\text{P}(\text{C}_6\text{H}_{11})_3$ and subsequent evaporation of the solvent at 80°C. The film is crosslinked by heating at 120°C for 1h. After detaching it from the glass plate, a tear-resistant film is obtained which is insoluble in both dioxane and DMF.

Example B18: Thermal crosslinking

A layer 500 μm thick of a 10% solution of the polymer according to Example A1 and 1% of $[(\text{C}_6\text{H}_{11})_3\text{P}]_2\text{Ru}(\text{CH}_3\text{OH})_2(\text{Tos})_2$ in toluene is applied to an iron panel.

Following the evaporation of the toluene, the polymer is crosslinked at 80°C for 1h. The resulting film is insoluble in CH₂Cl₂.


Example B19: Thermal crosslinking

A layer 500 μm thick of a 10% solution of the polymer according to Example A1 and 1% of [(C₆H₁₁)₃P]₂RuCl₂ in toluene is applied to an iron panel. Following the evaporation of the toluene, the polymer is crosslinked at 80°C for 1h. The resulting film is insoluble in CH₂Cl₂.

PATENT CLAIMS:

1. A composition comprising (a) catalytic amounts of a one-component catalyst for metathesis polymerization and (b) at least one polymer with strained cycloalkenylene radicals bonded in the polymer backbone, alone or mixed with strained cycloolefins.

2. A composition according to claim 1, wherein the polymers are those with recurring structural units of the formula (a) in the polymer backbone



in which

R_{01} and R_{02} independently of one another are H or C_1 - C_6 alkyl, or R_{01} and R_{02} together are a bond, and A, together with the C-C group, forms an unsubstituted or substituted strained cycloolefin ring.

3. A composition according to claim 2, wherein the structural units of the formula (a) are bonded directly or via bridge groups.

4. A composition according to claim 2, wherein R_{01} and R_{02} are H.

5. A composition according to claim 2, wherein the substituents for the cycloolefin ring are C_1 - C_6 alkyl or -alkoxy; C_1 - C_4 haloalkyl or -alkoxy; halogen; -CN; -NH₂; secondary amino having 2 to 18 C atoms; tertiary amino having 3 to 18 C atoms; -C(O)-OR₀₃ or -C(O)-NR₀₃R₀₄, in which R₀₃ and R₀₄ independently of one another are H, C_1 - C_{18} alkyl, phenyl or benzyl.

6. A composition according to claim 2, wherein in formula (a) R_{01} and R_{02} together [lacuna] a bond, and A [lacuna] unsubstituted or substituted C_1 - C_{12} alkyl ne, unsubstituted or substituted C_2 - C_{12} heteroalkylene, with at least on heteroatom from the group consisting of O, S and N; unsubstituted or substituted



C_5-C_{12} cycloalkylene, unsubstituted or substituted C_4-C_{12} heterocycloalkylene, with at least one heteroatom from the group consisting of O, S and N; unsubstituted or substituted C_2-C_{12} alkenylene; unsubstituted or substituted C_3-C_{12} heteroalkenylene, with at least one heteroatom from the group consisting of O, S and N; unsubstituted or substituted C_5-C_{12} cycloalkenylene; or unsubstituted or substituted C_4-C_{12} heterocycloalkenylene, with at least one heteroatom from the group consisting of O, S and N; or

R_{01} and R_{02} independently of one another [lacuna] H or C_1-C_6 alkyl and A [lacuna] unsubstituted or substituted C_5-C_{12} cycloalkenylene; unsubstituted or substituted C_4-C_{12} heterocycloalkenylene, with at least one heteroatom from the group consisting of O, S and N; or unsubstituted or substituted C_5-C_{12} cycloalkdienylene; or

R_{01} [lacuna] a double bond together with a terminal C atom of the radical A; R_{02} [lacuna] H or C_1-C_6 alkyl; and A [lacuna] unsubstituted or substituted C_1-C_{12} alkylene, unsubstituted or substituted C_3-C_{12} heteroalkylene, with at least one heteroatom from the group consisting of O, S and N; unsubstituted or substituted C_5-C_{12} cycloalkylene; unsubstituted or substituted C_4-C_{12} heterocycloalkylene with at least one heteroatom from the group consisting of O, S and N; unsubstituted or substituted C_2-C_{12} alkenylene; unsubstituted or substituted C_3-C_{12} heteroalkenylene with at least one heteroatom from the group consisting of O, S and N; unsubstituted or substituted C_5-C_{12} cycloalkenylene; or unsubstituted or substituted C_4-C_{12} heterocycloalkenylene with at least one heteroatom from the group consisting of O, S and N; or

R_{01} and R_{02} each [lacuna] a double bond together with in each case a terminal C atom of the radical A, and A is unsubstituted or substituted C_3-C_{12} alkylene; unsubstituted or substituted C_3-C_{12} heteroalkylene, with at least one heteroatom from the group consisting of O, S and N; unsubstituted or substituted C_5-C_{12} cycloalkyl n ; or unsubstituted or substituted C_4-C_{12} heterocycloalkylene, with at least one heteroatom from the group consisting of O, S and N; it being possible for phenylene, C_4-C_6 cycloalkylene or C_4-C_6 heterocycloalkylene to be fused onto the alkylene, heteroalkylene, cycloalkylene, heterocycloalkylene, alkenylene, heteroalkenylene, cycloalkenylene, heterocycloalkenylene, alkaldienylene, heteroalkaldienylene, cycloalkaldienylene and heterocycloalkaldienylene.


7. A composition according to claim 6, wherein R_{01} and R_{02} together are a bond, and A is unsubstituted or substituted C_2-C_6 alkylene, unsubstituted or substituted C_3-C_7 cycloalkylene, unsubstituted or substituted C_2-C_6 alkenylene or unsubstituted or substituted C_3-C_7 cycloalkenylene; or R_{01} and R_{02} independently of one another are H or C_1-C_4 alkyl and A is unsubstituted or substituted C_3-C_7 cycloalkenylene; or R_{01} is a double bond together with a terminal C atom of the radical A; R_{02} is H or C_1-C_4 alkyl; and A is unsubstituted or substituted C_2-C_6 alkenylene, unsubstituted or substituted C_3-C_7 cycloalkylene, unsubstituted or substituted C_2-C_6 alkenylene or unsubstituted or substituted C_3-C_7 cycloalkenylene; or R_{01} and R_{02} each are a double bond together with in each case a terminal C atom of the radical A and A is unsubstituted or substituted C_3-C_6 alkylene or unsubstituted or substituted C_3-C_7 cycloalkylene.
8. A composition according to claim 1, wherein the polymers are homo- or copolymers.
9. A composition according to claim 2, wherein the polymer contains the structural elements of the formula (a) to the extent of at least 5 mol %, based on the polymer.
10. A composition according to claim 9, wherein the polymer contains the structural elements of the formula (a) to the extent of 5 to 100 mol %.
11. A composition according to claim 1, wherein the polymers are chosen from the homo- and copolymers of linear polyepoxides, polyesters, polyamides, polyester-amides, polyurethanes and polyureas in which the divalent diepoxide, dicarboxylic acid or diisocyanate radicals, or in which the divalent diol or diamine radicals, or both of these radicals, contain strained cycloolfin radicals, and which, in the case of the copolymers of these divalent radicals, contain different diepoxide, dicarboxylic acid or diisocyanate, diol or diamine radicals.
12. A composition according to claim 11, wherein the polyepoxides contain recurring structural elements chosen from the group of structural elements of the formulae (b), (c), (d) and (e)




with the proviso that they contain at least structural elements of the formulae [sic] (b) or (c) or both, in which R_{05} and R_{06} independently of one another are a divalent radical of a strained cycloolefin or a divalent radical with a strained cycloolefin, R_{07} is a divalent radical of a diglycidyl ether reduced by the glycidyloxy groups and R_{08} is a divalent radical of a diol reduced by the hydroxyl group.

13. A composition according to claim 12, wherein R_{05} and R_{06} independently of one another are mono- or diolefinically unsaturated C_5 - C_9 cycloalkylene or fused polycyclic C_7 - C_{10} cycloalkylene.

14. A composition according to claim 12, wherein R_{05} and R_{06} independently of one another are a norbornene radical of the formulae (nr_1) or (nr_2)



(nr_1)



(nr_2)

15. A composition according to claim 12, wherein R_{07} and R_{08} are C_2 - C_{18} alkylene, polyoxaalkylene having 2 to 50 oxaalkylene units and 2 to 6 C atoms in the oxyalkyl ne, C_3 - C_{12} cycloalkyl ne, C_5 - C_9 cycloalkylene- CH_2 -, $-CH_2$ -(C_5 - C_6 cycloalkylene)- CH_2 -, C_6 - C_{14} arylene, bisphenylene, benzylene, xylylene or - C_6H_4 - X_{01} - C_6H_4 -, where X_{01} is O, S, SO, SO_2 , CO, CO_2 , NH, $N(C_1$ - C_4 alkyl), alkylidene having 1 to 18 C atoms, or C_5 - C_7 cycloalkylidene.

16. A composition according to claim 11, wherein the polyesters contain identical structural elements of the group of structural elements of the


formulae (f), (g), (h) and (i), where at least the structural elements of the formulae [sic] (f) or (g) or both must be present



in which R_{09} and R_{010} independently of one another are a divalent radical of a strained cycloolefin or a divalent radical with a strained cycloolefin, R_{011} is a divalent radical of a dicarboxylic acid reduced by the carboxyl groups and R_{012} is a divalent radical of a diol reduced by the hydroxyl group.

17. A composition according to claim 16, wherein R_{09} and R_{010} independently of one another are mono- or diolefinically unsaturated C_5 - C_8 cycloalkylene or fused polycyclic C_7 - C_{18} cycloalkylene.

18. A composition according to claim 16, wherein R_{09} and R_{010} independently of one another are a norbornene radical of the formulae (nr_1) or (nr_2)



19. A composition according to claim 16, wherein R_{011} is C_2 - C_{18} alkylene or -alkenylene, C_3 - C_{12} cycloalkylene or -cycloalkenylene, C_5 - C_8 cycloalkylene- CH_2 -, - CH_2 -(C_5 - C_8 cycloalkylene)- CH_2 -, C_6 - C_{18} arylene, bisphenylene, benzylene, xylylene or - C_6H_4 - X_{01} - C_6H_4 -, where X_{01} is O, S, SO, SO_2 , CO, CO_2 , NH, $N(C_1$ - C_4 alkyl), alkylidene having 1 to 18 C atoms, or C_5 - C_7 cycloalkylidene.

20. A composition according to claim 16, wherein R_{012} is C_2 - C_{18} alkylene, polyoxaalkylene having 2 to 50 oxaalkylene units and 2 to 6 C atoms in the oxyalkylene, C_3 - C_{12} cycloalkylene, C_5 - C_8 cycloalkylene- CH_2 -, $-CH_2$ -(C_5 - C_8 cycloalkylene)- CH_2 -, C_6 - C_{14} arylene, bisphenylene, benzylene, xylylene, $-C_6H_4-X_{01}-C_6H_4-$, where X_{01} is O, S, SO, SO_2 , CO, CO_2 , NH, $N(C_1$ -C-alkyl), alkylidene having 1 to 18 C atoms, or C_5 - C_7 cycloalkylidene.


21. A composition according to claim 11, wherein the polyamides contain identical or different structural elements chosen from the group of structural elements of the formulae (j), (k), (l) and (m), where at least the structural elements of the formulae [sic] (j) or (k) or both must be present




in which R_{013} and R_{014} independently of one another are a divalent radical of a strained cycloolefin or a divalent radical with a strained cycloolefin, R_{015} is a divalent radical of a dicarboxylic acid reduced by the carboxyl groups and R_{016} is a divalent radical of a diamine reduced by the amino groups.

22. A composition according to claim 21, wherein R_{013} and R_{014} independently of one another are mono- or diolefinically unsaturated C_5 - C_8 cycloalkylene or fused polycyclic C_7 - C_{18} cycloalkylene.

23. A composition according to claim 21, wherein R_{013} and R_{014} independently of one another are a norbornene radical of the formulae (nr_1) or (nr_2)



(nr_1)




(nr_2) .

24. A composition according to claim 21, wherein R_{015} is C_2-C_{18} alkylene or -alkenylene, C_3-C_{12} cycloalkylene or -cycloalkenylene, C_5-C_8 cycloalkylene- CH_2- , $-CH_2-(C_5-C_8$ cycloalkylene)- CH_2- , C_6-C_{18} arylene, bisphenylene, benzylene, xylylene or $-C_6H_4-X_{01}-C_6H_4-$, where X_{01} is O, S, SO, SO_2 , CO, CO_2 , NH, $N(C_1-C_4$ alkyl) or alkylidene having 1 to 18 C atoms, or C_5-C_7 cycloalkylidene.

25. A composition according to claim 21, wherein R_{016} is C_2-C_{18} alkylene, C_3-C_{12} cycloalkylene, C_5-C_8 cycloalkylene- CH_2- , $CH_2-(C_5-C_8$ cycloalkylene)- CH_2- , C_6-C_{18} arylene, bisphenylene, benzylene, xylylene or $-C_6H_4-X_{01}-C_6H_4-$, where X_{01} is O, S, SO, SO_2 , CO, CO_2 , NH, $N(C_1-C_4$ alkyl), or alkylidene having 1 to 18 C atoms, or C_5-C_7 cycloalkylidene.


26. A composition according to claim 11, wherein the polyurethanes and polyureas contain identical or different structural elements chosen from the group of structural elements of the formulae (n), (o), (p) and (q), where at least the structural elements of the formulae [sic] (n) or (o) or both must be present



in which R_{017} and R_{018} independently of one another are a divalent radical of a strained cycloolefin or a divalent radical with a strained cycloolefin, R_{019} is a divalent radical of a diisocyanate reduced by the cyanate groups and R_{020} is a divalent radical of a diamine or of a diol reduced by the amino or hydroxyl groups, and the X_{02} independently of one another are -O- or -NH-.

27. A composition according to claim 26, wherein R_{017} and R_{018} are mono- or diolefinically unsaturated C_5-C_8 cycloalkylene or fused polycyclic C_7-C_{18} cycloalkylene.

28. A composition according to claim 27, wherein R_{017} and R_{018} independently of one another are cyclopentenylene, cycloheptenylene, cyclooctenylene or norbornene radicals of the formulae (nr₁) or (nr₂)




29. A composition according to claim 26, wherein R_{019} is C_2 - C_{18} alkylene or -alkenylene, C_3 - C_{12} cycloalkylene or -cycloalkenylene, C_5 - C_8 cycloalkylene- CH_2 -, $-CH_2$ -(C_5 - C_8 cycloalkylene)- CH_2 -, C_6 - C_{18} arylene, bisphenylene, benzylene, xylylene or $-C_6H_4-X_{01}-C_6H_4-$, where X_{01} is O, S, SO, SO_2 , CO, CO_2 , NH, $N(C_1-C_4alkyl)$ or alkylidene having 1 to 18 C atoms, or C_5 - C_7 cycloalkylidene.

30. A composition according to claim 26, wherein R_{020} is C_2 - C_{18} alkylene, polyoxaalkylene having 2 to 50 oxaalkylene units and 2 to 8 C atoms in the oxyalkylene, C_3 - C_{12} cycloalkylene, C_5 - C_8 cycloalkylene- CH_2 -, $-CH_2$ -(C_5 - C_8 cycloalkylene)- CH_2 -, C_6 - C_{14} arylene, bisphenylene, benzylene, xylylene, $-C_6H_4-X_{01}-C_6H_4-$, where X_{01} is O, S, SO, SO_2 , CO, CO_2 , NH, $N(C_1-C_4alkyl)$ or alkylidene having 1 to 18 C atoms, or C_5 - C_7 cycloalkylidene.

31. A composition according to claim 1, wherein the polymers are those having a carbon backbone.

32. A composition according to claim 31, wherein the polymers are essentially or completely linear metathesis polymers of fused at least bicyclic cycloaliphatic dienes which contain two olefinic double bonds in different rings.

33. A composition according to claim 31, wherein the polymers contain recurring structural elements of the formula (r)




(r).

in which R_{021} is C_2 - C_{10} alkylene onto which a cycloalkenylene having a total of 5 to 8 C atoms is fused directly or via another fused-on cycloalkylene having 5 to 8 C atoms.

34. A composition according to claim 31, wherein the polymer is a linear polynorbornadiene with recurring structural elements of the formula (r')



or linear polydicyclopentadiene with recurring structural elements of the formula (r'')



or wherein it is a copolymer with these two recurring structural elements.

35. A composition according to claim 34, wherein the polymer is a linear copolymer with a recurring structural element of the formula (r), in each case one or both of the structural elements (r') and (r'') and structural elements of the formula (r''')



of a strained cyclool fin, in which

Q_3 is a linear or branched C_1 - C_{18} alkylene which is unsubstituted or substituted by halogen, =O, -CN, -NO₂, -COOM, -SO₃M, -PO₃M, -COO(M₁)_{1/2}, -SO₃(M₁)_{1/2}, -PO₃(M₁)_{1/2}, C_1 - C_{20} alkyl, $R_1R_2R_3Si(O)_n$, C_1 - C_{20} hydroxyalkyl, C_1 - C_{20} haloalkyl, C_1 - C_6 cyanoalkyl, C_3 - C_6 cycloalkyl, C_6 - C_{16} aryl, C_7 - C_{16} aralkyl, C_3 - C_6 heterocycloalkyl, C_3 - C_{16} heteroaryl,

- C_4-C_{16} heteroaralkyl or R_4-X ; or in which two adjacent C atoms are substituted by $-CO-O-CO-$ or $-CO-NR_5-CO-$; or in which, possibly at adjacent carbon atoms, an alicyclic, aromatic or heteroaromatic ring is fused on which is unsubstituted or is substituted by halogen, $-CN$, $-NO_2$, $R_6R_7R_8Si(O)_u$, $-COOM$, $-SO_3M$, $-PO_3M$, $-COO(M_1)_{1/2}$, $-SO_3(M_1)_{1/2}$, $-PO_3(M_1)_{1/2}$, C_1-C_{20} alkyl, C_1-C_{20} haloalkyl, C_1-C_{20} hydroxyalkyl, C_1-C_6 cyanoalkyl, C_3-C_6 cycloalkyl, C_6-C_{16} aryl, C_7-C_{16} aralkyl, C_3-C_6 heterocycloalkyl, C_3-C_{16} heteroaryl, C_4-C_{16} heteroaralkyl or $R_{13}-X_1$;
- X and X_1 independently of one another are $-O-$, $-S-$, $-CO-$, $-SO-$, $-SO_2-$, $-O-C(O)-$, $-C(O)-O-$, $-C(O)-NR_5-$, $-NR_{10}-C(O)-$, $-SO_2-O-$ or $-O-SO_2-$;
- R_1 , R_2 and R_3 independently of one another are C_1-C_{12} alkyl, C_1-C_{12} perfluoroalkyl, phenyl or benzyl;
- R_4 and R_{13} independently are C_1-C_{20} alkyl, C_1-C_{20} haloalkyl, C_1-C_{20} hydroxyalkyl, C_3-C_6 cycloalkyl, C_6-C_{16} aryl, C_7-C_{16} aralkyl;
- R_5 and R_{10} independently of one another are hydrogen, C_1-C_{12} alkyl, phenyl or benzyl, the alkyl groups in turn being unsubstituted or substituted by C_1-C_{12} alkoxy or C_3-C_6 cycloalkyl;
- R_6 , R_7 and R_8 independently of one another are C_1-C_{12} alkyl, C_1-C_{12} perfluoroalkyl, phenyl or benzyl;
- M is an alkali metal and M_1 is an alkaline earth metal; and
- u is 0 or 1;
- the alicyclic ring formed with Q_3 possibly containing further non-aromatic double bonds;
- Q_2 is hydrogen, C_1-C_{20} alkyl, C_1-C_{20} haloalkyl, C_1-C_{12} alkoxy, halogen, $-CN$, $R_{11}-X_2$;
- R_{11} is C_1-C_{20} alkyl, C_1-C_{20} haloalkyl, C_1-C_{20} hydroxyalkyl, C_3-C_6 cycloalkyl, C_6-C_{16} aryl or C_7-C_{16} aralkyl;
- X_2 is $-C(O)-O-$ or $-C(O)-NR_{12}-$;
- R_{12} is hydrogen, C_1-C_{12} alkyl, phenyl or benzyl;
- the abovementioned cycloalkyl, heterocycloalkyl, aryl, heteroaryl, aralkyl and heteroaralkyl groups being unsubstituted or substituted by C_1-C_{12} alkyl, C_1-C_{12} alkoxy, $-NO_2$, $-CN$ or halogen, and the heteroatoms of the abovementioned heterocycloalkyl, heteroaryl and heteroaralkyl groups being selected from the group $-O-$, $-S-$, $-NR_5-$ and $-N=$; and
- Q_3 being hydrogen, C_1-C_{12} alkyl, phenyl or benzyl.

36. A composition according to claim 35, wherein Q_2 is H.

37. A composition according to claim 31, wherein the polymers with a carbon backbone are copolymers of strained cycloolefins with fused at least bicyclic cycloaliphatic dienes which contain at least two olefinic double bonds in different rings, and ethylenically unsaturated comonomers.

38. A composition according to claim 37, wherein the polymers contain recurring structural elements of the formula (r) and of the formula (s)



in which

R_{021} is C_2 - C_{10} alkylene, onto which an alkenylene having 2 to 6 C atoms is bonded directly or via a fused-on cycloalkylene ring having 5 to 8 C atoms; R_{022} is H, F, C_1 - C_{12} alkyl, $-COOH$, $-C(O)O-C_1-C_{12}$ alkyl, $-C(O)-NH_2$ or $-C(O)-NH-C_1-C_{12}$ alkyl; R_{023} is H, F, Cl, CN or C_1 - C_{12} alkyl; R_{024} is H, F, Cl, CN, OH, C_1 - C_{12} alkyl, C_1 - C_{12} alkoxy, phenyl which is unsubstituted or substituted by OH, Cl, Br, C_1 - C_4 alkyl, C_1 - C_4 alkoxy, $-COOH$, $C(O)-NH-C_1-C_{12}$ alkyl, $-C(O)-NH_2$, $-C(O)-NH-C_1-C_{12}$ alkyl, $-SO_3H$ or $-SO_3-C_1-C_{12}$ alkyl, $-C(O)OH$, $-C(O)O-C_2-C_{12}$ hydroxyalkyl, $-C(O)O-C_1-C_{12}$ alkyl, $-C(O)-NH_2$ or $-C(O)-NH-C_1-C_{12}$ alkyl; and R_{025} is H, F or C_1 - C_{12} alkyl.

39. A composition according to claim 38, wherein R_{022} is H, F, C_1 - C_4 alkyl, $-COOH$ or $-C(O)-C_1-C_6$ alkyl.

40. A composition according to claim 38, wherein R_{023} is H, F, Cl or C_1 - C_4 alkyl.

41. A composition according to claim 38, wherein R_{024} is H, F, Cl, CN, OH, C_1 - C_4 alkyl, C_1 - C_4 alkoxy, phenyl which is unsubstituted or substituted by OH, Cl,


Br, C₁-C₄alkyl, C₁-C₄alkoxy, -COOH, -C(O)OC₁-C₄alkyl, -C(O)-NH₂,
C(O)-NH-C₁-C₄alkyl, -SO₃H or -SO₃-C₁-C₄alkyl, -COOH, -C(O)O-C₁-C₄alkyl,
-C(O)-NH₂, -C(O)O-C₂-C₆hydroxyalkyl or -C(O)-NH-C₁-C₄alkyl.

42. A composition according to claim 38, wherein R₀₃₅ is H or F.

43. A composition according to claim 37, wherein the structural elements of the formula (r) are chosen from the structural elements of the formula (r') and (r'')



and



44. A composition according to claim 31, wherein the polymers with a carbon backbone are metathesis polymers or copolymers of strained cycloolefins with a double bond in the ring and olefinically unsaturated comonomers, of which the olefinic double bonds in the polymer backbone are reacted partly or completely with open-chain or cyclic 1,3-dienes having 4 to 12 C atoms in a Diels-Alder reaction to give cycloalkenylene radicals having 6 to 14 C atoms.

45. A composition according to claim 44, wherein 5 to 80% of the double bonds are reacted.

46. A composition according to claim 44, wherein the metathesis polymers contain recurring structural elements of the formula (t)




in which A₁ is mono- or bicyclic C₃-C₆cycloalkenylene.

47. A composition according to claim 46, wherein the structural element of the formula (t) is norborn-1,2-enylene of the formula (nr₃)



(nr₃).

48. A composition according to claim 44, wherein the metathesis polymer contains recurring structural units of the formula (u)



(u)


and recurring structural elements of the formula (w)



(w).

in which A₁, together with the -CH-CH- group, is bicyclic C₅-C₈cycloalkenylenes and R₀₂₆ is C₁-C₁₂alkylene.

and, if desired, recurring structural elements of the formula (s)



(s).

in which R₀₂₂ is H, F, C₁-C₁₂alkyl, -COOH, -C(O)O-C₁-C₁₂alkyl, -C(O)-NH₂ or -C(O)-NH-C₁-C₁₂alkyl; R₀₂₃ is H, F, Cl, CN or C₁-C₁₂alkyl; R₀₂₄ is H, F, Cl, CN, OH, C₁-C₁₂alkyl, C₁-C₁₂alkoxy, phenyl which is unsubstituted or substituted by OH, Cl, Br, C₁-C₄alkyl, C₁-C₄alkoxy, -COOH, C(O)OC₁-C₁₂alkyl, -C(O)-NH₂, -C(O)-NH-C₁-C₁₂alkyl, -SO₃H or -SO₃-C₁-C₁₂alkyl, -C(O)OH, -C(O)O-C₁-C₁₂hydroxyalkyl, -C(O)O-C₁-C₁₂alkyl, -C(O)-NH₂ or -C(O)-NH-C₁-C₁₂alkyl; and R₀₂₅ is H, F or C₁-C₁₂alkyl.

and recurring structural elements of the formula (z)



in which A_1 , together with the $-\text{CH}-\text{CR}_{027}$ group, is bicyclic C_5-C_8 cycloalkenylene and R_{027} is H, Cl or C_1-C_{12} alkyl, and, if desired, recurring structural elements of the formula (s)



in which R_{022} is H, F, C_1-C_{12} alkyl, $-\text{COOH}$, $-\text{C}(\text{O})\text{O}-\text{C}_1-\text{C}_{12}$ alkyl, $-\text{C}(\text{O})-\text{NH}_2$ or $-\text{C}(\text{O})-\text{NH}-\text{C}_1-\text{C}_{12}$ alkyl; R_{023} is H, F, Cl, CN or C_1-C_{12} alkyl; R_{024} is H, F, Cl, CN, OH, C_1-C_{12} alkyl, C_1-C_{12} alkoxy, phenyl which is unsubstituted or substituted by OH, Cl, Br, C_1-C_4 alkyl, C_1-C_4 alkoxy, $-\text{COOH}$, $\text{C}(\text{O})\text{OC}_1-\text{C}_{12}$ alkyl, $-\text{C}(\text{O})-\text{NH}_2$, $-\text{C}(\text{O})-\text{NH}-\text{C}_1-\text{C}_{12}$ alkyl, $-\text{SO}_3\text{H}$ or $-\text{SO}_3-\text{C}_1-\text{C}_{12}$ alkyl, $-\text{C}(\text{O})\text{OH}$, $-\text{C}(\text{O})\text{O}-\text{C}_2-\text{C}_{12}$ hydroxyalkyl, $-\text{C}(\text{O})\text{O}-\text{C}_1-\text{C}_{12}$ alkyl, $-\text{C}(\text{O})-\text{NH}_2$ or $-\text{C}(\text{O})-\text{NH}-\text{C}_1-\text{C}_{12}$ alkyl; and R_{025} is H, F or C_1-C_{12} alkyl.

55. A composition according to claim 1, wherein the comonomeric strained cycloolefins correspond to the formula I



in which

Q_1 is a radical having at least one carbon atom which, together with the $-\text{CH}=\text{CQ}_2-$ group, forms an at least 3-membered alicyclic ring which may contain one or more heteroatoms chosen from the group consisting of silicon, phosphorus, oxygen, nitrogen or sulfur; and which is unsubstituted or substituted by halogen, $=\text{O}$, $-\text{CN}$, $-\text{NO}_2$, $\text{R}_1\text{R}_2\text{R}_3\text{Si}(\text{O})_n-$, $-\text{COOM}$,

$-\text{SO}_3\text{M}$, $-\text{PO}_3\text{M}$, $-\text{COO}(\text{M}_1)_{1/2}$, $-\text{SO}_3(\text{M}_1)_{1/2}$, $-\text{PO}_3(\text{M}_1)_{1/2}$, $\text{C}_1\text{-C}_{20}\text{alkyl}$,
 $\text{C}_1\text{-C}_{20}\text{hydroxyalkyl}$, $\text{C}_1\text{-C}_{20}\text{haloalkyl}$, $\text{C}_1\text{-C}_6\text{cyanoalkyl}$, $\text{C}_3\text{-C}_6\text{cycloalkyl}$,
 $\text{C}_6\text{-C}_{16}\text{aryl}$, $\text{C}_7\text{-C}_{16}\text{aralkyl}$, $\text{C}_3\text{-C}_6\text{heterocycloalkyl}$, $\text{C}_3\text{-C}_{16}\text{heteroaryl}$,
 $\text{C}_4\text{-C}_{16}\text{heteroaralkyl}$ or $\text{R}_4\text{-X}$; or in which two adjacent C atoms are
substituted by $-\text{CO-O-CO-}$ or $-\text{CO-NR}_5\text{-CO-}$; or in which an alicyclic,
aromatic or heteroaromatic ring which is unsubstituted or substituted by
halogen, $-\text{CN}$, $-\text{NO}_2$, $\text{R}_6\text{R}_7\text{R}_8\text{Si}(\text{O})_u$, $-\text{COOM}$, $-\text{SO}_3\text{M}$, $-\text{PO}_3\text{M}$,
 $-\text{COO}(\text{M}_1)_{1/2}$, $-\text{SO}_3(\text{M}_1)_{1/2}$, $-\text{PO}_3(\text{M}_1)_{1/2}$, $\text{C}_1\text{-C}_{20}\text{alkyl}$, $\text{C}_1\text{-C}_{20}\text{haloalkyl}$, $\text{C}_1\text{-}$
 $\text{C}_{20}\text{hydroxyalkyl}$, $\text{C}_1\text{-C}_6\text{cyanoalkyl}$, $\text{C}_3\text{-C}_6\text{cycloalkyl}$, $\text{C}_6\text{-C}_{16}\text{aryl}$, $\text{C}_7\text{-}$
 $\text{C}_{16}\text{aralkyl}$, $\text{C}_3\text{-C}_6\text{heterocycloalkyl}$, $\text{C}_3\text{-C}_{16}\text{heteroaryl}$, $\text{C}_4\text{-C}_{16}\text{heteroaralkyl}$ or
 $\text{R}_{13}\text{-X}_1$ may be fused onto adjacent carbon atoms of the alicyclic ring;
X and X_1 independently of one another are $-\text{O-}$, $-\text{S-}$, $-\text{CO-}$, $-\text{SO-}$, $-\text{SO}_2\text{-}$, $-\text{O-C(O)-}$,
 $-\text{C(O)-O-}$, $-\text{C(O)-NR}_5\text{-}$, $-\text{NR}_{10}\text{-C(O)-}$, $-\text{SO}_2\text{-O-}$ or $-\text{O-SO}_2\text{-}$;
 R_1 , R_2 and R_3 independently of one another are $\text{C}_1\text{-C}_{12}\text{alkyl}$, $\text{C}_1\text{-}$
 $\text{C}_{12}\text{perfluoroalkyl}$, phenyl or benzyl;
 R_4 and R_{13} independently are $\text{C}_1\text{-C}_{20}\text{alkyl}$, $\text{C}_1\text{-C}_{20}\text{haloalkyl}$,
 $\text{C}_1\text{-C}_{20}\text{hydroxyalkyl}$, $\text{C}_3\text{-C}_6\text{cycloalkyl}$, $\text{C}_6\text{-C}_{16}\text{aryl}$, $\text{C}_7\text{-C}_{16}\text{aralkyl}$;
 R_5 and R_{10} independently of one another are hydrogen, $\text{C}_1\text{-C}_{12}\text{alkyl}$, phenyl or
benzyl, where the alkyl groups in their turn are unsubstituted or
substituted by $\text{C}_1\text{-C}_{12}\text{alkoxy}$ or $\text{C}_3\text{-C}_6\text{cycloalkyl}$;
 R_6 , R_7 and R_8 independently of one another are $\text{C}_1\text{-C}_{12}\text{alkyl}$, $\text{C}_1\text{-}$
 $\text{C}_{12}\text{perfluoroalkyl}$, phenyl or benzyl;
M is an alkali metal and M_1 is an alkaline earth metal; and
u is 0 or 1;
where the alicyclic ring formed with Q_1 may contain further non-aromatic double
bonds;
 Q_2 is hydrogen, $\text{C}_1\text{-C}_{20}\text{alkyl}$, $\text{C}_1\text{-C}_{20}\text{haloalkyl}$, $\text{C}_1\text{-C}_{12}\text{alkoxy}$, halogen, $-\text{CN}$, R_{11} ,
 X_2 ;
 R_{11} is $\text{C}_1\text{-C}_{20}\text{alkyl}$, $\text{C}_1\text{-C}_{20}\text{haloalkyl}$, $\text{C}_1\text{-C}_{20}\text{hydroxyalkyl}$, $\text{C}_3\text{-C}_6\text{cycloalkyl}$,
 $\text{C}_6\text{-C}_{16}\text{aryl}$ or $\text{C}_7\text{-C}_{16}\text{aralkyl}$;
 X_2 is $-\text{C(O)-O-}$ or $-\text{C(O)-NR}_{12}\text{-}$;
 R_{12} is hydrogen, $\text{C}_1\text{-C}_{12}\text{alkyl}$, phenyl or benzyl;
where the abovementioned cycloalkyl, heterocycloalkyl, aryl, heteroaryl, aralkyl
and heteroaralkyl groups are unsubstituted or substituted by $\text{C}_1\text{-C}_{12}\text{alkyl}$,
 $\text{C}_1\text{-C}_{12}\text{alkoxy}$, $-\text{NO}_2$, $-\text{CN}$ or halogen and where the heteroatoms of the

abovementioned heterocycloalkyl, heteroaryl and heteroaralkyl groups are chosen from the group consisting of -O-, -S-, -NR₂- and -N=; and R₉ is hydrogen, C₁-C₁₂alkyl, phenyl or benzyl.


56. A composition according to claim 1, which comprises comonomeric polyfunctional strained cycloolefins which are those of the formula (f1)



(f1),

in which T is the radical of a strained cycloolefin, U is a direct bond or an n-valent bridge group and n is an integer from 2 to 8.

57. A composition according to claim 56, wherein the radicals T correspond to cycloolefin radicals of the formula (f2)



(f2)

in which

Q₁ is a radical having at least one carbon atom which, together with the -CH=CO₂- group, forms an at least 3-membered alicyclic ring which may contain one or more heteroatoms chosen from the group consisting of silicon, phosphorus, oxygen, nitrogen or sulfur; and which is unsubstituted or substituted by halogen, =O, -CN, -NO₂, R₁R₂R₃Si(O)_u-, -COOM, -SO₃M, -PO₃M, -COO(M₁)_{1/2}, -SO₃(M₁)_{1/2}, -PO₃(M₁)_{1/2}, C₁-C₂₀alkyl, C₁-C₂₀hydroxyalkyl, C₁-C₂₀haloalkyl, C₁-C₈cyanoalkyl, C₃-C₈cycloalkyl, C₆-C₁₈aryl, C₇-C₁₈aralkyl, C₃-C₈heterocycloalkyl, C₃-C₁₈heteroaryl, C₄-C₁₈heteroaralkyl or R₄-X-; or in which two adjacent C atoms are substituted by -CO-O-CO- or -CO-NR₅-CO-; or in which an alicyclic, aromatic or heteroaromatic ring which is unsubstituted or substituted by halogen, -CN, -NO₂, R₄R₇R₈Si(O)_u-, -COOM, -SO₃M, -PO₃M, -COO(M₁)_{1/2}, -SO₃(M₁)_{1/2}, -PO₃(M₁)_{1/2}, C₁-C₂₀alkyl, C₁-C₂₀haloalkyl, C₁-C₂₀hydroxyalkyl, C₁-C₈cyanoalkyl, C₃-C₈cycloalkyl, C₆-C₁₈aryl, C₇-

C_{1-6} aralkyl, C_3-C_6 heterocycloalkyl, C_3-C_{10} heteroaryl, C_4-C_{10} heteroaralkyl or $R_{13}-X_1$ may be fused onto adjacent carbon atoms of the alicyclic ring;
 X and X_1 independently of one another are $-O-$, $-S-$, $-CO-$, $-SO-$, $-SO_2-$, $-O-C(O)-$, $-C(O)-O-$, $-C(O)-NR_5-$, $-NR_{10}-C(O)-$, $-SO_2-O-$ or $-O-SO_2-$;
 R_1 , R_2 and R_3 independently of one another are C_1-C_{12} alkyl, C_1-C_{12} perfluoroalkyl, phenyl or benzyl;
 R_4 and R_{13} independently are C_1-C_{20} alkyl, C_1-C_{20} haloalkyl, C_1-C_{20} hydroxyalkyl, C_3-C_6 cycloalkyl, C_6-C_{18} aryl, C_7-C_{18} aralkyl;
 R_5 and R_{10} independently of one another are hydrogen, C_1-C_{12} alkyl, phenyl or benzyl, where the alkyl groups in their turn are unsubstituted or substituted by C_1-C_{12} alkoxy or C_3-C_6 cycloalkyl;
 R_6 , R_7 and R_8 independently of one another are C_1-C_{12} alkyl, C_1-C_{12} perfluoroalkyl, phenyl or benzyl;
 M is an alkali metal and M_1 is an alkaline earth metal; and
 u is 0 or 1;

where the alicyclic ring formed with Q_1 may contain further non-aromatic double bonds;

Q_2 is hydrogen, C_1-C_{20} alkyl, C_1-C_{20} haloalkyl, C_1-C_{12} alkoxy, halogen, $-CN$, $R_{11}-X_2$;

R_{11} is C_1-C_{20} alkyl, C_1-C_{20} haloalkyl, C_1-C_{20} hydroxyalkyl, C_3-C_6 cycloalkyl, C_6-C_{18} aryl or C_7-C_{18} aralkyl;

X_2 is $-C(O)-O-$ or $-C(O)-NR_{12}-$;

R_{12} is hydrogen, C_1-C_{12} alkyl, phenyl or benzyl;

where the abovementioned cycloalkyl, heterocycloalkyl, aryl, heteroaryl, aralkyl and heteroaralkyl groups are unsubstituted or substituted by C_1-C_{12} alkyl, C_1-C_{12} alkoxy, $-NO_2$, $-CN$ or halogen and where the heteroatoms of the

abovementioned heterocycloalkyl, heteroaryl and heteroaralkyl groups are chosen from the group consisting of $-O-$, $-S-$, $-NR_9-$ and $-N=$; and
 R_9 is hydrogen, C_1-C_{12} alkyl, phenyl or benzyl.

58. A composition according to claim 56, wherein U is

(a) a divalent bridg group of th formula (f5)



(f5).

in which

X_5 and X_6 independently of one another are a direct bond, -O-, -CH₂-O-, -C(O)O-, -O(O)C-, -CH₂-O(O)C-, -C(O)-NR₀₂₉-, -R₀₂₉N-(O)C-, -NH-C(O)-NR₀₂₉-, -O-C(O)-NH-, -CH₂-O-C(O)-NH- or -NH-C(O)-O-, and

R₀₂₈ is C₂-C₁₈alkylene, C₅-C₈cycloalkylene which is unsubstituted or substituted by C₁-C₄alkyl or C₁-C₄alkoxy, C₆-C₁₈arylene or C₇-C₁₉aralkylene which are unsubstituted or substituted by C₁-C₄alkyl or C₁-C₄alkoxy, or polyoxaalkylene having 2 to 12 oxaalkylene units and 2 to 6 C atoms in the alkylene, and

R₀₂₉ is H or C₁-C₈alkyl; or

(b) a trivalent bridge group of the formula (f6)



in which

X_5 , X_6 and X_7 are -O-, -CH₂-O-, -C(O)O-, -O(O)C-, -CH₂-O(O)C-, -C(O)-NR₀₂₉-, -R₀₂₉N-(O)C-, -NH-C(O)-NR₀₂₉-, -O-C(O)-NH-, -CH₂-O-C(O)-NH- or -NH-C(O)-O-, and

R₀₃₁ is a trivalent aliphatic hydrocarbon radical having 3 to 20 C atoms, a trivalent cycloaliphatic radical which has 3 to 8 C atoms and is unsubstituted or substituted by C₁-C₄alkyl or C₁-C₄alkoxy, or a trivalent aromatic radical having 6 to 18 C atoms, which is unsubstituted or substituted by C₁-C₄alkyl or C₁-C₄alkoxy, a trivalent araliphatic radical having 7 to 19 C atoms, which is unsubstituted or substituted by C₁-C₄alkyl or C₁-C₄alkoxy, or a trivalent heteroaromatic radical having 3 to 13 C atoms and 1 to 3 heteroatoms from the group consisting of -O-, -N- and -S-, which is unsubstituted or substituted by C₁-C₄alkyl or C₁-C₄alkoxy, and R₀₃₁ is H or C₁-C₈alkyl; or

(c) a tetravalent bridge group of the formula (f7)



in which

X_3 , X_6 , X_7 and X_8 are $-C(O)O-$, $-CH_2-O(O)C-$ or $-C(O)-NR_{023}$, and R_{023} is a tetravalent aliphatic hydrocarbon radical having 4 to 20 C atoms, a tetravalent cycloaliphatic radical having 4 to 8 ring C atoms, which is unsubstituted or substituted by C_1-C_4 alkyl or C_1-C_4 alkoxy, or a tetravalent aromatic radical having 6 to 18 C atoms, which is unsubstituted or substituted by C_1-C_4 alkyl or C_1-C_4 alkoxy, a tetravalent araliphatic radical having 7 to 19 C atoms, which is unsubstituted or substituted by C_1-C_4 alkyl or C_1-C_4 alkoxy, or a tetravalent heteroaromatic radical having 3 to 13 C atoms and 1 to three heteroatoms from the group consisting of $-O-$, $-N-$ and $-S-$, which is unsubstituted or substituted by C_1-C_4 alkyl or C_1-C_4 alkoxy, and R_{023} is H or C_1-C_6 alkyl.

59. A composition according to claim 1, which comprises polymers and, if desired, monomers which are built up only from carbon and hydrogen.

60. A composition according to claim 1, which comprises the one-component catalyst in an amount of 0.001 to 20 mol %, based on the amount of the monomer.

61. A composition according to claim 60, which comprises the one-component catalyst in an amount of 0.01 to 10 mol %, based on the amount of the monomer.

62. A composition according to claim 1, which comprises, as the one-component catalyst,

- (a) a ruthenium compound or osmium compound which possesses at least one photolabile ligand attached to the ruthenium atom or osmium atom, and the rest of whose coordination sites are occupied by non-photolabile ligands; or
- (b) a molybdenum(VI) compound or tungsten(VI) compound which has at least two methyl groups or two monosubstituted methyl groups attached to the metal, the substituent containing no hydrogen atom in the α position; or
- (c) a titanium(IV), niobium(V), tantalum(V), molybdenum(VI) or tungsten(VI) compound in which a silylmethyl group and at least one halogen are attached to the metal; or


- (d) a niobium(V) compound or tantalum(V) compound which has at least two methyl groups or two monosubstituted methyl groups attached to the metal, the substituent containing no hydrogen atom in the α position; or
- (e) a titanium(IV) compound which has at least two methyl groups or two monosubstituted methyl groups attached to the metal, the substituent containing no hydrogen atom in the α position; or
- (f) a ruthenium compound or osmium compound which have [sic] at least one phosphine group, at least one photolabile ligand and, if desired, neutral ligands attached to the metal atom, a total of from 2 to 5 ligands being attached, and contains the acid anions for charge compensation; or
- (g) a divalently cationic ruthenium compound or osmium compound having a metal atom to which 1 to 3 tertiary phosphine ligands with, in the case of the ruthenium compound, sterically bulky substituents, if desired, non-photolabile neutral ligands, and anions for charge compensation are attached, with the proviso that in ruthenium(trisphenylphosphine) dihalides or hydride halides the phenyl groups are substituted by C_1 - C_{18} alkyl, C_1 - C_{18} haloalkyl or C_1 - C_{18} alkoxy.

63. A composition according to claim 62, wherein the photolabile ligands are nitrogen (N_2), monocyclic, polycyclic or fused arenes having 6 to 24 C atoms, which are unsubstituted or substituted by OH, C_1 - C_4 alkyl, C_1 - C_4 alkoxy, C_6 - C_{12} aryl or halogen, or monocyclic heteroarenes, fused heteroarenes or fused arene-heteroarenes having 3 to 22 C atoms and 1 to 3 heteroatoms chosen from the group consisting of O, S and N, which are unsubstituted or substituted by C_1 - C_4 alkyl, C_1 - C_4 alkoxy or halogen; or aliphatic, cycloaliphatic, aromatic or araliphatic nitriles having 1 to 22 C atoms, which are unsubstituted or substituted by C_1 - C_4 alkyl, C_1 - C_4 alkoxy or halogen.

64. A composition according to claim 62, wherein the non-photolabile ligands are H_2O , H_2S , NH_3 ; halogenated or unhalogenated, aliphatic or cycloaliphatic alcohols or mercaptans having 1 to 18 C atoms, aromatic alcohols or thiols having 6 to 18 C atoms, and araliphatic alcohols or thiols having 7 to 18 C atoms; aliphatic, cycloaliphatic, araliphatic or aromatic ethers, thioethers, sulfoxides, sulfones, ketones, aldehydes, carboxylic acid esters, lactones, optionally N- C_1 - C_4 mono- or -dialkylated carboxylic acid amides having 2 to 20 C atoms and optionally N- C_1 - C_4 alkylated lactams; aliphatic, cycloaliphatic, araliphatic or aromatic, primary.

secondary and tertiary amines having 1 to 20 C atoms; and unsubstituted or substituted cyclopentadienyls.

65. A composition according to claim 62, wherein the ruthenium or osmium compound corresponds to the formula IX



in which

Me is ruthenium or osmium;

n is 0, 1, 2, 3, 4, 5, 6, 7 or 8;

L₁ is a photolabile ligand;

L₂, L₃, L₄, L₅ and L₆ independently of one another are a non-photolabile or a photolabile ligand;

m is 1, 2, 3, 4, 5 or 6;

o, p, q, r and s independently of one another are 0, 1, 2, 3, 4 or 5;

z₁, z₂, z₃, z₄, z₅, z₆ and z₇ independently of one another are -4, -3, -2, -1, 0, +1 or +2; and

L₇ is a non-coordinating cation or anion;

where the sum of m + o + p + q + r + s is an integer from 2 to 6 and t is the quotient of (n + m • z₁ + o • z₂ + p • z₃ + q • z₄ + r • z₅ + s • z₆)/z₇.

66. A composition according to claim 62, wherein the methyl groups or monosubstituted methyl groups are those of the formula XI



in which R is H, -CF₃, -SiR₃₉R₃₉R₄₀, -CR₄₁R₄₂R₄₃, or C₆-C₁₀aryl or C₄-C₁₃heteroaryl having 1 to 3 heteroatoms from the group consisting of O, S and N, which are unsubstituted or substituted by C₁-C₆alkyl or C₁-C₆alkoxy;


R₃₉, R₃₉ and R₄₀ independently of one another are C₁-C₁₂alkyl, C₃- or C₆cycloalkyl, or are unsubstituted or C₁-C₆alkyl- or C₁-C₆alkoxy-substituted phenyl or benzyl;

and

R₄₁, R₄₂ and R₄₃ independently of one another are C₁-C₁₀alkyl which is unsubstituted or substituted by C₁-C₁₀alkoxy, or R₄₁ and R₄₂ have this meaning and

R_{43} is C_6 - C_{10} aryl or C_4 - C_9 heteroaryl which is unsubstituted or substituted by C_1 - C_6 alkyl or C_1 - C_6 alkoxy.

67. Compound according to claim 62, wherein the molybdenum or tungsten compound is that of one of the formulae XII to XIIc.



in which

Me is Mo(VI) or W(VI);

at least two of the radicals R_{53} to R_{56} are a radical $-CH_2-R$ of the formula XI according to claim 66;

in each case two of the other radicals of R_{53} to R_{56} are $=O$ or $=N-R_{44}$, and R_{44} is linear or branched C_1 - C_{18} alkyl which is unsubstituted or substituted by C_1 - C_6 alkoxy, C_5 - or C_6 cycloalkyl which is unsubstituted or substituted by

C₁-C₈alkyl, C₁-C₈alkoxy or halogen, phenyl which is unsubstituted or substituted by C₁-C₈alkyl, C₁-C₈alkoxy, C₁-C₈alkoxymethyl, C₁-C₈alkoxyethyl, di(C₁-C₈alkyl)amino, di(C₁-C₈alkyl)amino-C₁-C₃alkyl, or halogen, or benzyl or phenylethyl which are unsubstituted or substituted by C₁-C₈alkyl, C₁-C₈alkoxy, C₁-C₈alkoxymethyl, C₁-C₈alkoxyethyl or halogen; and/or the other radicals of R₅₃ to R₅₈ are secondary amino having 2 to 18 C atoms, R₄₅O- or R₄₅S-, halogen, cyclopentadienyl or bridged biscyclopentadienyl or a neutral ligand, in which R₄₅ is linear or branched C₁-C₁₈alkyl which is unsubstituted or substituted by C₁-C₈alkoxy or halogen, C₅- or C₆cycloalkyl which is unsubstituted or substituted by C₁-C₈alkyl, C₁-C₈alkoxy or halogen, phenyl which is unsubstituted or substituted by C₁-C₈alkyl, C₁-C₈alkoxy, C₁-C₈alkoxymethyl, C₁-C₈alkoxyethyl or halogen, or benzyl or phenylethyl which are unsubstituted or substituted by C₁-C₈alkyl, C₁-C₈alkoxy, C₁-C₈alkoxymethyl, C₁-C₈alkoxyethyl or halogen.

68. A composition according to claim 62, wherein the silylmethyl group is that of the formula XIV




in which


R₃₈, R₃₉ and R₄₀ independently of one another are C₁-C₁₈alkyl, C₅- or C₆cycloalkyl or phenyl or benzyl which are unsubstituted or substituted by C₁-C₈alkyl or C₁-C₈alkoxy.

69. A composition according to claim 62, wherein the titanium, niobium, tantalum, molybdenum or tungsten compound is that of one of the formulae XV, XVa and XVb





(Xva).



(XVb).

in which

Me₁ is Mo(VI) or W(VI);

Me₂ is Nb(V) or Ta(V);

one of the radicals R₆₉ to R₇₄ is a radical -CH₂-SiR₃₈R₃₉R₄₀ of the formula XIV according to claim 68;


at least one of the radicals R₆₉ to R₇₄ is F, Cl or Br;

R₃₈, R₃₉ and R₄₀ independently of one another are C₁-C₆alkyl, C₃- or C₆cycloalkyl, or phenyl or benzyl which are unsubstituted or substituted by C₁-C₆alkyl or C₁-C₆alkoxy;

in formula XV two or in each case two, and in formula XVa two of the other radicals of R₆₉ to R₇₄, each together are =O or =N-R₄₄, and R₄₄ is linear or branched C₁-C₁₈alkyl which is unsubstituted or substituted by C₁-C₆alkoxy, C₃- or C₆cycloalkyl which is unsubstituted, or substituted by C₁-C₆alkyl, C₁-C₆alkoxy or halogen, phenyl which is unsubstituted or substituted by C₁-C₆alkyl, C₁-C₆alkoxy, C₁-C₆alkoxymethyl, C₁-C₆alkoxyethyl, di(C₁-C₆alkyl)amino, di(C₁-C₆alkyl)amino-C₁-C₃alkyl or halogen, or benzyl or phenylethyl which are unsubstituted or substituted by C₁-C₆alkyl, C₁-C₆alkoxy, C₁-C₆alkoxymethyl, C₁-C₆alkoxyethyl, di(C₁-C₆alkyl)amino, di(C₁-C₆alkyl)amino-C₁-C₃alkyl or halogen, and the other radicals are secondary amino having 2 to 18 C atoms, R₄₅O- or R₄₅S-, halogen, unsubstituted or substituted cyclopentadienyl or bridged biscyclopentadienyl or a neutral ligand, in which the R₄₅ independently of one another are linear or branched C₁-C₁₈alkyl which is unsubstituted or substituted by C₁-C₆alkoxy or halogen, C₃- or C₆cycloalkyl which is unsubstituted or substituted by C₁-C₆alkyl, C₁-C₆alkoxy or halogen, phenyl which is unsubstituted or

substituted by C₁-C₆alkyl, C₁-C₆alkoxy, C₁-C₆alkoxymethyl, C₁-C₆alkoxyethyl, di(C₁-C₆-alkyl)amino, di(C₁-C₆-alkyl)amino-C₁-C₃alkyl or halogen, or benzyl or phenylethyl which are unsubstituted or substituted by C₁-C₆alkyl, C₁-C₆alkoxy, C₁-C₆alkoxymethyl, C₁-C₆alkoxyethyl, di(C₁-C₆-alkyl)amir.o, di(C₁-C₆-alkyl)amino-C₁-C₃alkyl or halogen; or in the formulae XV, XVa and XVb, the other radicals independently of one another are secondary amino having 2 to 18 C atoms, R₄₅O- or R₄₅S-, halogen, unsubstituted or substituted cyclopentadienyl or bridged biscyclopentadienyl or a neutral ligand, in which the R₄₅ independently of one another are linear or branched C₁-C₁₈alkyl which is unsubstituted or substituted by C₁-C₆alkoxy or halogen, C₅- or C₆cycloalkyl which is unsubstituted or substituted by C₁-C₆alkyl, C₁-C₆alkoxy or halogen, phenyl which is unsubstituted or substituted by C₁-C₆alkyl, C₁-C₆alkoxy, C₁-C₆alkoxymethyl, C₁-C₆alkoxyethyl, di(C₁-C₆-alkyl)amino, di(C₁-C₆-alkyl)amino-C₁-C₃alkyl or halogen, or benzyl or phenylethyl which are unsubstituted or substituted by C₁-C₆alkyl, C₁-C₆alkoxy, C₁-C₆alkoxymethyl, C₁-C₆alkoxyethyl, di(C₁-C₆-alkyl)amino, di(C₁-C₆-alkyl)amino-C₁-C₃alkyl or halogen

70. A composition according to claim 62, wherein the niobium or tantalum compound is that of the formula XVIII



(XVIII).

in which

Me is Nb(V) or Ta(V).

at least two of the radicals R₈₂ to R₈₆ are a radical -CH₂-R of the formula XI according to claim 66;


two of the other radicals of R₈₂ to R₈₆ together are =O or =N-R₈₄ and R₈₄ is linear or branched C₁-C₁₈alkyl which is unsubstituted or substituted by C₁-C₆alkoxy, C₅- or C₆cycloalkyl which is unsubstituted or substituted by C₁-C₆alkyl, C₁-C₆alkoxy or halogen, phenyl which is unsubstituted or substituted by C₁-C₆alkyl, C₁-C₆alkoxy, C₁-C₆alkoxymethyl, C₁-C₆alkoxyethyl, di(C₁-C₆-alkyl)amino, di(C₁-C₆-

alkyl)amino-C₁-C₃alkyl or halogen, or benzyl or phenylethyl which are unsubstituted or substituted by C₁-C₆alkyl, C₁-C₆alkoxy, C₁-C₆alkoxymethyl, C₁-C₆alkoxyethyl, di(C₁-C₆alkyl)amino, di(C₁-C₆alkyl)amino-C₁-C₃alkyl or halogen; and/or

the other radicals of R₈₂ to R₉₆ independently of one another are secondary amino having 2 to 18 C atoms, R₄₅O-, R₄₅S-, halogen, cyclopentadienyl or bridged biscyclopentadienyl or a neutral ligand, in which the R₄₅ independently of one another are linear or branched C₁-C₁₈alkyl which is unsubstituted or substituted by C₁-C₆alkoxy or halogen, C₃- or C₆cycloalkyl which is unsubstituted or substituted by C₁-C₆alkyl, C₁-C₆alkoxy or halogen, phenyl which is unsubstituted or substituted by C₁-C₆alkyl, C₁-C₆alkoxy, C₁-C₆alkoxymethyl, C₁-C₆alkoxyethyl.

di(C₁-C₆alkyl)amino, di(C₁-C₆alkyl)amino-C₁-C₃alkyl or halogen, or benzyl or phenylethyl which are unsubstituted or substituted by C₁-C₆alkyl, C₁-C₆alkoxy, C₁-C₆alkoxymethyl, C₁-C₆alkoxyethyl, di(C₁-C₆alkyl)amino, di(C₁-C₆alkyl)amino-C₁-C₃alkyl or halogen.

71. A composition according to claim 1, wherein the titanium(IV) compound is that of the formula XX



(XX).

in which

at least two of the radicals R₈₇ to R₉₀ are a radical -CH₂-P of the formula XI according to claim 66; and


the other radicals R₈₇ to R₉₀ are secondary amino having 2 to 18 C atoms, R₄₅O-, R₄₅S-, halogen, cyclopentadienyl or bridged biscyclopentadienyl or a neutral ligand, in which the R₄₅ independently of one another are linear or branched C₁-C₁₈alkyl which is unsubstituted or substituted by C₁-C₆alkoxy or halogen, C₃- or C₆cycloalkyl which is unsubstituted or substituted by C₁-C₆alkyl, C₁-C₆alkoxy or halogen, phenyl which is unsubstituted or substituted by C₁-C₆alkyl, C₁-C₆alkoxy, C₁-C₆alkoxymethyl, C₁-C₆alkoxyethyl, di(C₁-C₆alkyl)amino, di(C₁-C₆alkyl)amino-C₁-C₃alkyl or halogen, or benzyl or phenylethyl which are unsubstituted or

substituted by C₁-C₆alkyl, C₁-C₆alkoxy, C₁-C₆alkoxymethyl, C₁-C₆alkoxyethyl, di(C₁-C₆alkyl)amino, di(C₁-C₆alkyl)amino-C₁-C₃alkyl or halogen.

72. A composition according to claim 62, wherein the phosphine ligands correspond to the formulae XXIII or XXIIIa









(XXIII)



(XXIIIa).

in which R₉₁, R₉₂ and R₉₃ independently of one another are H, C₁-C₂₀-alkyl, C₁-C₂₀alkoxy, C₄-C₁₂cycloalkyl or cycloalkoxy which are unsubstituted or substituted by C₁-C₆alkyl, C₁-C₆haloalkyl or C₁-C₆alkoxy or C₆-C₁₈aryl or C₆-C₁₈aryloxy which are unsubstituted or substituted by C₁-C₆alkyl, C₁-C₆haloalkyl or C₁-C₆alkoxy, or C₇-C₁₈aralkyl or C₇-C₁₈aralkyloxy which are unsubstituted or substituted by C₁-C₆alkyl, C₁-C₆haloalkyl or C₁-C₆alkoxy; the radicals R₉₁ and R₉₂ together are tetra- or pentamethylene or tetra- or pentamethylenedioxy which are unsubstituted or substituted by C₁-C₆alkyl, C₁-C₆haloalkyl or C₁-C₆alkoxy, or tetra- or pentamethylene or tetra- or pentamethylenedioxy which are unsubstituted or substituted by C₁-C₆alkyl, C₁-C₆haloalkyl or C₁-C₆alkoxy and fused with 1 or 2 1,2-phenylene, or tetramethylenedioxy which is unsubstituted or substituted by C₁-C₆alkyl, C₁-C₆haloalkyl or C₁-C₆alkoxy and is fused in the 1,2- and 3,4-positions with 1,2-phenylene, and R₉₃ has the abovementioned meaning; and Z₁ is linear or branched C₂-C₁₂alkylene which is unsubstituted or substituted by C₁-C₄alkoxy, 1,2- or 1,3-cycloalkylene having 4 to 8 C atoms, which is unsubstituted or substituted by C₁-C₄alkyl or C₁-C₄alkoxy, or 1,2- or 1,3-heterocycloalkylene having 5 or 6 ring members and one heteroatom from the group consisting of O or N, which is unsubstituted or substituted by C₁-C₄alkyl or C₁-C₄alkoxy.

73. A composition according to claim 62, wherein the ruthenium or osmium compound is that of one of the formulae XXV to XXVf



in which

Me is Ru or Os;

Z in formulae XXV to XXVe is H⁺, cyclopentadienyl, Cl⁻, Br⁻, BF₄⁻, PF₆⁻, SbF₆⁻, AsF₆⁻, CF₃SO₃⁻, C₆H₅-SO₃⁻, 4-methyl-C₆H₅-SO₃⁻, 3,5-dimethyl-C₆H₅-SO₃⁻, 2,4,6-trimethyl-C₆H₅-SO₃⁻ and 4-CF₃-C₆H₅-SO₃⁻ and in formula XXVf is H⁺, cyclopentadienyl, BF₄⁻, PF₆⁻, SbF₆⁻, AsF₆⁻, CF₃SO₃⁻, C₆H₅-SO₃⁻, 4-methyl-C₆H₅-SO₃⁻, 2,6-dimethyl-C₆H₅-SO₃⁻, 2,4,6-trimethyl-C₆H₅-SO₃⁻ or 4-CF₃-C₆H₅-SO₃⁻;

R₉₄, R₉₅ and R₉₆ independently of one another are C₁-C₆alkyl, or cyclopentyl or cyclohexyl or cyclopentyloxy or cyclohexyloxy which are unsubstituted or substituted by 1 to 3 C₁-C₄alkyl, or phenyl or benzyl or phenyloxy or benzyloxy which are unsubstituted or substituted by 1 to 3 C₁-C₄alkyl;


L₈ is C₆-C₁₀arene or C₅-C₉heteroarene which are unsubstituted or substituted by 1 to 3 C₁-C₄alkyl, C₁-C₄alkoxy, -OH, -F or Cl;

L₉ is C₁-C₆alkyl-CN, benzonitrile or benzylnitrile; and

L₁₀ is H₂O or C₁-C₆alkanol.

74. A composition according to claim 62, wherein the ruthenium or osmium compound is that of one of the formulae XXVI, XXVIa, XXVib, XXVlc and XXVld





in which

Me is Ru or Os;

Y_1 is the anion of a monobasic acid;

L_{11} is a phosphine of the formula XXIII or XXIIIa according to claim 72,

L_{12} is a neutral ligand;

L_{13} is cyclopentadienyl which is unsubstituted or substituted by $\text{C}_1\text{-C}_4$ alkyl; and

L_{14} is CO.

75. A process for the preparation of crosslinked polymers by metathesis polymerization, wherein a composition of

(a) a catalytic amount of a one-component catalyst for metathesis polymerization and

(b) at least one polymer with strained cycloalkenylene radicals bonded in the polymer backbone, alone or mixed with strained cycloolefins,

(c) is polymerized by heating,

(d) is polymerized by irradiation,

(e) is polymerized by heating and irradiation,

(f) the one-component catalyst is activated by brief heating and the polymerization is brought to completion by irradiation, or

(g) the one-component catalyst is activated by brief irradiation and the polymerization is brought to completion by heating.

76. A process according to claim 75, wherein the heating is carried out at a temperature of 50 to 300°C.

77. A crosslinked metathesis polymer of at least one polymer with strained cycloalkenyl radicals bonded in the polymer backbone, alone or mixed with strained cycloolefins.



78. A coated carrier material, wherein a layer of a composition according to claim 1 is applied to a substrate.

79. A coated carrier material with a crosslinked layer of a composition according to claim 1.

80. A shaped article of crosslinked metathesis polymers of at least one polymer with strained cycloalkenylene radicals bonded in the polymer backbone, alone or as a mixture with strained cycloolefins.

81. A process for the preparation of coated materials or relief images on carrier materials, in which a composition according to claim 1 and, if desired, a solvent are applied as a layer to a carrier, if desired the solvent is removed, and the layer is irradiated or heated for polymerization, or the layer is irradiated through a photomask and the non-irradiated portions are then removed with a solvent, and, if desired, the resulting relief image is after-heated.

82. A polyepoxide with recurring structural elements chosen from the group of structural elements of the formulae (b), (c), (d) and (e)



with the proviso that they contain at least structural elements of the formulae [sic] (b) or (c) or both, in which R_{05} and R_{06} independently of one another are a divalent radical of a strained cycloolefin or a divalent radical with a strained cycloolefin, R_{07} is a divalent radical of a diglycidyl ether reduced by the glycidyloxy groups and R_{06} is a divalent radical of a diol reduced by the hydroxyl group.

83. A polyester having identical or different structural elements chosen from the group of structural elements of the formulae (f), (g), (h) and (i), where at least the structural elements of the formulae [sic] (f) or (g) or both must be present




in which R_{00} and R_{010} independently of one another are a divalent radical of a strained cycloolefin or a divalent radical with a strained cycloolefin, R_{011} is a divalent radical of a dicarboxylic acid reduced by the carboxyl groups and R_{012} is a divalent radical of a diol reduced by the hydroxyl group.

84. A polyamide having identical or different structural elements chosen from the group of structural elements of the formulae (j), (k), (l) and (m), where at least the structural elements of the formulae [sic] (j) or (k) or both must be present



in which R_{013} and R_{014} independently of one another are a divalent radical of a strained cycloolefin or a divalent radical with a strained cycloolefin, R_{015} is a divalent radical of a dicarboxylic acid reduced by the carboxyl groups and R_{016} is a divalent radical of a diamine reduced by the amino groups.

85. A polyurethan and polyurea or copolymer thereof having identical or different structural elements chosen from the group of structural elements of the formulae (n), (o), (p) and (q), where at least the structural elements of the formulae [sic] (n) or (o) or both must be present



in which R_{017} and R_{018} independently of one another are a divalent radical of a strained cycloolefin or a divalent radical with a strained cycloolefin, R_{019} is a divalent radical of a diisocyanate reduced by the cyanate groups and R_{020} is a divalent radical of a diamine or of a diol reduced by the amino or hydroxyl groups, and the X_{02} independently of one another are -O- or -NH-.

86. A copolymer of strained cycloolefins with fused at least bicyclic cycloaliphatic dienes which contain at least two olefinic double bonds in different rings and ethylenically unsaturated comonomers, with the exception of copolymers of norbornene with ethylene and, if desired, further olefinic comonomers.

87. A copolymer according to claim 86, wherein it contains recurring structural elements of the formula (r) and of the formula (s)



in which

R_{021} is C_2 - C_{10} alkylene, onto which an alkenylene having 2 to 6 C atoms is bonded directly or via a fused-on cycloalkylene ring having 5 to 8 C atoms;

R_{022} is H, F, C_1 - C_{12} alkyl, -COOH, -C(O)O- C_1 - C_{12} alkyl, -C(O)-NH- C_1 - C_{12} alkyl or -C(O)-NH₂;

- R_{023} is H, F, Cl, CN or C_1-C_{12} alkyl;
 R_{024} is H, F, Cl, CN, OH, C_1-C_{12} alkyl, C_1-C_{12} alkoxy, phenyl which is unsubstituted or substituted by OH, Cl, Br, C_1-C_4 alkyl, C_1-C_4 alkoxy, $-C(O)OC_1-C_{12}$ alkyl, $-C(O)-NH_2$, $-SO_3H$, $-COOH$, $-C(O)-NH-C_1-C_{12}$ alkyl or $-SO_3-C_1-C_{12}$ alkyl, or is $-C(O)OH$, $-C(O)O-C_2-C_{12}$ hydroxyalkyl, $-C(O)O-C_1-C_{12}$ alkyl, $-C(O)-NH_2$ or $-C(O)-NH-C_1-C_{12}$ alkyl; and
 R_{025} is H, F or C_1-C_{12} alkyl.

88. A polymer with a carbon backbone, which is a metathesis polymers of strained cycloolefins with a double bond in the ring, or copolymeric metathesis polymers of strained cycloolefins with a double bond in the ring and olefinically unsaturated comonomers, of which the olefinic double bonds in the polymer backbone are reacted partly or completely with open-chain or cyclic 1,3-dienes having 4 to 12 C atoms in a Diels-Alder reaction to give cycloalkenylene radicals having 6 to 14 C atoms.

89. A polymer according to claim 88, wherein the metathesis polymer contains recurring structural elements of the formula (t)



in which A_1 is mono- or bicyclic C_5-C_8 cycloalkenylene.

90. A polymer according to claim 88, wherein the metathesis polymer [lacuna] recurring structural units of the formula (u)



and recurring structural elements of the formula (w)



in which A_1 , together with the $-\text{CH}-\text{CH}-$ group, is bicyclic C_5-C_9 cycloalkenylene, and R_{026} is C_1-C_{12} alkylene, and, if desired, recurring structural elements of the formula (s) according to claim 87.

91. A polymer with a carbon backbone, which is a homo- or copolymer of 1,3-dienes and, if desired, olefinically unsaturated monomers, of which the olefinic double bonds in the polymer backbone are reacted partly or completely with open-chain or cyclic 1,3-dienes having 4 to 12 C atoms in a Diels-Alder reaction to give cycloalkenylene radicals having having [sic] 6 to 14 C atoms.

92. A polymer according to claim 91, wherein the polymer contains recurring structural elements of the formula (t)



in which A_1 is mono- or bicyclic C_5-C_9 cycloalkenylene.

93. A polymer according to claim 92, wherein the polymer [lacuna] recurring structural units of the formula (y)



and recurring structural elements of the formula (z)



in which A_1 , together with the $-\text{CH}-\text{CR}_{027}$ group, is bicyclic C_5-C_9 cycloalkenylene, and R_{027} is H, Cl or C_1-C_{12} alkyl, and, if desired, recurring structural elements of the formula (s) according to claim 87.

Polymerizable composition, process for the production of crosslinked polymers,
and crosslinked polymers

Abstract

Composition comprising (a) catalytic amounts of a one-component catalyst for metathesis polymerization and (b) at least one polymer with strained cycloalkenylene radicals bonded in the polymer backbone, alone or as a mixture with strained cycloolefins. The composition can be polymerized thermally or photochemically by metathesis polymerization and is suitable for the production of shaped articles, coatings and relief images.

THIS PAGE BLANK (USPTO)